

PU - Foam

- Electrostatic conductive
- Complies with EN 61340-5-1 and ANSI/ESD S20.20-1999
- Open cells
- Soft
- **Colour:** Black



Physical properties:

	Standard	Typical values
Density	DIN 53420	20 kg/m ³
Tensile Strength	DIN 53571	>50 kPa
Elongation	DIN 53571	150 %
Compressive strength	DIN 53577	at 40% bending: 2,5 kPa
Temperature range	Internal test	- 30° to + 90° C
Thickness		6 mm, 15 mm

Electrical properties:

	Standard	typical values
Surface resistance R _s	EN 61340-5-1 EN 61340-2-3	10 ⁴ - 10 ⁵ Ω