

Shrinkstat



- For automatic and manual wrapping of unpopulated PCB's, I.C. shipping tubes etc.
- Electrostatic dissipative Polyolefine
- Complies with EN 61340-5-1 and ANSI/ESD S20.20-1999
- Polycarbonate compatible, amine-free
- Non-corrosive, clean surface
- Excellent shrinkability
- Recyclable
- Transparent



Technical data:

Properties	Standard	Typical values
Mechanical		
Thickness	ASTM D-882	25 µm
Tensile strength	ASTM D-882	
MD		400 kg/cm ²
TD		800 kg/cm ²
Elongation	ASTM D-882	
MD		125 %
TD		120 %
Tear strength:	ASTM D-1992	
MD		11 g/µm
TD		12 g/µm
Shrinkage:	ANSI/ASTM D-2732	
MD		50 %
TD		60 %
Friction coefficient:	ASTM D-1894	0,4
Electrical		
Surface resistance:	EN 61340-5-1	10 ¹⁰ - 10 ¹¹ Ω
Decay time:	EN 61340-5-1	< 2 sec.

MD = Machine Direction

TD = Transversal Direction