

Permastat® Stretch Film



- Electrostatic dissipative Polyolefine (proprietary formulation)
- Good mechanical properties
- Suitable for machine and hand wrapping
- Recyclable
- Colour: Pink



Technical data:

Property	Test Method	Typical values
Mechanical		
Thickness	ASTM D-882	25 µm
Tensile Strength	ASTM D-882	
MD		35 N/mm ²
TD		30 N/mm ²
Elongation	ASTM D-882	
MD		600 %
TD		700 %
Tackiness	In house test	16 gr/5 cm
Puncture Energy	In house test	400 N/mm
Electrical		
Typical surface resistance	IEC 61340-5-1	10 ¹⁰ - 10 ¹¹ Ω

MD = Machine Direction

TD = Transversal Direction