

Cation–Anion Interaction-Directed Molecular Design Strategy for Mechanochromic Luminescence

Gaocan Li, Feijie Song, Di Wu, Jingbo Lan, Xingyan Liu, Jie Wu, Shuaijun Yang, Dan Xiao, and Jingsong You*

Mechanofluorochromic materials have great potential for a wide variety of applications such as sensors, memory devices, motion systems, security systems, and so forth. However, only few design principles have been disclosed, which greatly impedes the growth of mechanofluorochromic dyes. Here, a strategy of molecular design for mechanochromic luminescence is reported, based on the cation–anion interaction-directed switching of molecular stacking. On the basis of this strategy, a series of common N-heteroaromatic onium fluorophores such as imidazolium, 1,2,4-triazolium, triazolopyridinium, benzoimidazolium, γ -carbolinium, and pyridinium salts have been designed and proved to have striking reversible mechanofluorochromic behaviors. The simple attachment of a non-fluorescent imidazolium unit to the pyrene scaffold through a flexible carbon chain can even trigger the mechanofluorochromic phenomenon, which gives a consummate interpretation that the cation–anion interaction can be considered as an important general tool to design organic mechanochromic luminescent materials.

1. Introduction

Mechanochromic luminescent materials, as a kind of “smart” stimuli-responsive materials, have great potential for various applications such as sensors, memory devices, motion systems, security systems, and so forth.^[1,2] Although many cases have been reported in the literature, the understanding of the relationship between molecular structures and mechano-responsive behaviors still remains obscure. Up to now, only few examples demonstrate the rational molecular designs of mechanochromic luminescence.^[2] Such hurdles have greatly impeded the growth of mechanofluorochromic dyes. In particular, the number of mechanical-stimuli-responsive organic small molecule materials is still limited despite the popularity of organic fluorophores.^[1,2] Currently, mechanically

induced luminescence changes have been observed mainly in certain metal (Au, Cu, Ag, Zn, Pt, Al, and Pd)^[3–9] and boron complexes,^[10] anthracene and pyrene-based molecules,^[11–14] oligo(*p*-phenylene vinylene) derivatives,^[15,16] and others.^[17–21] Undoubtedly, it is highly desirable, yet very challenging, to establish fundamental principles of molecular design that can be applied to assemble a large number of libraries of mechanofluorochromic dyes.

Mechanochromic materials commonly rely on the changes in physical molecular packing modes.^[1,2] From this perspective, mechanochromic phenomenon is ascribed to a reversible switching between two different stable or metastable mechano-dependent molecular stacking models in the solid state. Generally, molecular stacking may be controllable by various secondary intermolecular interactions.

Metal-metal interaction, π – π interaction, hydrogen bonding and dipole-dipole interaction have been proposed as possible parameters to trigger an alteration of the stacking modes.^[1] However, the cation–anion interaction, an important type of interaction, has been almost entirely ignored for the rational design of organic mechanochromic luminescent materials.


To enable a reproducible switching of mechano-dependent molecular stacking modes, a subtle balance of diverse intra- and intermolecular interactions appears to represent a crucial prerequisite.^[1,11,15] It is well-known that the cation–anion interaction is one of the important interactions to govern the molecular packing modes of onium salts and, thus, can lead to changes in the properties such as melting point, density, viscosity, and electrical conductivity.^[22–25] Given that the molecular assemblies of organic cations with a rich set of anions can offer a great abundance of cation–anion interactions, we envisioned that the cation–anion interactions and other intra- and intermolecular interactions could be regarded as ideal competing factors to reach such a balance through the variation of counteranions. Thus, onium salts would be promising candidates for mechanochromic luminescent materials.

Another important requirement to achieve these goals mentioned above is that the organic cation exhibits significant luminescent properties in the solid state. Imidazolium salts have been shown to be the most common type of ionic liquids (ILs), typically bearing two alkyl groups at the two nitrogen atoms of the imidazolium core. Unfortunately, these imidazolium salts

G. Li, Dr. F. Song, Prof. Dr. D. Wu, Prof. Dr. J. Lan, X. Liu, J. Wu, Dr. S. Yang, Prof. Dr. D. Xiao, Prof. Dr. J. You
Key Laboratory of Green Chemistry and Technology of Ministry of Education
College of Chemistry and State Key Laboratory of Biotherapy
West China Medical School
Sichuan University
29 Wangjiang Road, Chengdu, 610064, PR China
E-mail: jsyou@scu.edu.cn



DOI: 10.1002/adfm.201302086



Alkyl alkyl ionic liquids (ILs) Aryl alkyl imidazolium salts

Scheme 1. Molecular modification of imidazolium salts.

generally exhibit very low emission intensities in the visible region ($\Phi_f < 0.05$) probably due to their relatively small chromophores.^[26] Consequently, it becomes difficult to observe the mechanofluorochromic phenomenon. Recently, a new generation of aryl alkyl ionic liquids (TAAILs) containing alkyl and aryl substituents at the nitrogen atoms has been developed.^[27] Their physicochemical and electronic properties may be tuned by altering anions or substituents at the nitrogen atoms. Herein, we disclose that the modular modification of the phenylimidazolium core can offer minimal fluorophores that not only emit intense visible light in the solid state, but also exhibit reversible mechanochromic luminescence through a simple adjustment of anion (Scheme 1).

2. Results and Discussion

2.1. Influence of Anions on Mechanochromic Luminescence

The phenylimidazolium salts, as a parent core, do not show luminescence emission in the visible region. Considering that the electron-deficient imidazolium ring is the electron-accepting moiety, the proper introduction of an electron donor such as dialkylamino on the benzene ring would present a “push–pull” π -electron mode, offering an unlocking opportunity for visible photoluminescence. The synthesis of aryl alkyl imidazolium salts with different counteranions included the copper-catalyzed *N*-arylation of imidazoles, followed by the quaternization of the imidazole ring at the N3-position with alkyl halide, and subsequent anion exchange.^[28] The initially prepared imidazolium salt **1·I** with an iodine anion displayed very weak fluorescence ($\Phi_f = 0.002$) in the solid state, which was presumably attributed to the external heavy atom effect of a halogen atom. After surveying a series of common counteranions such as NTf_2^- (bis((trifluoromethyl)sulfonyl)amide), PF_6^- , OTf^- , BF_4^- and $\text{N}(\text{CN})_2^-$, the NTf_2^- anion was proven

to be an ideal counteranion to enable excellent luminescent properties (Table 1). Moreover, the emission wavelengths varied with different counteranions, which implied that different molecular packing modes could be gained by tuning anions.

Owing to the low emission quantum yield of **1·I** in the solid state, we chose five counteranions (i.e., NTf_2^- , PF_6^- , OTf^- , BF_4^- , and $\text{N}(\text{CN})_2^-$) to illustrate the correlation between the cation–anion interaction and the mechanochromic performance of **1·X** ($\text{X} = \text{counteranion}$). After three minutes of pressing under 6 MPa using an oil press, **1·NTf₂**, **1·PF₆**, **1·OTf**, **1·BF₄**, and **1·N(CN)₂** underwent redshifts of the peak emission wavelengths (approximately 102 nm, 90 nm, 78 nm, 36 nm, and 7 nm, respectively) (Table 1 and Figure 1a), which was in good agreement with the known order of the strength of the cation–anion interaction as following: $\text{NTf}_2^- < \text{PF}_6^- < \text{OTf}^- < \text{BF}_4^- < \text{N}(\text{CN})_2^-$.^[22–25] It hinted that the strength of the cation–anion interaction could determine the mechanochromic luminescence property to a certain extent. The NTf_2^- anion associated with the delocalization of negative charge and the shielding effect of the sulfonyl oxygens and trifluoromethane groups is widely used to reduce the capacity of the cation–anion interaction to develop low melting ionic liquids.^[29] In this context, the NTf_2^- anion was well demonstrated as an ideal counteranion to induce mechanochromic luminescence. We rationalized that the weak interactions between the imidazolium cation and the NTf_2^- anion made molecular stacking relatively loose. The loose molecular stacking was more susceptible to tiny slip by mechanical stimuli. It is worth noting that **1·NTf₂** is one of the smallest fluorophore exhibiting an obvious mechanofluorochromic behavior, which constitutes one of the longest emission wavelength redshifts reported so far.^[2,14]

2.2. Mechanochromic Luminescence of **1·NTf₂**

To gain further understanding of the mechanochromic performance, the influence of applied pressure on the mechanochromic luminescence of **1·NTf₂** was investigated. As the operating pressure increased from 0 to 6 MPa, a gradual redshift of the fluorescence emission of the **1·NTf₂** powder appeared with a peak wavelength change from 407 nm to 509 nm (Figure 1b), which implied that different stress conditions could lead to the tiny dissimilarity in the molecular aggregation. However, after the pressure exceeded 6 MPa, no further redshifts of the emission wavelengths were observed.

Table 1. Physical and photophysical properties of onium salts **1·X**.

1·X	M.p. [°C]	λ_{abs} [nm] ^{a)} (in CHCl_3)	λ_{em} (nm) ^{b)} (Φ_f) ^{c)} (pristine)	λ_{em} (nm) ^{b)} (under 6.0 MPa pressure)	Emission wavelength shift [nm]
1·NTf₂	82–83	299	407 (0.76)	509	102
1·PF₆	133–134	299	371 (0.12)	461	90
1·OTf	58–60	300	423 (0.59)	501	78
1·BF₄	156–157	302	433 (0.45)	469	36
1·N(CN)₂	108–110	298	418 (0.53)	425	7

^{a)}Only the wavelengths of maximum absorption are shown; ^{b)}Excited at 370 nm (excited at 350 nm for **1·PF₆**); ^{c)}Absolute emission quantum yields estimated by calibrated integrating sphere system.




Figure 1. a) Mechanochromic performance of onium salts **1-X** and **C-X** with different counteranions upon grinding and under pressure (3 min, 6 MPa). b) Normalized emission spectra of the powder under the external pressure and yellow crystals of **1-NTf₂** excited at 370 nm. c) Chromaticity analysis of **1-NTf₂** in different states shown in (a,b): a linear trajectory of chromaticity coordinates plotted on a 1931 CIE diagram.

The imidazolium salt **1-NTf₂** is a white crystalline powder as prepared and displayed a blue emission ($\lambda_{\text{em}} = 407 \text{ nm}$) with a fluorescence quantum yield ($\Phi_f = 0.76$) in the solid state (Figure 2a,b,n). After being heated to the melting state and cooled down to room temperature, the pristine white powder switched to a pale yellow solid emitting a yellowish-green luminescence ($\lambda_{\text{em}} = 518 \text{ nm}$, $\Phi_f = 0.25$), which could remain for several months at room temperature (Figure 2c,d,n). Upon a gentle grinding with a spatula, the blue emission was converted to the yellowish-green luminescence (Figure 2e,f,n). Figure 1a,c clearly indicated that the grinding process exhibited a more redshifted light emission than the pressing operation (111 nm versus 102 nm), which hinted that these two different operations might have different effect on molecular packing or conformation variations. As illustrated in the confocal laser-scanning microscopy (CFLSM) images, even a tiny scratch on the surface of colorless crystals also resulted in a yellow emission color (as the emission below 500 nm was filtered out) under irradiation at 405 nm (Figure 2j–m). The perturbed yellowish-green-emitting




Figure 2. Photographs of **1-NTf₂** under ambient light and UV irradiation at 365 nm: a) the pristine crystalline powder under ambient light, and b) under UV light; c) the solid under fast cooling from its melting state under ambient light, and d) under UV light; e) the pristine solid after grinding the right-half with a spatula under ambient light, and f) under UV light; g) the entirely ground solid, and h) the sample after thermal annealing under UV light; and i) the regeneration of the yellowish-green emission demonstrated by the letters “SCU” and the Chinese characters “Sichuan University” written with a spatula. CFLSM images of colorless single crystal of **1-NTf₂**: j) the image of unscratched crystal under ambient light, and k) under irradiation at 405 nm; and l) the image of crystal with a tiny scratch under ambient light, and m) under irradiation at 405 nm (as the emission below 500 nm was filtered out). n) Normalized emission spectra of **1-NTf₂** in different states excited at 370 nm. o) Normalized UV-visible absorption spectra of **1-NTf₂** in thin film before and after grinding. p) Reversible switching of emission of **1-NTf₂** by repeated grinding-heating cycles ($\lambda_{\text{ex}} = 370 \text{ nm}$).




Figure 3. Photographs of single crystals of **1·NTf₂**: a) the colorless single crystal under ambient light, and b) under UV light ($\lambda_{\text{ex}} = 365$ nm); and c) the yellow single crystal under ambient light, and d) under UV light ($\lambda_{\text{ex}} = 365$ nm). Molecular stacking of the colorless single crystals of **1·NTf₂**: e) side view; and f) partial view of the crystal packing with anions omitted for clarity. g) Powder X-ray diffraction patterns of **1·NTf₂** in different states.

sample was treated with thermal annealing at approximately 80 °C to revert back to the blue emission (Figure 2g,h,n), and recovered again by subsequent regrinding (Figure 2i). The emission of **1·NTf₂** could be reversibly switched between the two different phases by repeated grinding and annealing treatments with no obvious fatigue response (Figure 2p).

2.3. Investigation of Plausible Mechanism of Piezochromic Luminescence of **1·NTf₂**

To gain insight into the mechanism of piezochromic luminescence of **1·NTf₂**, both single crystal X-ray diffraction (XRD) and powder X-ray diffraction (PXRD) measurements were conducted. After numerous attempts, two different forms of crystals of **1·NTf₂** were fortunately isolated from the dilute and concentrated ethyl acetate solutions in refrigerator, respectively (Figure 3a–d). X-ray single crystal structural analysis of the colorless crystals revealed that the molecules stacked in a face-to-face orientation with a slip angle of approximately 32° along the long molecular axis, and a dihedral angle of approximately 15° between the phenyl ring and the imidazolium ring (Figure 3e,f). Furthermore, only weak π – π interactions in the sheet-like stacking pattern were observed through analysis with the program PLATON. Interestingly, the yellow crystals did exhibit the stacking pattern and the cell parameters identical to the colorless ones (Supporting Information, Figures S3,S4, and Table S2). Although the XRD patterns of the pristine powder agreed well with those simulated from the single crystal data in both crystalline forms, the diffraction data of the ground solid showed tiny changes in the diffrac-

tion peaks, which disclosed the possible formation of new aggregates (Figure 3g and Figure S5, Supporting Information). The colorless crystals displayed blue emission very similar to the emission spectra of the pristine powder and the annealed sample with the emission wavelength of about 407 nm (Figures 3b, 2n). The yellow ones emitted blue-green fluorescence, which was neither consistent with the ground sample nor the pristine powder (Figures 3d, 2n, 1b). Therefore, one could suggest that the mechanism was different from the well-known typical models, in which obvious changes in the XRD patterns are observed.^[1,2]

Subsequently, absorption and fluorescence decay measurements of the pristine and ground samples of **1·NTf₂** were carried out. The absorption spectra clearly showed a new small absorption peak at a longer wavelength of 341 nm after grinding (Figure 2o), which suggested the generation of a new aggregate during the grinding process. The phenomena could also be explained by the different fluorescence emissions and lifetimes of the white pristine powder ($\lambda_{\text{em}} = 407$ nm, $\tau = 3.5$ ns) and the yellowish ground sample ($\lambda_{\text{em}} = 518$ nm, $\tau = 4.2$ ns) (Figure S6, Supporting Information). Furthermore, chromaticity analysis of **1·NTf₂** illustrated that the samples in different states were probably binary blends of the blue-emitting aggregate (absorption at 321 nm) and the new aggregate (absorption at 341 nm) (Figure 1c, 2o). The concentration of the new aggregate in the yellow crystals was too low to be detected by single crystal XRD measurements. Differential scanning calorimetry (DSC) analysis for the pristine and ground samples of **1·NTf₂** showed that the ground sample generated a new, very small endothermic peak at approximately 71 °C before melting in the first heating curve (Figure 4), which further suggested the formation of new aggregate with a low concentration.^[13] However, despite very small amounts of the new aggregate, its luminescence efficiency reached a high enough level to cause the pronounced change in fluorescence emission.^[3] We assumed that a tiny slip of the molecular stacking after grinding or pressure led to the generation of new aggregates ascribed to the local distortions in the whole crystalline structure or the formation of the local amorphous





Figure 4. DSC curves (first heating) of **1·NTf₂** in different states: a) pristine solid and b) ground solid.

Table 3. Physical and photophysical properties of onium salts.



Compd.	M.p. [°C]	λ_{abs} [nm] ^{a)} (in CHCl ₃)	λ_{em} [nm] ^{b)} (Φ_f) ^{c)} (pristine)	λ_{em} [nm] ^{b)} (ground)	Emission wavelength shift [nm]
P-NTf ₂	59-61	375	415 (0.07)	486	71
Bz-NTf ₂	65-68	316	475 (0.55)	511	36
Pz-NTf ₂	92-93	345	434 (0.06)	472	38
Py-NTf ₂	146-147	478	648 (0.09)	712	64
C-NTf ₂	163-164	338	456 (0.23)	485	29

^{a)}Only the maximum absorption wavelengths are shown; ^{b)}Excited at the corresponding maximum excitation wavelength; ^{c)}Absolute emission quantum yields estimated by calibrated integrating sphere system.

luminescence. This strategy has been successfully harnessed to discover a wide range of onium piezochromic luminescent materials such as imidazolium salts, 1,2,4-triazolium salts, triazopyridinium salts, benzimidazolium salts, γ -carbolinium salts, and pyridinium salts. The possible mechanism of piezochromic luminescence of **1**·NTf₂ has been proposed, but each onium salt itself may have an idiographic model. Although a deeper understanding of the relationship between molecular structures and mechano-responsive behaviors is still required, these first results have already opened a new avenue of investigation into stimuli-responsive luminescent materials, and may enable organic onium salts to find an array of novel applications in sensors, memory devices, liquid crystals, optical displays, and rewritable optical media.

4. Experimental Section

Instrumentation: NMR spectra were obtained on a Bruker AV II-400 or Bruker AV II-600. Fluorescence emission spectra were obtained using a Horiba Jobin Yvon-Edison Fluoromax-4 fluorescence spectrometer. Absorption spectra were obtained on a HITACHI U-2910 spectrometer. Fluorescence lifetime data were determined in 1 mm cell on a Hamamatsu FL920S instrument. Differential scanning calorimetry (DSC) data was performed using a TA instrument DSC-Q200 1474 (rate = 5 °C min⁻¹, range = -40 to 200 °C). The ESI-TOF mass spectra were recorded with a Waters Q-ToF premier instrument. X-Ray single-crystal diffraction data were collected on an Oxford Xcalibur E CCD area-detector diffractometer. Melting points were determined with XRC-1 and are uncorrected.

General Procedure for the Synthesis of Neutral N-Arylheterocycles: A flame-dried Schlenk tube with a magnetic stir bar was charged with aryl iodide (5.0 mmol), free (N-H) heterocycle (6.0 mmol), CuI (0.380 g, 1.0 mmol), base (10.0 mmol) and DMF (5.0 mL) under N₂. The reaction system was then evacuated and backfilled with N₂ for twice. After stirring at the indicated temperature for 36 h, DMF was removed under reduced

pressure and the residue was purified by column chromatography on silica gel.

General Procedure for the Synthesis of Onium Salts: A Schlenk tube with a magnetic stir bar was charged with neutral N-arylheterocycles, alkyl halide and solvent under N₂. The resulting mixture was stirred at indicated temperature for 24 h and the solvent was then removed. The residue was purified by column chromatography on silica gel and the product was further purified by recrystallization.

Crystallographic data for the structures reported in this paper have been deposited with the Cambridge Crystallographic Data Centre as supplementary publication no. CCDC-912422 and no. CCDC-912423 for colorless crystal and yellow crystal of **1**·NTf₂, respectively.

Supporting Information

Supporting Information is available from the Wiley Online Library or from the author.

Acknowledgements

This work was supported the National High Technology Research and Development Program of China (863 Program) (No. 2013AA031901) and the National NSF of China (Nos 21025205, 21272160, and 21021001).

Received: June 19, 2013

Revised: August 20, 2013

Published online: September 3, 2013

[1] Y. Sagara, T. Kato, *Nat. Chem.* **2009**, *1*, 605.

[2] Z. Chi, X. Zhang, B. Xu, X. Zhou, C. Ma, Y. Zhang, S. Liu, J. Xu, *Chem. Soc. Rev.* **2012**, *41*, 3878.

- [3] S. Perruchas, X. F. L. Goff, S. Maron, I. Maurin, F. Guillen, A. Garcia, T. Gacoin, J.-P. Boilot, *J. Am. Chem. Soc.* **2010**, *132*, 10967.
- [4] H. Ito, T. Saito, N. Oshima, N. Kitamura, S. Ishizaka, Y. Hinatsu, M. Wakeshima, M. Kato, K. Tsuge, M. Sawamura, *J. Am. Chem. Soc.* **2008**, *130*, 10044.
- [5] T. Lasanta, M. E. Olmos, A. Laguna, J. M. López-de-Luzuriaga, P. Naumov, *J. Am. Chem. Soc.* **2011**, *133*, 16358.
- [6] S. Mizukami, H. Houjou, K. Sugaya, E. Koyama, H. Tokuhisa, T. Sasaki, M. Kanesato, *Chem. Mater.* **2005**, *17*, 50.
- [7] V. N. Kozhevnikov, B. Donnio, D. W. Bruce, *Angew. Chem. Int. Ed.* **2008**, *47*, 6286.
- [8] H. Bi, D. Chen, D. Li, Y. Yuan, D. Xia, Z. Zhang, H. Zhang, Y. Wang, *Chem. Commun.* **2011**, *47*, 4135.
- [9] A. L. Balch, *Angew. Chem. Int. Ed.* **2009**, *48*, 2641.
- [10] G. Zhang, J. Lu, M. Sabat, C. L. Fraser, *J. Am. Chem. Soc.* **2010**, *132*, 2160.
- [11] Y. Sagara, T. Mutai, I. Yoshikawa, K. Araki, *J. Am. Chem. Soc.* **2007**, *129*, 1520.
- [12] Y. Sagara, T. Kato, *Angew. Chem. Int. Ed.* **2008**, *47*, 5175.
- [13] Z. Zhang, D. Yao, T. Zhou, H. Zhang, Y. Wang, *Chem. Commun.* **2011**, *47*, 7782.
- [14] Y. Dong, B. Xu, J. Zhang, X. Tan, L. Wang, J. Chen, H. Lv, S. Wen, B. Li, L. Ye, B. Zou, W. Tian, *Angew. Chem. Int. Ed.* **2012**, *51*, 10782.
- [15] J. Kunzelman, M. Kinami, B. R. Crenshaw, J. D. Protasiewicz, C. Weder, *Adv. Mater.* **2008**, *20*, 119.
- [16] S.-J. Yoon, J. W. Chung, J. Gierschner, K. S. Kim, M.-G. Choi, D. Kim, S. Y. Park, *J. Am. Chem. Soc.* **2010**, *132*, 13675.
- [17] X. Luo, J. Li, C. Li, L. Heng, Y. Q. Dong, Z. Liu, Z. Bo, B. Z. Tang, *Adv. Mater.* **2011**, *23*, 3261.
- [18] J. Wang, J. Mei, R. Hu, J. Z. Sun, A. Qin, B. Z. Tang, *J. Am. Chem. Soc.* **2012**, *134*, 9956.
- [19] N. Mizoshita, T. Tani, S. Inagaki, *Adv. Mater.* **2012**, *24*, 3350.
- [20] M.-J. Teng, X.-R. Jia, S. Yang, X.-F. Chen, Y. Wei, *Adv. Mater.* **2012**, *24*, 1255.
- [21] Y. Ren, W. H. Kan, M. A. Henderson, P. G. Bomben, C. P. Berlinguette, V. Thangadurai, T. Baumgartner, *J. Am. Chem. Soc.* **2011**, *133*, 17014.
- [22] S. Tsuzuki, H. Tokuda, K. Hayamizu, M. Watanabe, *J. Phys. Chem. B* **2005**, *109*, 16474.
- [23] K. Fumino, A. Wulf, R. Ludwig, *Angew. Chem. Int. Ed.* **2008**, *47*, 3830.
- [24] K. Fumino, A. Wulf, S. P. Verevkin, A. Heintz, R. Ludwig, *ChemPhys-Chem* **2010**, *11*, 1623.
- [25] S. Wei, X.-G. Wei, X. Su, J. You, Y. Ren, *Chem. Eur. J.* **2011**, *17*, 5965.
- [26] A. Paul, P. K. Mandal, A. Samanta, *J. Phys. Chem. B* **2005**, *109*, 9148.
- [27] S. Ahrens, A. Peritz, T. Strassner, *Angew. Chem. Int. Ed.* **2009**, *48*, 7908.
- [28] L. Zhu, G. Li, L. Luo, P. Guo, J. Lan, J. You, *J. Org. Chem.* **2009**, *74*, 2200.
- [29] J. D. Holbrey, W. M. Reichert, R. D. Rogers, *J. Chem. Soc., Dalton Trans.* **2004**, 2267.