

# Prolonged Hot Electron Dynamics in Plasmonic-Metal/Semiconductor Heterostructures with Implications for Solar Photocatalysis\*\*

Joseph S. DuChene, Brendan C. Sweeny, Aaron C. Johnston-Peck, Dong Su, Eric A. Stach, and Wei David Wei\*

**Abstract:** Ideal solar-to-fuel photocatalysts must effectively harvest sunlight to generate significant quantities of long-lived charge carriers necessary for chemical reactions. Here we demonstrate the merits of augmenting traditional photoelectrochemical cells with plasmonic nanoparticles to satisfy these daunting photocatalytic requirements. Electrochemical techniques were employed to elucidate the mechanics of plasmon-mediated electron transfer within Au/TiO<sub>2</sub> heterostructures under visible-light ( $\lambda > 515$  nm) irradiation in solution. Significantly, we discovered that these transferred electrons displayed excited-state lifetimes two orders of magnitude longer than those of electrons photogenerated directly within TiO<sub>2</sub> via UV excitation. These long-lived electrons further enable visible-light-driven H<sub>2</sub> evolution from water, heralding a new photocatalytic paradigm for solar energy conversion.

Solar photocatalysis for chemical fuel production represents a promising approach to sustainably satisfy escalating global energy demands.<sup>[1]</sup> Unfortunately, current photocatalysts exhibit limited solar-to-fuel efficiencies because the lifetimes of photogenerated electron-hole pairs (ps– $\mu$ s) are often incommensurate with the prolonged timescales required to facilitate photocatalytic reactions (ms–s) at the semiconductor surface.<sup>[1,2a]</sup> This kinetic discrepancy hinders the realization of efficient photosynthetic devices for solar energy conversion.<sup>[1]</sup> Recently, the integration of Au or Ag nanoparticles (NPs) into traditional photoelectrochemical (PEC) cells has been shown to endow the plasmonic composite with enhanced photocatalytic performance by utilizing the surface plasmon resonance (SPR) of plasmonic-metal NPs.<sup>[2–4]</sup> These

SPs predominantly relax non-radiatively via Landau damping, yielding highly energetic “hot” electrons that transiently populate electronic states above the metal Fermi level.<sup>[5]</sup> When plasmonic-metal NPs are proximal to a semiconductor with a dense manifold of conduction band (CB) states, the hot electrons can be directly injected into the energetically accessible CB levels of the semiconductor.<sup>[2,3,5,6]</sup> This plasmon-mediated electron transfer (PMET) process constitutes a unique photosensitization strategy enabling these plasmonic NPs to serve as light-harvesting assemblies when anchored to a semiconductor scaffold.<sup>[2,3,5]</sup>

Although PMET occurs on an ultrafast timescale ( $t < 240$  fs),<sup>[6a]</sup> the temporal evolution of these transferred electrons within the semiconductor CB after PMET deserves further study. The average lifetime of hot electrons within the semiconductor CB represents an important catalytic parameter, as these photoexcited electrons must persist long enough to facilitate surface reactions.<sup>[7]</sup> Previous dynamics studies were conducted in air using femtosecond pulsed-laser excitation,<sup>[6a,b]</sup> and thus did not adequately capture the excited-state dynamics relevant to PEC systems operating in solution.<sup>[8]</sup> Knowledge of these hot electron dynamics within a plasmonic device under simulated solar conditions is therefore crucial to the further optimization and eventual exploitation of the PMET process in artificial photosynthetic constructs.

To that end, we used a plasmonic PEC cell to elucidate the PMET mechanism in plasmonic-metal/semiconductor (Au/TiO<sub>2</sub>) heterostructures during in situ (i.e. aqueous solution) operation. This device architecture renders the plasmonic composite electronically addressable, providing an ideal platform to probe the PMET process. These PEC studies unambiguously confirm that visible-light excitation of the plasmonic Au/TiO<sub>2</sub> photoanode induces PMET from the Au NPs to the CB of the TiO<sub>2</sub> nanowires (NWs). Significantly, we monitored the excited-state lifetimes ( $\tau_n$ ) of these hot electrons within the semiconductor CB in situ and found that the PMET process yields excited-state electrons with prolonged lifetimes compared to those of electrons excited directly within TiO<sub>2</sub>. These long-lived electrons were subsequently harnessed for visible-light-driven hydrogen (H<sub>2</sub>) evolution from water, demonstrating the utility of PMET for solar photocatalysis.

A TiO<sub>2</sub> NW array was chosen as the Au NP support to unambiguously assign the visible-light response to the plasmonic NPs, while the semiconductor NW served solely as a conduit for hot electron transport. Moreover, relative to planar semiconductor configurations, this nanowire topology has been shown to improve PEC performance by decoupling the directions for light absorption and charge transport within


[\*] J. S. DuChene, B. C. Sweeny, Prof. Dr. W. D. Wei  
Department of Chemistry and  
Center for Nanostructured Electronic Materials  
University of Florida, Gainesville, FL 32611 (USA)  
E-mail: wei@chem.ufl.edu

Dr. A. C. Johnston-Peck, Dr. D. Su, Dr. E. A. Stach  
Center for Functional Nanomaterials  
Brookhaven National Laboratory, Upton, NY 11973 (USA)

[\*\*] W.D.W. acknowledges financial support from the NSF under grant number CHE-1038015, the CCI Center for Nanostructured Electronic Materials, ORAU, Sigma Xi, and the University of Florida. We thank W. Niu for SEM imaging and K. Farnell, Design Driven Media, Inc. for artwork. Research carried out in part at the Center for Functional Nanomaterials at Brookhaven National Lab through user proposal number BNL-CFN-31913, supported by the U.S. Department of Energy, Office of Basic Energy Sciences under contract number DE-AC01-98CH10886.

Supporting information for this article is available on the WWW under <http://dx.doi.org/10.1002/anie.201404259>.


the device, while providing an uninterrupted conductive corridor for charge carriers to reach the back contact.<sup>[9]</sup> Scanning electron microscopy (SEM) showed that the TiO<sub>2</sub> NWs were perpendicularly oriented on the substrate with average lengths (*l*) of 2.2 ± 0.2 μm and diameters (*d*) of 200 ± 50 nm (Figure S1a–c). X-ray diffraction (XRD) confirmed that these NWs were monocrystalline and composed of rutile TiO<sub>2</sub> (Figure S1d), as initially reported.<sup>[9b]</sup> Plasmonic Au NPs (*d* = 20 ± 5 nm) were then photochemically grafted<sup>[10]</sup> directly onto the TiO<sub>2</sub> NWs to construct Au/TiO<sub>2</sub> heterojunctions free of surfactants and chemical linkers (see the Supporting Information). A dramatic color change occurred after photo-deposition, indicating the presence of plasmonic Au NPs (Figures S2 and S3). SEM analysis revealed that the Au NPs were distributed along the TiO<sub>2</sub> support but were predominantly located at the NW terminus (Figure 1a). Given the



**Figure 1.** Structural analysis of a typical plasmonic photoanode. a) SEM image of a plasmonic Au/TiO<sub>2</sub> photoanode on the FTO glass substrate. b) HAADF-STEM image demonstrating direct physical contact at the Au/TiO<sub>2</sub> interface ( $d_{\text{Au}(111)} = 2.35 \text{ \AA}$ ).

importance of the Au/TiO<sub>2</sub> interface to the PMET mechanism,<sup>[2]</sup> the heterojunction was further inspected by high-angle annular dark-field scanning transmission electron microscopy (HAADF-STEM). As shown in Figure 1b, a coherent interface was established at the Au/TiO<sub>2</sub> heterojunction, confirming that photodeposition yields the intimate physical contact requisite for PMET.

A suite of PEC experiments were then performed using a three-electrode electrochemical cell consisting of a plasmonic Au/TiO<sub>2</sub> photoanode (working), Pt wire (auxiliary), and Ag/AgCl (reference) electrode all immersed in a supporting electrolyte of 1M NaOH (see the Supporting Information). All electrode potentials (*E*) are reported relative to the reversible hydrogen electrode (RHE). Chronoamperometry was used to evaluate the PMET process with the plasmonic photoanode potentiostatically poised at  $E_{\text{appl}} = 1.20 V_{\text{RHE}}$  while being illuminated with periodic (3 s on/off) visible light ( $\lambda > 515 \text{ nm}$ ). This approach permits the selective excitation of the Au NPs while excluding any contribution from direct interband transitions within the TiO<sub>2</sub> support (Figure S4). As shown in Figure 2a, the plasmonic device exhibits a prompt and reproducible anodic photocurrent ( $J_{\text{ph}}$ ) when exposed to periodic visible-light irradiation. In contrast, the TiO<sub>2</sub>-only device produced no  $J_{\text{ph}}$  under identical conditions (Figure 2a). We therefore attribute the  $J_{\text{ph}}$  of



**Figure 2.** Photoelectrochemical data from TiO<sub>2</sub>-only (gray) and Au/TiO<sub>2</sub> (black) photoanodes. a) Chronoamperometry ( $J_{\text{ph}}(t)$ ) during periodic visible-light excitation. b) Photovoltage action spectrum difference ( $\Delta V_{\text{ph}}(\lambda)$ ) between photoanodes.


1  $\mu\text{A cm}^{-2}$  from the plasmonic device to hot electron injection via optical excitation of the Au NPs.

To further correlate the visible-light activity of the plasmonic photoanode to the optical properties of the Au NPs, the open-circuit voltage ( $V_{\text{oc}}$ ) was monitored as a function of incident photon energy. The occupancy of CB states within a semiconductor during optical excitation is given by the quasi-Fermi level ( $E_{\text{F}}^*$ ) of the device, which can be monitored externally via the  $V_{\text{oc}}$  of the PEC cell.<sup>[11a]</sup> Under open-circuit conditions, the photovoltage ( $V_{\text{ph}}$ ) corresponds to the increase in  $E_{\text{F}}^*$  with respect to the equilibrium value obtained in the dark ( $E_{\text{F,Redox}}$ ), as given by Equation (1):

$$V_{\text{ph}} = \frac{(E_{\text{F,n}}^* - E_{\text{F,Redox}})}{q} = \frac{k_{\text{B}} T}{q} \ln\left(\frac{n}{n_0}\right) \quad (1)$$

where  $E_{\text{F,Redox}}$  corresponds to the Fermi level of the electrolyte,  $k_{\text{B}}$  is the Boltzmann constant,  $T$  is the temperature (in Kelvin),  $q$  is the unsigned charge of an electron, while  $n$  and  $n_0$  represent the free electron concentration under illumination and in the dark, respectively.<sup>[11]</sup> We emphasize that no increase in  $E_{\text{F}}^*$  was observed for the TiO<sub>2</sub>-only device when it was illuminated with visible light, permitting utilization of the  $V_{\text{ph}}$  as a PEC probe to monitor the generation of hot electrons in the plasmonic photoanode, as shown in Figure 2b. The  $V_{\text{ph}}$  difference spectrum ( $\Delta V_{\text{ph}}(\lambda) = (\text{Au/TiO}_2)V_{\text{ph}}(\lambda) - (\text{TiO}_2)V_{\text{ph}}(\lambda)$ ) reveals a clear distinction between these devices in the visible region assignable to the Au NPs, with the maximum  $\Delta V_{\text{ph}}$  qualitatively corresponding to  $\lambda_{\text{max}}$  of the plasmonic device (Figure S2). Taken together, these PEC characteristics conclusively demonstrate that visible-light excitation induces PMET from the Au NPs to the TiO<sub>2</sub> NWs, enabling these plasmonic photoanodes to harvest visible light.

The dynamics of these hot electrons within the TiO<sub>2</sub> CB were then examined in situ by monitoring the temporal profile of the  $V_{\text{oc}}$  from the plasmonic photoanode while selectively exciting the Au NPs. An extended  $V_{\text{oc}}$  transient lasting ca. 50 s was observed under  $\lambda > 515 \text{ nm}$  irradiation as hot electrons accumulated within the TiO<sub>2</sub> CB, which slowly shifted the  $V_{\text{oc}}$  of the plasmonic photoanode to more negative potentials (Figure 3a). The extended  $V_{\text{oc}}$  transient reveals



**Figure 3.** Transient open-circuit voltage decay (OCVD) from the TiO<sub>2</sub>-only (gray) and the Au/TiO<sub>2</sub> (black) photoanodes following exposure to UV or visible-light excitation, respectively. a)  $V_{oc}$  transient rise/decay obtained during excitation/termination of irradiation. Horizontal dashed black line represents the  $V_{oc}$  baseline in the dark. b) Average electron lifetimes ( $\tau_n$ ) within the device.

a limited transmission probability for hot electrons into the TiO<sub>2</sub> CB, strongly suggesting the presence of a Schottky barrier ( $\phi \approx 1.0$  eV)<sup>[5b–f]</sup> at the Au/TiO<sub>2</sub> interface. The relaxation dynamics of these transferred electrons were then monitored immediately after irradiation, and a prolonged  $V_{oc}$  decay was observed over several minutes as the CB electrons recombined with any holes trapped on the Au NPs.

The PMET dynamics in the Au/TiO<sub>2</sub> device were distinguished from the intrinsic optical transitions within the TiO<sub>2</sub> support by monitoring the  $V_{oc}$  of the TiO<sub>2</sub>-only photoanode under UV ( $\lambda < 400$  nm) light. As shown in Figure 3a, a substantial distribution of electron-hole pairs was generated via UV excitation of the TiO<sub>2</sub> NWs, and a significant  $V_{ph}$  of 0.7 V was promptly established. Upon termination of the UV irradiation, the  $V_{oc}$  rapidly decreased back to the equilibrium value obtained in the dark as the CB electrons were scavenged by adsorbed surface species (e.g. dissolved O<sub>2</sub>) or relaxed via recombination with holes trapped in the valence band (VB).

Subsequent analysis of these  $V_{oc}$  transients via the open-circuit voltage decay (OCVD) method<sup>[11]</sup> yields the average lifetime of the photogenerated carriers ( $\tau_n$ ) within the device, according to Equation (2):

$$\tau_n = -\frac{k_B T}{q} \left( \frac{dV_{oc}}{dt} \right)^{-1} \quad (2)$$

where  $\tau_n$  represents the average electron lifetime and all other variables are as previously defined.<sup>[11]</sup> This measurement preferentially probes the slow recombination kinetics (milliseconds–seconds) of interfacial charge transfer processes occurring at the semiconductor-liquid junction.<sup>[11a,b]</sup> Consequently, this approach lends unique insight into the extended dynamics of long-lived electrons capable of facilitating reduction reactions, since these processes transpire on similar timescales.<sup>[1]</sup>


As shown in Figure 3b, the hot electrons transferred to the TiO<sub>2</sub> CB via PMET exhibited lifetimes that were 1–2 orders of magnitude longer ( $\tau_n \approx 10^3$  s) than those of CB electrons excited within the TiO<sub>2</sub> NWs themselves ( $\tau_n \approx 10^1$  s). Moreover, the relatively short-lived distribution ( $\tau_n \approx 0.1$  s)

indicative of rapid recombination was not observed for the hot electrons generated through the PMET mechanism. The absence of these short-lived carriers strongly suggests a reduced recombination rate following the PMET process. It must be recognized that  $\tau_n$  corresponds to the characteristic lifetimes for both free and trapped electrons within the TiO<sub>2</sub> CB.<sup>[11]</sup> Although trap states often mediate electron transport within NP-based TiO<sub>2</sub> films,<sup>[12]</sup> our device is composed of a highly-oriented rutile TiO<sub>2</sub> NW array known to possess a low density of defects.<sup>[12b]</sup> The photodeposition of Au NPs is further expected to preferentially passivate defects on the TiO<sub>2</sub> surface,<sup>[3c,10]</sup> suggesting a diminished contribution from trap states to the lifetimes observed in the Au/TiO<sub>2</sub> device. We emphasize that the lifetimes of CB electrons within the TiO<sub>2</sub>-only device are consistent with prior reports;<sup>[3e,11c]</sup> however, the singular nature of the prolonged  $V_{oc}$  transient in the Au/TiO<sub>2</sub> device implies a substantially reduced tendency for recombination following the PMET process.

Previous dynamics studies on Au/TiO<sub>2</sub> systems have employed NP-based mesoscopic films with TiO<sub>2</sub> particle sizes of 10–20 nm,<sup>[6]</sup> which are too small to facilitate the formation of a depletion layer within the TiO<sub>2</sub> NPs.<sup>[1c,12f]</sup> As a consequence there is no internal electric field to assist in the separation of electron-hole pairs within the semiconductor.<sup>[1c,12f]</sup> In contrast, the dimensions of the semiconductor scaffold used in our study (0.2–2  $\mu$ m) are suitable to support a depletion layer within the TiO<sub>2</sub> NW.<sup>[2e]</sup> Thus, the prolonged lifetimes observed for the hot electrons should result from the significant Schottky barrier ( $\phi \approx 1.0$  eV) established at the Au/TiO<sub>2</sub> interface.<sup>[5b–f]</sup> Although this Schottky barrier tempers the transmission of hot electrons into the TiO<sub>2</sub> CB, once the barrier has been breached, the depletion layer within the semiconductor promotes charge separation by sweeping these hot electrons away from the Au/TiO<sub>2</sub> interface. Recombination is further suppressed by the absence of VB holes in TiO<sub>2</sub> under visible-light irradiation. Constraining the number of relaxation channels available to these transferred electrons prolongs the charge-separated state, as the only accessible recombination pathway requires traversing back through the depletion layer and across the Schottky barrier before quenching any holes trapped in the Au NPs. This rationale is supported by the direct physical contact created at the Au/TiO<sub>2</sub> interface via photochemical deposition (Figure 1b) and is consistent with the prolonged  $V_{oc}$  transient observed under visible-light excitation (Figure 3a). On the contrary, direct excitation of TiO<sub>2</sub> with UV light generates CB electrons that are not physically separate from VB holes, encouraging geminate recombination within the semiconductor. Thus, the salient feature of the PMET process involves the spatial isolation of the hot electrons in the TiO<sub>2</sub> CB from the holes left behind on the Au NPs (see the Supporting Information for further discussion).

Finally, since the PMET process procures a steady source of excited-state electrons exhibiting lifetimes commensurate with the timescales required for solar photochemistry,<sup>[1,13]</sup> we evaluated the PEC activity of the Au/TiO<sub>2</sub> device for visible-light-driven H<sub>2</sub> evolution from water (see the Supporting Information). PEC experiments confirm that these hot electrons are catalytically suitable for water reduction,





**Figure 4.** Visible-light-driven H<sub>2</sub> evolution from H<sub>2</sub>O with a plasmonic PEC cell. a) Average H<sub>2</sub>-production curve over time. b) PEC stability experiments performed over four consecutive days. Vertical dashed lines delineate the start/stop of each experiment.

facilitating H<sub>2</sub> evolution from the Pt wire cathode at a rate ( $k$ ) of  $0.9 \pm 0.1 \mu\text{mol H}_2 \text{ cm}^{-2} \text{ h}^{-1}$  in the presence of methanol as a sacrificial reagent (Figure 4a). Significantly, the plasmonic photoanodes were also found to exhibit excellent PEC stability when subjected to repeated 5 h photocatalytic cycling experiments, as shown in Figure 4b. We note that the TiO<sub>2</sub>-only device does not produce H<sub>2</sub> when subjected to identical experimental conditions (Figure S6), further demonstrating the unique characteristics of hot electrons for solar photochemistry.<sup>[14]</sup>

In summary, we used PEC techniques to probe hot electron dynamics within Au/TiO<sub>2</sub> heterojunctions in situ and confirm the existence of PMET in these plasmonic photoanodes. We discovered that the lifetimes of hot electrons transferred to the TiO<sub>2</sub> CB are 1–2 orders of magnitude longer than those of CB electrons generated directly within the TiO<sub>2</sub> support via UV excitation. Such marked differences in lifetime are attributed to the Schottky barrier at the Au/TiO<sub>2</sub> interface, which impedes recombination following PMET to the TiO<sub>2</sub> CB. We further harnessed these long-lived electrons for visible-light-driven H<sub>2</sub> evolution from water, demonstrating their potential for solar photocatalysis. These results highlight the merits of the PMET strategy for extending the excited-state lifetimes of charge carriers within PEC devices, while simultaneously sensitizing the semiconductor scaffold to sub-band gap light. We anticipate improved photocatalytic efficiencies for a variety of kinetically hindered chemical reactions if plasmonic-metal/semiconductor heterostructures can be appropriately engineered to exploit the PMET process.

Received: April 12, 2014

Published online: June 11, 2014

**Keywords:** electron transfer · photoelectrochemistry · solar energy conversion · surface plasmon resonance · water splitting

[1] a) N. S. Lewis, D. G. Nocera, *Proc. Natl. Acad. Sci. USA* **2006**, *103*, 15729–15735; b) A. J. Cowan, J. R. Durrant, *Chem. Soc. Rev.* **2013**, *42*, 2281–2293; c) M. Grätzel, *Nature* **2001**, *414*, 338–344.

- [2] a) S. Linic, P. Christopher, D. B. Ingram, *Nat. Mater.* **2011**, *10*, 911–921; b) S. C. Warren, E. Thimsen, *Energy Environ. Sci.* **2012**, *5*, 5133–5146; c) X. Lang, X. Chen, J. Zhao, *Chem. Soc. Rev.* **2014**, *43*, 473–486; d) A. Primo, A. Corma, H. García, *Phys. Chem. Chem. Phys.* **2011**, *13*, 886–910; e) Z. Zhang, J. T. Yates, Jr., *Chem. Rev.* **2012**, *112*, 5520–5551.
- [3] a) Y. Tian, T. Tatsuma, *J. Am. Chem. Soc.* **2005**, *127*, 7632–7637; b) Y. Nishijima, K. Ueno, Y. Kotake, K. Murakoshi, H. Inoue, H. Misawa, *J. Phys. Chem. Lett.* **2012**, *3*, 1248–1252; c) C. Gomes Silva, R. Juárez, T. Marino, R. Molinari, H. García, *J. Am. Chem. Soc.* **2011**, *133*, 595–602; d) S. Mubeen, J. Lee, N. Singh, S. Kramer, G. D. Stucky, M. Moskovits, *Nat. Nanotechnol.* **2013**, *8*, 247–251; e) Y. Pu, G. Wang, K. Chang, Y. Ling, Y. Lin, B. C. Fitzmorris, C. Liu, X. Lu, Y. Tong, J. Z. Zhang, Y. Hsu, Y. Li, *Nano Lett.* **2013**, *13*, 3817–3823; f) Z. Bian, T. Tachikawa, P. Zhang, M. Fujitsuka, T. Majima, *J. Am. Chem. Soc.* **2014**, *136*, 458–465; g) A. Primo, T. Marino, A. Corma, R. Molinari, H. García, *J. Am. Chem. Soc.* **2011**, *133*, 6930–6933.
- [4] a) E. Thimsen, F. Le Formal, M. Grätzel, S. C. Warren, *Nano Lett.* **2011**, *11*, 35–43; b) I. Thomann, B. A. Pinaud, Z. Chen, B. M. Clemens, T. F. Jaramillo, M. L. Brongersma, *Nano Lett.* **2011**, *11*, 3440–3446; c) H. Gao, C. Liu, H. E. Jeong, P. Yang, *ACS Nano* **2012**, *6*, 234–240; d) D. B. Ingram, S. Linic, *J. Am. Chem. Soc.* **2011**, *133*, 5202–5205; e) J. Li, S. K. Cushing, P. Zheng, F. Meng, D. Chu, N. Wu, *Nat. Commun.* **2013**, *4*, 2651–2658; f) Q. Zhang, D. Q. Lima, I. Lee, F. Zaera, M. Chi, Y. Yin, *Angew. Chem. Int. Ed.* **2011**, *50*, 7088–7092; *Angew. Chem.* **2011**, *123*, 7226–7230; g) R. Long, K. Mao, M. Gong, S. Zhou, J. Hu, M. Zhi, Y. You, S. Bai, J. Jiang, Q. Zhang, X. Wu, Y. Xiong, *Angew. Chem. Int. Ed.* **2014**, *53*, 3205–3209; *Angew. Chem.* **2014**, *126*, 3269–3273.
- [5] a) M. W. Knight, H. Sobhani, P. Nordlander, N. J. Halas, *Science* **2011**, *332*, 702–704; b) Y. K. Lee, C. H. Jung, J. Park, H. Seo, G. A. Somorjai, J. Y. Park, *Nano Lett.* **2011**, *11*, 4251–4255; c) A. O. Govorov, H. Zhang, Y. K. Gun'ko, *J. Phys. Chem. C* **2013**, *117*, 5548–5552; d) S. Mubeen, G. Hernandez-Sosa, D. Moses, J. Lee, M. Moskovits, *Nano Lett.* **2011**, *11*, 5548–5552; e) R. Long, O. V. Prezhdo, *J. Am. Chem. Soc.* **2014**, *136*, 4343–4354; f) E. W. McFarland, J. Tang, *Nature* **2003**, *421*, 616–618.
- [6] a) A. Furube, L. Du, K. Hara, R. Katoh, M. Tachiya, *J. Am. Chem. Soc.* **2007**, *129*, 14852–14853; b) J. Sá, G. Tagliabue, P. Friedli, J. Szlachetko, M. H. Rittman-Frank, F. G. Santomauro, C. J. Milne, H. Sigg, *Energy Environ. Sci.* **2013**, *6*, 3584–3588; c) K. Wu, W. E. Rodríguez-Córdoba, Y. Yang, T. Lian, *Nano Lett.* **2013**, *13*, 5255–5263; d) J. B. Priebe, M. Karnahl, H. Junge, M. Beller, D. Hollmann, A. Brückner, *Angew. Chem. Int. Ed.* **2013**, *52*, 11420–11424; *Angew. Chem.* **2013**, *125*, 11631–11635.
- [7] A. Linsebigler, G. Lu, J. T. Yates, Jr., *Chem. Rev.* **1995**, *95*, 735–758.
- [8] W. Hou, S. B. Cronin, *Adv. Funct. Mater.* **2013**, *23*, 1612–1619.
- [9] a) M. G. Walter, E. L. Warren, J. R. McKone, S. W. Boettcher, Q. Mi, E. M. Santori, N. S. Lewis, *Chem. Rev.* **2010**, *110*, 6446–6473; b) B. Liu, E. S. Aydil, *J. Am. Chem. Soc.* **2009**, *131*, 3985–3990; c) J. M. Foley, M. L. Price, J. I. Feldblyum, S. Maldonado, *Energy Environ. Sci.* **2012**, *5*, 5203–5220; d) M. Law, L. E. Greene, J. C. Johnson, R. Saykally, P. Yang, *Nat. Mater.* **2005**, *4*, 455–459.
- [10] a) S. C. Chan, M. A. Barteau, *Langmuir* **2005**, *21*, 5588–5595; b) Y. Matsumoto, S. Ida, T. Inoue, *J. Phys. Chem. C* **2008**, *112*, 11614–11616; c) X. Huang, X. Qi, Y. Huang, S. Li, C. Xue, C. Gan, F. Boey, H. Zhang, *ACS Nano* **2012**, *4*, 6196–6202.
- [11] a) J. Bisquert, A. Zaban, M. Greenshtein, I. Mora-Seró, *J. Am. Chem. Soc.* **2004**, *126*, 13550–13559; b) A. Zaban, M. Greenshtein, J. Bisquert, *ChemPhysChem* **2003**, *4*, 859–864; c) B. H. Meekins, P. V. Kamat, *ACS Nano* **2009**, *3*, 3437–3446.
- [12] a) J. R. Swierk, T. E. Mallouk, *Chem. Soc. Rev.* **2013**, *42*, 2357–2387; b) X. Feng, K. Zhu, A. J. Frank, C. A. Grimes, T. E. Mallouk, *Angew. Chem. Int. Ed.* **2012**, *51*, 2727–2730; *Angew. Chem.*

- Chem.* **2012**, *124*, 2781–2784; c) L. Bertoluzzi, I. Herraiz-Cardona, R. Gottesman, A. Zaban, J. Bisquert, *J. Phys. Chem. Lett.* **2014**, *5*, 689–694; d) M. Yang, B. Ding, S. Lee, J. Lee, *J. Phys. Chem. C* **2011**, *115*, 14534–14541; e) Y. J. Hwang, C. Han, B. Liu, P. Yang, *ACS Nano* **2012**, *6*, 5060–5069; f) A. Hagfeldt, M. Grätzel, *Chem. Rev.* **1995**, *95*, 49–68.
- [13] a) Z. Huang, Y. Lin, W. Rodríguez-Córdoba, K. J. McDonald, K. S. Hagen, K. S. Choi, B. S. Brunshwig, D. G. Musaev, C. L. Hill, D. Wang, T. Lian, *Energy Environ. Sci.* **2012**, *5*, 8923–8926; b) R. Liu, G. Yuan, C. L. Joe, T. E. Lightburn, K. L. Tan, D. Wang, *Angew. Chem. Int. Ed.* **2012**, *51*, 6709–6712; *Angew. Chem.* **2012**, *124*, 6813–6816; c) R. J. Dillon, J. Joo, F. Zaera, Y. Yin, C. J. Bardeen, *Phys. Chem. Chem. Phys.* **2013**, *15*, 1488–1496; d) F. Le Formal, S. R. Pendlebury, M. Cornuz, S. D. Tilley, M. Grätzel, J. R. Durrant, *J. Am. Chem. Soc.* **2014**, *136*, 2564–2574.
- [14] a) S. Linic, P. Christopher, H. Xin, A. Marimuthu, *Acc. Chem. Res.* **2013**, *46*, 1890–1899; b) S. Mukherjee, L. Zhou, A. M. Goodman, N. Large, C. Ayala-Orozco, Y. Zhang, P. Nordlander, N. J. Halas, *J. Am. Chem. Soc.* **2014**, *136*, 64–67.
-