

Second-Order Optical Nonlinearities of β -Sulfonylstyrene DerivativesYoshio SUGIYAMA,* Yasushi SUZUKI, Shuichi MITAMURA, Yugen KAWAMOTO,[†]
Makoto FUJITA,[†] and Katsuyuki OGURA[†]

Advanced Materials & Technology Research Laboratories, Nippon Steel Corporation, 1618 Ida, Nakahara-ku, Kawasaki 211

[†] Department of Synthetic Chemistry, Faculty of Engineering, Chiba University, Yayoicho 1-33, Chiba 260

(Received February 24, 1994)


Synopsis. The second-order optical nonlinearities and transparencies of eight substituted styrenes containing at least one sulfonyl group at the β -position, as the electron-withdrawing group, were examined. Oxidation at a sulfur atom (SMe→SOMe→SO₂Me) brings about increases in the β and $\lambda_{\max}$ values.

Second-harmonic generation materials convert the light of semiconductor lasers (800 nm band) into blue laser light (400 nm band). It is well known that molecules containing electron-donating and electron-withdrawing groups separated by a large π -electron conjugated system possess large second-order molecular hyperpolarizabilities (β).¹⁾

Here, we report on the second-order optical nonlinearities and transparencies of a new system represented by a general formula (I) which has a ketene dithioacetal *S,S*-dioxide, *S,S,S'*-trioxide, or *S,S,S',S'*-tetraoxide group²⁾ as an electron-withdrawing part (Chart 1).

Results and Discussion

Table 1 summarizes the nonlinearities β (10⁻³⁰ esu) measured by the EFISH technique, SHG (XUrea), and the transparencies ($\lambda_{\max}$ (nm) and λ_{cutoff} (nm)) of two β,β -bis(methylsulfonyl)styrenes (**1**²⁾ and **2**) having a 4- or 2-methoxyl as the electron-donating group. SHG (XUrea) means the relative intensity of SHG. The measured molecular dipole moments (in units of 10⁻¹⁸ esu=1 Debye=3.3356×10⁻³⁰ C m) of these compounds are also given in Table 1. Contrary to our expectation,

I
Chart 1.Table 1. Nonlinearities and Transparencies of β,β -Bis(methylsulfonyl)styrenes

Compound		$\lambda_{\max}$	λ_{cutoff}	μ	β	SHG
	X Y	nm	nm	10 ⁻¹⁸ esu	10 ⁻³⁰ esu	(×Urea)
1 ²⁾	MeO H	325	377	6.1	6.4	8.6
2	H MeO	333	402	—	—	0.000

$$\beta \text{ (m}^4 \text{ V}^{-1}\text{)} = 4.1888 \times 10^{-10} \beta \text{ (esu)}.$$

the methoxyl-group substitution at the ortho position, not at the para position, as for compound **1**, makes the relative intensity of the SHG of **2** zero.

In order to determine the effect of a *p*-tolylsulfonyl group, not a methylsulfonyl group, on the β , SHG (XUrea), and $\lambda_{\max}$, nine *p*-tolylsulfonyl-substituted styrenes, **3**–**11**, were synthesized and examined, as listed in Table 2. Compound **3** has no substituents in the benzene ring. The oxygen coordination at a sulfur atom (4 SMe→5 SOMe→6 SO₂Me; 8 SMe→9 SOMe→10 SO₂Me) brings about increases of β (4→5→6; 8→9→10) and $\lambda_{\max}$ (4→5→6; 8→9→10). The introduction of a methoxyl group as the electron-donating group also increases β (3→5; 4→8; 5→9; 6→10) and $\lambda_{\max}$ (3→5; 4→8; 5→9; 6→10). The increase in the electron-donating ability (4 MeO→11 Me₂N) results in those of β (4→11) and $\lambda_{\max}$ (4→11). It coincides with an estimation from a two-level model,^{1a)} in which increasing $\lambda_{\max}$ tends to increase β . The introduction of a *p*-tolylsulfonyl group, not a methylsulfonyl group (6→7), leads to a decrease in β (6→7). The introduction of various kinds of substituents (**3**–**11**) has no ability to increase the relative intensity of SHG (<1), contrary to our expectation.


In this study, we examined the second-order optical nonlinearities and transparencies of eleven (eight new and the reported three (**1**, **6**, **10**)²⁾) substituted styrenes containing at least one sulfonyl group as the electron-withdrawing group. The oxidation at a sulfur atom (SMe→SOMe→SO₂Me) and the electron-donating ability (H<MeO<Me₂N) in these eleven styrene derivatives bring about increases of the β and $\lambda_{\max}$ values.

Experimental

Compounds **1**–**11** were prepared as described below; the other compounds were commercially available.

The melting points were determined on a hotstage microscope apparatus (Yanagimoto) and were uncorrected. ¹H NMR spectra were obtained on a JEOL (JNM-FX 270) spectrometer. Infrared spectra were measured with a JASCO (A-200) spectrometer; the data are presented for important diagnostic absorptions. Elementary analyses were provided by the chemical analysis center of Chiba university.

Measurements of the absorption maximum wavelength ($\lambda_{\max}$), the absorption cutoff (λ_{cutoff}) evaluated based on the wavelength, the transmittance of which was 95% in an ethanol solution, the second-order molecular hyperpolarizability (β), the molecular dipole (μ), and the relative in-

Table 2. Nonlinearities and Transparencies of β -(*p*-Tolylsulfonyl)styrenes


	Compound			$\lambda_{\max}$	λ_{cutoff}	μ	β	SHG
	X	Y	A	nm	nm	10^{-18} esu	10^{-30} esu	($\times$ Urea)
3	H	H	SOMe	280	377	4.9	3.8	0.004
4	MeO	H	SMe	314	386	5.9	4.6	0.000
5	MeO	H	SOMe	324	398	5.1	6.0	0.000
6²⁾	MeO	H	SO ₂ Me	330	—	6.6	8.3	0.000
7	MeO	H	SO ₂ Tol	337	—	6.5	6.4	0.000
8	MeO	MeO	SMe	336	397	5.6	6.5	0.000
9	MeO	MeO	SOMe	347	421	5.2	7.3	0.08
10²⁾	MeO	MeO	SO ₂ Me	352	—	6.8	10.6	0.000
11	Me ₂ N	H	SMe	381	457	6.7	10.3	0.000

tensity of SHG were described in a previous paper.³⁾ The solubilities of compounds **6**, **7**, and **10** in ethanol and that of compound **2** in dioxane were poor. Therefore, the λ_{cutoff} , μ , and β of those compounds could not be measured, as given in Tables 1 and 2.

Preparation of 4-Methoxy- β,β -bis(methylsulfonyl)styrene (1). **A Typical Procedure:** This compound was prepared by the oxidation of 4-methoxy- β -methylsulfinyl- β -methylthiostyrene⁴⁾ (1.07 g; 4.41 mmol) with *m*-chloroperbenzoic acid (MCPBA) (2.72 g; 14.77 mmol) in dichloromethane (50 ml) at -20°C (5 h) and then at room temperature (60 h). The usual workup and separation by column chromatography on silica gel [eluent: benzene-ethyl acetate (2:1)] gave **1** (1.23 g; 97% yield). Colorless crystals; mp $164\text{--}165^\circ\text{C}$ (from CHCl_3 /hexane); $^1\text{H NMR}$ (CDCl_3) $\delta=3.35$ (6H, d), 3.89 (3H, s), 6.99 (2H, d, $J=9.0$ Hz), 7.89 (2H, d, $J=9.0$ Hz), 8.29 (1H, s). IR (KBr) 2900, 1605, 1580, 1560, 1420, 1300, 1280, 1180, 1140, 1030, 980, 950, 830, 780 and 760 cm^{-1} .

Found: C, 45.40; H, 4.83%. Calcd for $\text{C}_{11}\text{H}_{14}\text{O}_5\text{S}_2$: C, 45.50; H, 4.86%.

2-Methoxy- β,β -bis(methylsulfonyl)styrene (2): Yellow crystals; mp $146\text{--}148^\circ\text{C}$ (from CHCl_3 /hexane); $^1\text{H NMR}$ (CDCl_3) $\delta=3.36$ (6H, d, $J=4.0$ Hz), 3.91 (3H, s), 6.91–7.64 (4H, m), 8.62 (1H, s). IR (KBr) 3000, 2925, 1585, 1470, 1455, 1320, 1295, 1240, 1130, 1010, 970, 950, 940, 925, 765, 740, 570, 560, 530, and 505 cm^{-1} .

Found: C, 44.79; H, 4.87%. Calcd for $\text{C}_{11}\text{H}_{14}\text{O}_5\text{S}_2$: C, 44.81; H, 4.96%.

Preparation of β -Methylsulfinyl- β -(*p*-tolylsulfonyl)styrene (3). **A Typical Procedure:** Oxidation of β -methylthio- β -(*p*-tolylsulfonyl)styrene⁵⁾ (996 mg; 3.28 mmol) with MCPBA (728 mg; 4.22 mmol) in dichloromethane (40 ml) was performed at -20°C (4 h) to give **3** (796 mg; 76% yield). Colorless crystals; mp $134\text{--}135^\circ\text{C}$ (from benzene/hexane); $^1\text{H NMR}$ (CDCl_3) $\delta=2.42$ (3H, s), 3.17 (3H, s), 7.34 (2H, d, $J=7.4$ Hz), 7.50 (5H, s), 7.96 (2H, d, $J=8.6$ Hz), 8.28 (1H, s). IR (KBr) 3000, 1580, 1560, 1510, 1480, 1440, 1400, 1300, 1280, 1200, 1140, 1060, 950, 930, 910, 810, 750, 690, 660, 600, 550, and 500 cm^{-1} .

Found: C, 59.88; H, 4.94%. Calcd for $\text{C}_{16}\text{H}_{16}\text{O}_3\text{S}_2$: C, 59.97; H, 5.03%.

4-Methoxy- β -methylsulfinyl- β -(*p*-tolylsulfonyl)-

styrene (5): Colorless crystals; mp $115\text{--}116^\circ\text{C}$; $^1\text{H NMR}$ (CDCl_3) $\delta=2.40$ (3H, s), 3.13 (3H, s), 3.84 (3H, s), 7.06 (2H, d, $J=8.6$ Hz), 7.40 (2H, d, $J=8.2$ Hz), 7.72 (2H, d, $J=8.6$ Hz), 7.95 (2H, d, $J=8.2$ Hz), 8.28 (1H, s). IR (KBr) 3450, 3000, 1600, 1508, 1458, 1420, 1300, 1260, 1180, 1145, 1070, 1025, 960, 910, 830, 770, 660 cm^{-1} .

Found: C, 58.24; H, 5.06%. Calcd for $\text{C}_{17}\text{H}_{18}\text{O}_4\text{S}_2$: C, 58.26; H, 5.18%.

3,4-Dimethoxy- β -methylsulfinyl- β -(*p*-tolylsulfonyl)styrene (9):⁵⁾ Pale yellow crystals; mp $145\text{--}146^\circ\text{C}$ (from benzene/hexane); $^1\text{H NMR}$ (CDCl_3) $\delta=2.42$ (3H, s), 3.10 (3H, s), 3.89 (3H, s), 3.92 (3H, s), 6.92 (1H, d, $J=8.0$ Hz), 7.11–7.50 (2H, m), 7.64 (1H, d, $J=8.0$ Hz), 7.54–8.04 (3H, m), 8.19 (1H, s). IR (KBr) 1510, 1265, 1140, 1080, 1065, 550 cm^{-1} .

Found: C, 56.92; H, 5.28%. Calcd for $\text{C}_{18}\text{H}_{20}\text{O}_5\text{S}_2$: C, 56.82; H, 5.30%.

Preparation of 4-Methoxy- β -methylthio- β -(*p*-tolylsulfonyl)styrene (4). **A Typical Procedure:** To a solution of (methylthio)methyl *p*-tolyl sulfone⁶⁾ (1.01 g; 4.66 mmol) in THF (15 ml), were added successively trimethylsilyl chloride (1.30 ml; 10.3 mmol) and a 1.58 mol dm^{-3} hexane solution of butyllithium (6.45 ml; 10.3 mmol) at -78°C . After the resulting solution had been stirred at the same temperature for 2 h, and then *p*-methoxybenzaldehyde (0.68 ml; 5.6 mmol) was added at -78°C . The reaction temperature was then slowly raised to room temperature, and the reaction mixture stirred for 2 h. Quenching with an aqueous solution of ammonium chloride, extraction with diisopropyl ether and chloroform, and column chromatography on silica gel [hexane-ethyl acetate (5:1)] gave **4** (1.01 g; 65% yield). Colorless crystals; mp $123\text{--}125^\circ\text{C}$ (from CHCl_3 /hexane); $^1\text{H NMR}$ (CDCl_3) $\delta=2.18$ (3H, s), 2.41 (3H, s), 3.84 (3H, s), 6.95 (2H, d, $J=9.0$ Hz), 7.32 (2H, d, $J=8.0$ Hz), 7.90 (2H, d, $J=8.2$ Hz), 7.98 (2H, d, $J=8.2$ Hz), 8.21 (1H, s). IR (KBr) 1600, 1500, 1440, 1340, 1280, 1260, 1170, 1140, 1080, 1020, 905, 840, 750, 650, 580, 560, and 530 cm^{-1} .

Found: C, 61.04; H, 5.45%. Calcd for $\text{C}_{17}\text{H}_{18}\text{O}_3\text{S}_2$: C, 61.05; H, 5.42%.

3,4-Dimethoxy- β -methylthio- β -(*p*-tolylsulfonyl)styrene (8):^{5,7)} Pale yellow crystals; mp $119\text{--}120^\circ\text{C}$ (from benzene/hexane); $^1\text{H NMR}$ (CDCl_3) $\delta=2.19$ (3H, s), 2.39 (3H, s), 3.85 (3H, s), 3.88 (3H, s), 6.90 (1H, d, $J=8.0$

Hz), 7.30 (2H, d, $J=8.0$ Hz), 7.52 (1H, dd, $J=1.0, 8.0$ Hz), 7.80 (1H, d, $J=1.0$ Hz), 7.87 (2H, d, $J=8.0$ Hz), 8.18 (1H, s). IR (KBr) 1585, 1510, 1310, 1260, 1140, 1085 cm^{-1} .

Found: C, 59.36; H, 5.50%. Calcd for $\text{C}_{18}\text{H}_{20}\text{O}_4\text{S}_2$: C, 59.32; H, 5.53%.

4-Dimethylamino- β -methythio- β -(*p*-tolylsulfonyl)-styrene (11): Yellow crystals; mp 114–116 °C (from benzene/hexane); ^1H NMR (CDCl_3) $\delta=2.16$ (3H, s), 2.40 (3H, s), 3.02 (6H, s), 6.68 (2H, d, $J=9.0$ Hz), 7.29 (2H, d, $J=7.9$ Hz), 7.82 (2H, d, $J=7.4$ Hz), 8.00 (2H, d, $J=8.6$ Hz), 8.16 (1H, s). IR (KBr) 2900, 1600, 1560, 1510, 1420, 1370, 1360, 1290, 1220, 1180, 1170, 1140, 1080, 910, 820, 720, 650, 580, 550, 520, 470 cm^{-1} .

Found: C, 62.12; H, 6.07; N, 3.99%. Calcd for $\text{C}_{18}\text{H}_{21}\text{O}_2\text{NS}_2$: C, 62.22; H, 6.09; N, 4.03%.

Preparation of 4-Methoxy- β -methysulfonyl- β -(*p*-tolylsulfonyl)styrene (6): A Typical Procedure:

This compound was produced by the oxidation of **4** (330 mg; 1.02 mmol) with excess MCPBA (535 mg; 3.09 mmol) in dichloromethane (10 ml) at -20 °C (3 h) and at room temperature (17 h). The usual workup and separation by column chromatography on silica gel [eluent: benzene–ethyl acetate (3:1)] gave **6** (235 mg; 64% yield). This product was shown by ^1H NMR to consist of two geometric isomers in the ratio of 8:2. Their geometry was not determined. Colorless crystals; mp 168–170 °C (from CH_3Cl /hexane); ^1H NMR (CDCl_3) $\delta=2.38$ (3H, s), 2.43 (3H, s), 3.22 (3H, s), 3.48 (3H, s), 3.87 (3H, s), 3.89 (3H, s), 6.98 (2H, d, $J=9.2$ Hz), 7.33 (2H, d, $J=8.6$ Hz), 7.84 (2H, d, $J=8.2$ Hz), 7.90 (2H, d, $J=8.6$ Hz), 8.29 (1H, s), 8.54 (1H, s). IR (KBr) 1590, 1570, 1540, 1500, 1440, 1420, 1360, 1300, 1270, 1180, 1140, 1080, 1020, 950, 930, 840, 820, 750, 700, 670, 585, 570, 535, 510 cm^{-1} .

Found: C, 55.52; H, 4.89%. Calcd for $\text{C}_{17}\text{H}_{18}\text{O}_5\text{S}_2$: C, 55.72; H, 4.95%.

3,4-Dimethoxy- β -methysulfonyl- β -(*p*-tolylsulfonyl)styrene (10): Pale yellow crystals; mp 160–161 °C (from CH_3Cl /hexane); ^1H NMR (CDCl_3) $\delta=2.38$ (3H, s), 2.43 (3H, s), 3.19 (3H, s), 3.48 (3H, s), 3.88 (3H, s), 3.91 (3H, s), 3.95 (3H, s), 3.97 (3H, s), 6.95 (1H, d, $J=8.0$ Hz), 7.35 (2H, d, $J=8.2$ Hz), 7.48 (1H, dd, $J=12.9$ Hz), 7.76 (1H, d, $J=2.4$ Hz), 7.85 (2H, d, $J=8.2$ Hz), 8.23 (1H, s),

8.55 (1H, s). IR (KBr) 1570, 1555, 1500, 1450, 1360, 1320, 1270, 1240, 1140, 1080, 1010, 970, 800, 770, 640, 560 cm^{-1} .

Found: C, 54.29; H, 5.08%. Calcd for $\text{C}_{17}\text{H}_{20}\text{O}_6\text{S}_2$: C, 54.53; H, 5.08%.

4-Methoxy- β , β -bis(*p*-tolylsulfonyl)styrene (7):

Compound **7** was prepared by the oxidation of 4-methoxy- β -(*p*-tolylsulfonyl)- β -(*p*-tolylthio)styrene in an analogous manner to **1**. Colorless crystals; mp 176–177 °C (from CH_3Cl /hexane); ^1H NMR (CDCl_3) $\delta=2.30$ (3H, s), 2.40 (3H, s), 3.80 (3H, s), 6.80–7.97 (12H, m), 8.54 (1H, s). IR (KBr) 2900, 1600, 1570, 1550, 1500, 1460, 1420, 1365, 1320, 1300, 1260, 1180, 1150, 1080, 1030, 930, 760, 710, 690, 660, 620, 590, 550, 520, 480 cm^{-1} .

Found: C, 62.24; H, 4.93%. Calcd for $\text{C}_{23}\text{H}_{22}\text{O}_5\text{S}_2$: C, 62.41; H, 5.01%.

References

- 1) A general paper for the molecules containing electron-donating and electron-withdrawing groups separated by an electron-conjugated system: a) J. L. Oudar, *J. Chem. Phys.*, **67**, 446 (1977); b) J. L. Oudar and D. S. Chemla, *J. Chem. Phys.*, **66**, 2664 (1977); c) B. F. Levine, *Chem. Phys. Lett.*, **37**, 516 (1976).
- 2) In a preliminary communication, we reported so high electron-acceptability of 2,2-bis(alkyl- or arylsulfonyl)ethenyl group as to serve as the electron-withdrawing group of second order nonlinear optics: K. Ogura, S. Takahashi, Y. Kawamoto, M. Suzuki, M. Fugita, Y. Suzuki, and Y. Sugiyama, *Tetrahedron Lett.*, **34**, 2649 (1993).
- 3) Y. Sugiyama, Y. Suzuki, S. Mitamura, and T. Nishiyama, *Bull. Chem. Soc. Jpn.*, **66**, 687 (1993).
- 4) K. Ogura, Y. Ito, and G. Tsuchihashi, *Bull. Chem. Soc. Jpn.*, **52**, 1203 (1979).
- 5) K. Ogura, N. Yahata, K. Hashizume, K. Tsuyama, K. Takahashi, and H. Iida, *Chem. Lett.*, **1983**, 767.
- 6) K. Ogura, N. Yahata, J. Watanabe, K. Takahashi, and H. Iida, *Bull. Chem. Soc. Jap.*, **56**, 3543 (1983).
- 7) This compound is also prepared by the Knoevenagel condensation of (methylthio)methyl *p*-tolyl sulfone with 3,4-dimethoxybenzaldehyde in the presence of potassium carbonate in refluxing isopropyl alcohol.⁵⁾