


# Influence of Symmetry on the Luminescence and Radiative Lifetime of Nine-Coordinate Europium Complexes

Nail M. Shavaleev,\* Svetlana V. Eliseeva, Rosario Scopelliti, and Jean-Claude G. Bünzli\*

École Polytechnique Fédérale de Lausanne, Institut des Sciences et Ingénierie Chimiques, Avenue Forel 2, BCH, CH-1015 Lausanne, Switzerland

# Supporting Information

ABSTRACT: Homoleptic mononuclear nine-coordinate lanthanum(III) and europium-(III) tris-complexes  $[Ln(N^N^O)_3] \cdot nH_2O$  with two tridentate N-benzylbenzimidazole pyridine-2-carboxylates exhibit a rare C<sub>3</sub>-symmetry of the lanthanide coordination polyhedron in the solid state, as confirmed by luminescence spectroscopy and by X-ray crystallography (the three N^N^O ligands are arranged "up-up-up" around the lanthanide ion). The symmetry, however, is changed to the more common  $C_1$  upon dissolution of the complexes in dichloromethane, as revealed by luminescence



spectroscopy (the three ligands are likely to be arranged "up-up-down"). The new europium complexes emit efficient ligand-sensitized metal-centered luminescence with excited-state lifetimes of 1.56-2.18 ms and quantum yields of 25–41% in the solid and in solution. The change of the symmetry from (a higher)  $C_3$  to (a lower)  $C_1$  alters the luminescence spectrum, shortens the radiative lifetime, and increases the luminescence efficiency of the europium complexes.

## ■ INTRODUCTION

Most trivalent lanthanide ions exhibit characteristic metalcentered line-like f-f luminescence with high color purity in the UV, visible, and near-infrared spectral ranges. 1-8 Although the f-f luminescence is long-lived, with a lifetime of up to milliseconds, it is usually not quenched by oxygen.9

The brightness of lanthanide luminescence, that is, the product of the luminescence quantum yield and the molar absorption coefficient (at the excitation wavelength), can be increased by many orders of magnitude by coordinating the lanthanide ion with chromophore ligands. 5,10-13 The ligands provide efficient light harvesting and ligand-to-lanthanide energy transfer and protect the lanthanide(III) from nonradiative deactivation.<sup>5</sup>

Upon coordination, mixing of ligand and lanthanide orbitals enhances the intensity of electric-dipole metal-centered Laporte-forbidden f-f transitions, especially when the coordination lowers the symmetry around the lanthanide. 1-3 Thus, the symmetry that the ligands define around the lanthanide ion in the complex determines the relative intensity of the emission bands and, therefore, both the luminescence color and the rate of radiative f-f transitions. 1-3,14,15

The emissive lanthanide ions, in particular europium(III), are used as luminescent probes and sensors,<sup>5</sup> because the efficiency, the lifetime, and the fine structure of the f-f luminescence spectra are sensitive to the symmetry and the composition of the coordination sphere of the lanthanide. 1-5,11-15 Here, we report on rare mononuclear nine-coordinate lanthanide(III) complexes  $[Ln(N^{\wedge}N^{\wedge}O)_3]$  that exhibit  $C_3$ -symmetry in the solid state but C<sub>1</sub>-symmetry in solution and on the effect that this change of symmetry has on the luminescence of the europium(III) complexes.

# ■ RESULTS AND DISCUSSION

**Synthesis.** Two new tridentate monoanionic N^N^O ligands HL1 and HL2 have been prepared from 2-carboxaldehyde-6hydroxymethylpyridine (Scheme 1). 16,17 The formation of a benzimidazole heterocycle<sup>18</sup> was followed by selective oxidation of pyridine-2-methanol first to carboxaldehyde with


Scheme 1. Synthesis of Ligands and Complexes<sup>a</sup>

<sup>a</sup>Reaction conditions: (a) Na<sub>2</sub>S<sub>2</sub>O<sub>4</sub>, 2-methoxyethanol/water or DMF/water, under nitrogen, 100-110 °C; (b) SeO<sub>2</sub>, dioxane, under nitrogen, 110 °C; (c) H<sub>2</sub>O<sub>2</sub>, formic acid, under air, 0 °C; (d) LnCl<sub>3</sub>· nH<sub>2</sub>O, NaOH, ethanol/water, under air, heating.

Received: July 16, 2015 Published: September 4, 2015

SeO<sub>2</sub> and then to carboxylic acid with  $H_2O_2$ /formic acid. <sup>19</sup> The homoleptic lanthanum(III) and europium(III) tris-complexes [Ln(Ligand)<sub>3</sub>]· $nH_2O$  (n=4, 5; Ln = La, Eu; Ligand = L1<sup>-</sup>, L2<sup>-</sup>; LnL1 and LnL2) have been obtained by reacting a 3:3:1 molar ratio of ligand, NaOH, and LnCl<sub>3</sub>· $nH_2O$  in ethanol/water mixtures. All of the products are air- and moisture-stable solids. They have been characterized by elemental analysis, NMR spectroscopy, ESI TOF mass spectrometry, and X-ray crystallography. The n-octyloxy group in the benzimidazole heterocycle increases the solubility of ligand HL2 and its complexes in organic solvents.

Molecular Structure of the Complexes LnL1. Figure 1 and Table 1 report the X-ray structure of  $[La(L1)_3] \cdot CH_3CN$ .




**Figure 1.** Structure of  $[La(L1)_3]$ - $CH_3CN$  viewed down the triangular face  $(C_3$  axis) of the tricapped trigonal prism (50% probability ellipsoids; one of the two independent molecules of the complex, the  $\Lambda$  isomer La(1), is shown; H atoms, benzyl groups, and cocrystallized acetonitrile molecule omitted; ORTEP). Heteroatoms: O, red; N, blue; La(1), black.

Table 1. Structure of [La(L1)<sub>3</sub>]·CH<sub>3</sub>CN<sup>a</sup>

	1	angles <sup>b</sup> (deg)		
complex	La-O	La-N(py)	La-N(b)	ру-ь
$[La(L1)_3]$ (1)	2.448(3)	2.695(3)	2.737(3)	24.4
	2.452(3)	2.693(3)	2.735(4)	21.5
	2.459(3)	2.690(4)	2.755(3)	24.5
$[La(L1)_3]$ (2)	2.449(3)	2.705(3)	2.722(4)	16.4
	2.457(3)	2.688(4)	2.782(3)	26.3
	2.457(3)	2.705(3)	2.745(3)	22.2
average $(2\sigma)$	2.454(8)	2.696(13)	2.746(38)	23(6)
max - min	0.011	0.017	0.060	9.9

<sup>a</sup>Two independent molecules are present in the unit cell. Each row corresponds to one ligand. py = pyridine. b = benzimidazole. <sup>b</sup>The dihedral angles between the planes of pyridine and benzimidazole.

The structure contains two slightly different molecules (both are present as  $\Lambda$  and  $\Delta$  isomers). The lanthanum ions are ninecoordinated by three deprotonated tridentate N^N^O ligands. Their coordination polyhedron is a distorted tricapped trigonal prism, with the N(py = pyridine) atoms in capping positions and in-plane with La<sup>III</sup> (Figure 2). The La–La distance is long, 9.142(2) Å. The triangular faces of the prism are defined by O–O–O and N(b)–N(b)–N(b) atoms (b = benzimidazole). The three ligands are arranged "up–up–up" around the La<sup>III</sup>, resulting in a complex with a distorted  $C_3$ -symmetry.



**Figure 2.** Coordination environment of  $La^{III}$  in  $[La(L1)_3]\cdot CH_3CN$  viewed down the square face of the tricapped trigonal prism. Heteroatoms: O, red; N, blue; La(1), black.

The coordinated ligands are not planar, with the dihedral angles between pyridine and benzimidazole in the range  $16.4-26.3^{\circ}$ . The ligands are not equally strongly bonded to the metal ion. For a given ligand, the lanthanum—benzimidazole bond is the longest one with the widest variation. The bonding of the ligands was quantified by the bond-valence method, wherein a donor atom j at a distance  $d_{\text{Ln},j}$  from the metal ion is characterized by a bond-valence contribution  $\nu_{\text{Ln},j}$ :

$$\nu_{\text{Ln},j} = e^{(R_{\text{Ln},j} - d_{\text{Ln},j})/b} \tag{1}$$

where  $R_{\text{Ln},j}$  are the bond-valence parameters for the interacting atoms (La–O, 2.148 Å; La–N, 2.261 Å)<sup>21</sup> and b is a constant (0.37 Å). The bond-valence sum (BVS) of the metal ion  $V_{\text{Ln}}$  is supposed to match its oxidation state,<sup>20</sup> if average bonds are standard:

$$V_{\rm Ln} = \sum_{j} \nu_{{\rm Ln},j} \tag{2}$$

The BVS for the  $[La(L1)_3]\cdot CH_3CN$  structure (3.03 and 3.07) is close to the expected value for  $La^{III}$  (3.00  $\pm$  0.25) (Table 2).<sup>20,21</sup> The average contributions from the coordinating

Table 2. Bond Valence Parameters of [La(L1)<sub>3</sub>]·CH<sub>3</sub>CN<sup>a</sup>

		$ u_{\mathrm{Ln,j}}^{b}$			
complex	$V_{ m Ln}$	0	N(py)	N(b)	
$[La(L1)_3]$ (1)	3.07	0.44(1)	0.31(0)	0.27(1)	
$[La(L1)_3]$ (2)	3.03	0.44(1)	0.31(1)	0.27(4)	
all data		0.44(1)	0.31(1)	0.27(3)	

 $^a$ Two independent molecules are present in the unit cell.  $^b$ Bond-valence contribution with standard deviation  $2\sigma$  averaged over the three ligands.

groups are in the expected order of affinity O, 0.44(1) > N(py), 0.31(1) > N(b), 0.27(3) (Table 2) and are within experimental error of those reported for the reference complexes R1 (Chart 1).  $^{17}$ 

The X-ray structure of  $[Eu(L1)_3]$  was of low quality (not shown), but it confirmed the connectivity, the presence of two independent molecules, and the  $C_3$ -symmetry of the complex. The long Eu–Eu distance in the structure (>9 Å) may minimize concentration quenching and may favor efficient luminescence of EuL1.

A review of the literature reveals that  $C_3$ -symmetry is rare for mononuclear tris-complexes  $[\text{Ln}(\text{N}^{\wedge}\text{N}^{\wedge}\text{O})_3]^{0/3-}$ . Only two examples of  $C_3$ -symmetry but 32 examples of  $C_1$ -symmetry (where the three ligands are arranged "up-up-down") were

### Chart 1. Reference Ligands and Complexes<sup>a</sup>

R' N OH OH R = 
$$n$$
-alkyl, aryl [Ln(Ligand)<sub>3</sub>]  $C_1$ , R2  $C_1$ , R1  $C_1$ , R2  $C_1$ , R3  $C_1$  or  $C_3$ , R4  $C_1$ , R5  $C_1$  or  $C_3$ , R9  $C_1$  or  $C_3$ , R1  $C_1$  or  $C_3$ , R2  $C_1$  or  $C_3$ , R2  $C_1$  or  $C_3$ , R3  $C_1$  or  $C_3$ , R9  $C_1$  or  $C_3$ , R9  $C_1$  or  $C_3$ , R10

"The ligands bond by the set of N^NO atoms with deprotonated carboxylate, phenolate, and tetrazolate groups. The composition and symmetry of the complexes are indicated. From the references: R1,<sup>17</sup> R2, R3, <sup>22</sup> R4, <sup>23</sup> R5, <sup>24</sup> R6, <sup>2</sup> R7, <sup>2</sup> R8, <sup>25</sup> R9, <sup>26</sup> R10. <sup>36</sup>

reported for the structures of the reference complexes  $R1-R5^{2,17,22-24}$  and  $R7-R9^{2,25,26}$  (Chart 1).

**Electronic States of the Ligands.** The new ligands and their complexes exhibit electronic absorption transitions at wavelengths of less than 410 nm in organic solvents (Figure 3). The main composite absorption band with a maximum at 315-342 nm is assigned to the  $\pi \to \pi^*$  transitions of the benzimidazole chromophore. From the ligands to the complexes,




Figure 3. Absorption spectra of ligands (in DMSO) and complexes (LnL1 in DMSO; LnL2 in dichloromethane).


Table 3. Absorption Spectra of Ligands and Complexes

compound	$\lambda_{\rm max}/{\rm nm}~(\varepsilon/10^3~{\rm M}^{-1}~{\rm cm}^{-1})$
HL1·H <sub>2</sub> O	315 (22)
$[La(L1)_3]\cdot 4H_2O$	315 (62)
$[Eu(L1)_3]\cdot 4H_2O$	316 (59)
HL2·0.5H <sub>2</sub> O	334 (23)
$[La(L2)_3] \cdot 4H_2O^b$	340 (48), 256 (24)
$[Eu(L2)_3] \cdot 5H_2O^b$	342 (50), 254 (27)

<sup>a</sup>See Figure 3. In DMSO at 298 K. Errors:  $\lambda_{\max}$  ±1 nm;  $\varepsilon$ , ±5%. <sup>b</sup>In dichloromethane.

its maximum red-shifts by up to 8 nm and its molar absorption coefficient increases from  $(22-23) \times 10^3 \text{ M}^{-1} \text{ cm}^{-1}$  to  $(48-62) \times 10^3 \text{ M}^{-1} \text{ cm}^{-1}$  (Table 3).

The ligand-to-lanthanide energy transfer often occurs mainly from the triplet state of the ligand.  $^{1,2,27,28}$  Its efficiency depends on the overlap integral between the emission spectrum of the donor and the absorption spectrum of the acceptor and may be related to the energy gap between the ligand triplet state and the lanthanide receiving level(s).  $^{1,28}$  The triplet-state energies of the coordinated ligands in lanthanum complexes ( $E_{\rm T}$ ) were determined from the zero-phonon transition in the phosphorescence spectra at 77 K to be 20 400 cm $^{-1}$  for LaL1 and 19 700 cm $^{-1}$  for LaL2 (Figure 4 and Table 4). These ligand



**Figure 4.** Phosphorescence spectra (corrected and normalized) of polycrystalline solid lanthanum complexes at 77 K.

Table 4. Phosphorescence of Lanthanum Complexes<sup>a</sup>


	$E/10^3 \text{ cm}^{-1}$			
complex	0-0	0-1	Δ	
$[La(L1)_3]\cdot 4H_2O$	20.4	19.3	1.1	
$[La(L2)_3]\cdot 4H_2O$	19.7	18.2	1.5	

<sup>a</sup>See Figure 4. In polycrystalline solid at 77 K. Error: ±200 cm<sup>-1</sup>.

triplet states have sufficiently high energy for exothermic energy transfer to the  $\rm Eu^{III}$  excited states  $^{29}$   $\rm Eu(^3D_1)$  at 19 000 cm<sup>-1</sup> and  $\rm Eu(^5D_0)$  at  $\sim$ 17 230 cm<sup>-1</sup>.

The electron-donor *n*-octyloxy group in the benzimidazole heterocycle red-shifts both the absorption maximum by 1800–2400 cm<sup>-1</sup> (19–26 nm) and the triplet state by 700 cm<sup>-1</sup> from **HL1/LnL1** to **HL2/LnL2** by generating intraligand benzimidazole-centered "alkoxy"-to-imine charge-transfer transition.


**Europium Luminescence.** Upon excitation with UV and visible light, the new europium complexes emit characteristic red luminescence with a line-like spectrum in the range 575-710 nm due to the metal-centered  $^5D_0 \rightarrow ^7F_J$  ( $0 \rightarrow J, J = 0-4$ ) transitions (Figure 5). The emission spectra are independent of the excitation wavelength. The excitation spectra correspond to the ligand absorption transitions, thereby confirming



**Figure 5.** Luminescence spectra (corrected and normalized) of the europium complexes displaying the  ${}^5D_0 \rightarrow {}^7F_J (J = 0-4)$  transitions at 298 K in the polycrystalline solid and in dichloromethane solution;  $\lambda_{evc} = 330 \text{ nm}$ ; emission slit: 0.2 nm.

ligand-to-europium energy transfer (Figure S1 in the Supporting Information). The new europium complexes do not exhibit ligand-centered fluorescence and phosphorescence.

High-resolution excitation scans over the  $^5D_0 \leftarrow ^7F_0$  transition of the polycrystalline solid complexes at 298 K exhibit one asymmetrical line with full width at half height (fwhh) of 9 cm<sup>-1</sup> and maximum at 17 236 cm<sup>-1</sup> for **EuL1** or 17 232 cm<sup>-1</sup> for **EuL2** (Figure 6). Upon cooling to 10 K, the



**Figure 6.** High-resolution excitation (exc) and emission (em) spectra of the  $^5\mathrm{D}_0 \to ^7\mathrm{F}_0$  transition of the polycrystalline solid europium complexes with 1 Å bandpass at 298 K and 10 K. The emission (for the excitation spectra) was monitored at the  $^5\mathrm{D}_0 \to ^7\mathrm{F}_2$  transition at 610–620 nm.

 $^5D_0 \leftarrow ^7F_0$  excitation transition for **EuL1** becomes narrower (fwhh = 4.4 cm<sup>-1</sup>) and shifts to 17 226 cm<sup>-1</sup>, but it remains asymmetrical, while the  $^5D_0 \rightarrow ^7F_0$  emission transition at 10 K displays a symmetrical broad line at 17 226 cm<sup>-1</sup> with a fwhh of 9.8 cm<sup>-1</sup> (Figure 6). A single sharp symmetrical line is expected for the electronic transition between the  $^5D_0$  and  $^7F_0$  levels of Eu<sup>III</sup> in each unique coordination environment, provided that the transition is allowed by symmetry. The observed asymmetry of the  $^5D_0 \leftarrow ^7F_0$  excitation transition for the polycrystalline solids may arise from the presence of two nearly identical coordination environments of Eu<sup>III</sup> (as confirmed by the X-ray analysis), from the variation in the conformation of (benzyl

groups of the) organic ligands, and from defects in the microcrystals.<sup>3</sup>

The X-ray structures reveal that LnL1 in single crystals have  $C_3$ -symmetry (Figures 1 and 2). Luminescence spectroscopy indicates that EuL1 and EuL2 in polycrystalline solids have  $C_3$ -symmetry also. The corrected emission spectra of the polycrystalline complexes EuL1 and EuL2 are similar (Figure 5). The emission intensity is fairly equally distributed among three main transitions (Table 5), the magnetic-dipole  $^5D_0 \rightarrow ^7F_1$  (22–24%), the hypersensitive  $^5D_0 \rightarrow ^7F_2$  (33–35%), and  $^5D_0 \rightarrow ^7F_4$  (38%), a situation typical of  $C_3$ -symmetry (see Figures 1 and 2). $^{3,23,30}$ 

The crystal field splitting (Table 6) reveals 1, 2, 2 (or 2 + 1 shoulder), and at least 5 (or 4 + 1 shoulder) components for the  ${}^5D_0 \rightarrow {}^7F_J$  transitions for J = 0, 1, 2, and 4. It is nearly in line with predictions for  $C_3$ -symmetry (1, 2, 3, and 6 components for J = 0, 1, 2, and 4),  ${}^{3,30}$  except for the very weak intensity of the  $0 \rightarrow 0$  transition, which is allowed in  $C_3$  by symmetry-governed selection rules. The emission spectra of the polycrystalline **EuL1** and **EuL2** are almost consistent with a higher than  $C_3$ -symmetry in the same trigonal class, that is, with  $D_3$ -symmetry (0, 2, 2, and 4 transitions predicted for J = 0, 1, 2, and 4).

High-resolution emission spectra of  ${}^5D_0 \rightarrow {}^7F_1$  and  ${}^5D_0 \rightarrow {}^7F_2$  transitions of polycrystalline **EuL1** at 10 K exhibit more components than would be expected for  $C_3$ -symmetry (Figure S2 in the Supporting Information), because of the reasons given above to explain the asymmetric  ${}^5D_0 \leftarrow {}^7F_0$  excitation transition (Figure 6).

The emission spectrum of EuL2 radically changes in going from the solid state to dichloromethane solution, indicating a change in the coordination environment of europium (Figure 5). In solution, the  $0 \rightarrow 0$  transition gains intensity and the  $0 \rightarrow 2$  one becomes dominant, representing 48% of the total emission intensity (Table 5). In contrast, the contributions of the  $0 \rightarrow 1$  and the  $0 \rightarrow 4$  transitions decrease to 19% and 30%, respectively. The number of components of the  $0 \rightarrow 1$ transition increases from two to three, and its total crystal-field splitting increases by about 100 cm<sup>-1</sup> to become 278 cm<sup>-1</sup> (Table 6). The distribution of intensity and the fine structure of the luminescence spectrum of EuL2 in the solution (1, 3, >3,and >5 components for J=0, 1, 2, 4) are not consistent with  $C_3$ -symmetry (which is observed in the solid), but point to a low  $C_1$ -symmetry around the metal ion (1, 3, 5, and9 components predicted for J = 0, 1, 2, and 4). 3,17,23The luminescence spectrum, however, reflects the presence of only one emitting  $\mathbf{\hat{E}u}^{III}$  center in the solution (Figure 5 and Table 6).

The luminescence decays of EuL1 and EuL2 ( $\tau_{\rm obs}$ , Table 7) in the polycrystalline solid and in dichloromethane solution are single-exponential functions, again confirming the presence of one main emissive europium center in each case. The long luminescence lifetimes of 1.56–2.67 ms and the high ligand-sensitized luminescence quantum yields of 25–41% (Table 7)

Table 5. Relative Luminescence Intensity of  ${}^5D_0 \rightarrow {}^7F_I$  Transitions of Europium Complexes

complex		0→0	0→1	0→2	0→3	0→4	total/0 $\rightarrow$ 1
$[Eu(L1)_3]\cdot 4H_2O$	solid	0.005	1.00	1.36	0.16	1.57	4.10
$[Eu(L2)_3] \cdot 5H_2O$	solid	0.005	1.00	1.56	0.19	1.71	4.47
	$CH_2Cl_2$	0.02	1.00	2.60	0.15	1.63	5.40

<sup>&</sup>lt;sup>a</sup>From Figure 5. Normalized to the  $^5D_0$  →  $^7F_1$  transition. Integrated from the corrected luminescence spectra (photon/s) versus wavelength (nm) at 298 K at  $λ_{exc}$  = 355 nm. Estimated error: ±5%.

Table 6. Energies of <sup>7</sup>F<sub>I</sub> and <sup>5</sup>D<sub>0</sub> Levels of Europium Complexes<sup>a</sup>

		$E/\mathrm{cm}^{-1}$					
complex		$^{7}F_{0}$	${}^{7}F_{1}$	$^{7}F_{2}$	${}^{7}F_{3}$	$^{7}\mathrm{F}_{4}$	<sup>5</sup> D <sub>0</sub>
[Eu(L1) <sub>3</sub> ]·4H <sub>2</sub> O	solid	0	275	997	1842	2718	17236
			446	1034 (sh)	1941	2760	
				1128	2015 (w)	2897	
						2950	
						3023	
$[Eu(L2)_3] \cdot 5H_2O$	solid	0	266	982	1833	2714	17232
			442	1129	1932	2901	
					2021 (w)	2967	
						3027	
	$CH_2Cl_2$	0	275	988	1883 (br)	2697	17253
			373	1067		2773	
			553	1186 (sh)		2832	
						2902	
						3053	

<sup>&</sup>lt;sup>a</sup>From Figure 5. At 298 K. Estimated error: ±6 cm<sup>-1</sup>.

Table 7. Luminescence Parameters of Europium Complexes<sup>a</sup>

		$ au_{ m obs}/{ m ms}$						
complex		$\nu_{0-0}/{\rm cm}^{-1b}$	$Q_{\rm L}^{\rm Eu}/\%$	298 K	10 K	$ au_{ m rad}/{ m ms}$	$Q_{\rm Eu}^{\rm Eu}/\%$	$\eta_{ m sens}/\%$
[Eu(L1) <sub>3</sub> ]·4H <sub>2</sub> O	solid	17236(9)	41	1.94	2.53	4.93	39	100
$[Eu(L2)_3] \cdot 5H_2O$	solid	17232(9)	25	1.56	2.67	4.52	35	71
	$CH_2Cl_2$		32	2.18		4.38	50	64

<sup>&</sup>quot;At 298 K, unless stated otherwise.  $\lambda_{\rm exc}$  = 355 nm. Relative errors:  $\tau_{\rm obs}$ ,  $\pm 2\%$ ;  $Q_{\rm L}^{\rm Eu}$ ,  $\pm 10\%$ ;  $\tau_{\rm rad}$ ,  $\pm 10\%$ ;  $Q_{\rm Ew}^{\rm Eu}$   $\pm 12\%$ ;  $\eta_{\rm sens}$ ,  $\pm 22\%$ . From Figure 6. Full-width at half-height in parentheses.

indicate that water molecules are not coordinated to the europium in EuL1 and EuL2 in the solid and in solution. 17,31

The luminescence lifetimes of the polycrystalline complexes increase significantly on cooling from 298 K to 10 K (but the luminescence decays remain single-exponential functions), especially for EuL2, pointing to the presence of a thermally activated nonradiative deactivation pathway. It may be caused by the europium-to-ligand back-transfer of energy,  $^{28}$  because the energy gaps from the ligand triplet to the receiving levels Eu( $^5D_1$ ) at 19 000 cm $^{-1}$  and Eu( $^5D_0$ ) at  $\sim$ 17 230 cm $^{-1}$  are only 700–3170 cm $^{-1}$ . Alternatively, it may be caused by quenching of Eu<sup>III</sup> by a ligand-to-metal charge transfer (LMCT, a frequently observed process for electron-donating ligands  $^{32}$ ), especially for complex EuL2, with an electron-rich n-octyloxy-substituted ligand.

We have analyzed the photophysics of the complexes in terms of eq 3, where  $Q_L^{Eu}$  and  $Q_{Eu}^{Eu}$  are ligand-sensitized and intrinsic  $Eu(^5D_0)$  luminescence quantum yields,  $\eta_{sens}$  is the efficiency of ligand-to-europium energy transfer, and  $\tau_{obs}$  and  $\tau_{rad}$  are the observed and radiative lifetimes of  $Eu(^5D_0)$ :

$$Q_{L}^{Eu} = \eta_{sens} \times Q_{Eu}^{Eu} = \eta_{sens} \times (\tau_{obs}/\tau_{rad})$$
 (3)

The radiative lifetime of Eu( $^5D_0$ ) was calculated from eq 4, $^{33}$  where n is the refractive index (1.5 for the solid complexes or 1.4242 for the CH<sub>2</sub>Cl<sub>2</sub> solution),  $A_{0\rightarrow 1}$  is the spontaneous emission probability for the  $^5D_0 \rightarrow ^7F_1$  transition in vacuo (14.65 s<sup>-1</sup>), and  $I_{\text{tot}}/I_{0\rightarrow 1}$  is the ratio of the integrated emission intensity of the total corrected europium spectrum to that of the magnetic-dipole  $^5D_0 \rightarrow ^7F_1$  transition (Table 5):

$$1/\tau_{\rm rad} = A_{0 \to 1} \times n^3 \times (I_{\rm tot}/I_{0 \to 1}) \tag{4}$$

Table 7 reports the photophysical parameters. The radiative lifetimes of the solid complexes are 4.93 ms for EuL1 and 4.52 ms for EuL2. When EuL2 is dissolved in dichloromethane, one anticipates a lengthening of its  $\tau_{\rm rad}$  from 4.52 ms (in the solid) to 5.28 ms (in solution) due to the decrease in refractive index (eq 4), <sup>1,2</sup> provided that the coordination sphere of the europium ion remains the same. In the experiment, however, we observe a shortening of the radiative lifetime to 4.38 ms in dichloromethane, which indicates that the coordination sphere of the europium ion changes upon dissolution of EuL2, probably to give a lower symmetry environment.

The intrinsic quantum yield of europium could not be measured because of the low intensity of the f–f absorption. Instead, it was calculated from the ratio  $Q_{\rm Eu}^{\rm Eu}=\tau_{\rm obs}/\tau_{\rm rad}$  to be 35–39% for the solid complexes and 50% for the EuL2 solution. The higher  $Q_{\rm Eu}^{\rm Eu}$  in solution for EuL2 results both from the longer  $\tau_{\rm obs}$  and from the shorter  $\tau_{\rm rad}$ .

In the solid complexes, the calculated efficiency of ligand-to-europium energy transfer,  $\eta_{\rm sens} = Q_{\rm L}^{\rm Eu}/Q_{\rm Eu}^{\rm Eu}$  decreases from 100% in **EuL1** to 71% in **EuL2**, because of the more facile nonradiative deactivation of **EuL2** both by energy back-transfer and by LMCT (see above). The sensitization efficiency for **EuL2** in solution (64%) is comparable to that in the solid (71%), indicating that the ligands remain bound to the europium in dichloromethane, a noncoordinating solvent.

The luminescence quantum yield and observed lifetime of EuL2 increase in going from the solid to the solution, probably, in part, because the five cocrystallized water molecules in the solid EuL2 quench the emissive state of europium via a second-sphere interaction. In contrast, in dichloromethane, these water molecules move into the bulk solution and are less likely to quench the europium ion.

**Symmetry and Luminescence.** The crystal structures reveal that the solid complexes **LnL1** have a rare  $C_3$ -symmetry of the lanthanide coordination polyhedron (Figure 2). The nearly identical luminescence spectra of the polycrystalline **EuL1** and **EuL2** suggest that the **LnL2** complexes in the solid have  $C_3$ -symmetry also (Figure 5). In fact, the luminescence spectra of the polycrystalline **EuL1** and **EuL2** are similar in intensity distribution and fine structure to those of the reference  $Eu^{III}$  complexes  $R4^{23}$  and  $R6^2$  (Chart 1) of  $C_3$ - or  $D_3$ -symmetry (in which the intensity of the  $0 \rightarrow 1$  transition is comparable to that of the  $0 \rightarrow 2$ , while the  $0 \rightarrow 4$  transition is the most intense), but are different from those of complexes  $R1^{17}$  of  $C_1$ -symmetry (in which the  $0 \rightarrow 2$  transition is the most intense).

The lanthanide—ligand bonds have predominant ionic character and, therefore, are nondirectional and labile, even with polydentate ligands.  $^{2,34}$  The significant changes in the luminescence spectrum as well as the shortening of the radiative lifetime of **EuL2** in going from the solid state to dichloromethane solution indicate a modification in the coordination environment of the europium ion. For example, in sharp contrast to **EuL2**, the radiative lifetime of **R6**, which have pseudo- $D_3$ -symmetry in all media, increases from 4.9 ms in the solid to 6.2—6.9 ms in aqueous solution due to the change in refractive index.  $^2$ 

We consider that in dichloromethane solution the labile lanthanide-ligand bonding lowers the symmetry of EuL2 from  $C_3$  to  $C_1$  by modifying the arrangement of the three ligands from "up-up-up" to "up-up-down" (for example, see the  $C_1$ -crystal structures of  $\mathbf{R}\mathbf{1}^{17}$ ). Taking into account the spectroscopic data, a mixture of  $C_1$ - and  $C_3$ -species in solution can most probably be ruled out. The photophysical properties of EuL2 are different in the solid but are similar in solution to those of the reference  $Eu^{III}$  complexes with  $C_1$ -symmetry. For example, for 16 complexes R1, which have C1-symmetry in all media, the radiative lifetimes are 3.22-4.7 ms in the solid and often increase to 3.91-4.40 ms in dichloromethane solution, while the luminescence spectra do not change (apart from becoming broader in solution) and have three components for the  $0 \rightarrow 1$  transition. <sup>17</sup> Moreover, the luminescence spectra of the  $C_1$ -symmetry complexes  $R1^{17}$  and  $R3-R5^{22-24}$  are dominated by the  $0 \rightarrow 2$  transition.

It appears that the  $C_3$ - and  $C_1$ -symmetry species (isomers) for **EuL2** are close in energy and, because of the labile lanthanide—ligand bonding, easily interconvert. The isolation of a rare  $C_3$ -species in the solid state for **LnL1** and **LnL2** is probably driven by crystal packing of the N-benzyl groups (in contrast, the N-alkyl and N-aryl analogues **R1** have  $C_1$ -symmetry in all media<sup>17</sup>). The cocrystallized solvent does not seem to play a crucial role in determining the  $C_3$ -symmetry of the complex in the solid; for example, a molecule of acetonitrile is cocrystallized in the single crystal of  $[La(L1)_3]$ ·CH<sub>3</sub>CN, but water molecules are cocrystallized in the polycrystalline  $[Eu(L1)_3]$ ·4H<sub>2</sub>O and  $[Eu(L2)_3]$ ·5H<sub>2</sub>O. The conversion of  $C_3$ - to  $C_1$ -species of **EuL2** in going from the solid to the solution is probably driven by a gain in entropy on lowering of the symmetry.

We note previous reports on the isomerization of the *fac* and *mer* six-coordinate complexes  $[LnCl_3(hexamethylphosphoramide)_3]^{35}$  and of the  $C_3$  and  $C_1$  nine-coordinate complexes  $[Ln(8-hydroxyquinolinate-2-carboxylate)_3]^{3-}$  and  $R9^{26}$  (Chart 1). The thermodynamics of the interconversion of  $C_3$ - and  $C_1$ -species in acetonitrile solution were studied for R10 (Chart 1). Two symmetry/structure isomers of eight-coordinate lanthanide

complexes were crystallized for  $[Ln(\beta\text{-diketonate O^O})_3(H_2O)_2]^{37}$  and  $[Ln(\beta\text{-diketonate O^O})_3(\text{diimine N^N})]^{38}$  and were identified by X-ray structure analysis and by luminescence spectroscopy of the europium complexes.

**Conclusions.** We report on mononuclear nine-coordinate lanthanum(III) and europium(III) complexes  $[Ln(N^{N}O)_3]$  with a rare  $C_3$ -symmetry of the lanthanide coordination polyhedron in the solid. These complexes, however, exhibit a lower  $C_1$ -symmetry in dichloromethane solution.

The change of the luminescence spectrum and the shortening of the Eu( $^5D_0$ ) radiative lifetime in going from the (higher)  $C_3$ - to the (lower)  $C_1$ -symmetry species of EuL2 (Table 5) suggests that the lower is the symmetry, the more allowed are the forbidden f–f transitions, which is in line with the predictions made from group-theoretical considerations.  $^{1-3}$ 

The shorter is the radiative lifetime, in other words, the faster is the rate of the radiative transition, the better the radiative process can compete with the nonradiative processes (provided that they are not changed), and, therefore, the higher is the luminescence efficiency, 1,2,32,39 which is what we observe for **EuL2** in going from the solid to the solution (Table 5).

Therefore, care has to be taken when comparing photophysical properties of a labile lanthanide complex in various media, because the coordination environment of a lanthanide ion can change its symmetry even without a change in its composition.

### EXPERIMENTAL SECTION

General Information. Elemental analyses were performed by Dr. E. Solari, Service for Elemental Analysis, Institute of Chemical Sciences and Engineering (EPFL). <sup>1</sup>H NMR spectra were recorded on Bruker Avance DRX 400 MHz spectrometer. Absorption spectra were measured on a PerkinElmer Lambda 900 UV/vis/NIR spectrometer. Luminescence spectra were recorded on a Horiba-Jobin Yvon Fluorolog FL 3-22 spectrometer and were corrected for the instrumental function. Quantum yields were determined on the same instrument by an absolute method with a modified homemade integrating sphere. Luminescence lifetimes were measured with a previously described instrumental setup.<sup>17</sup> Reported luminescence quantum yields and lifetimes are an average of 3-6 independent determinations. Spectroscopic studies were conducted in optical cells of 2 mm path length or in 2 mm i.d. quartz capillaries under air. The solutions in CH<sub>2</sub>Cl<sub>2</sub> (Fisher Scientific, analytical reagent grade) were freshly prepared before each experiment.

Commercial reagents were used without purification. Chromatography was performed on a column with an i.d. of 30 mm on silica gel 60 (Fluka, Nr 60752). The progress of reactions and the elution of products were followed on TLC plates (silica gel 60  $F_{254}$  on aluminum sheets, Merck).

Synthesis of Ligands. The reaction was performed under air.  $^{17,19}$  Substituted pyridine-2-carboxaldehyde (its synthesis is described in the Supporting Information) was dissolved in formic acid (Merck, 98–100%) at room temperature to give a yellow solution, which sometimes appeared cloudy because of the presence of a red solid, probably residual Se from the previous synthetic step. The amount of formic acid was a minimum of 3–5 molar equiv relative to aldehyde or the minimum volume necessary to dissolve the aldehyde at 0 °C. The solution was cooled to 0 °C and stirred for 10 min. Then, cold  $\rm H_2O_2$  (30% wt aqueous solution) was added in excess. The solution was stirred for 6 h at 0 °C and kept overnight at 0 °C. Addition of ice-cold water to the solution precipitated the product. The suspension was stirred for 1 h at 0 °C and filtered. The product was washed with water and organic solvent, and then it was dried under vacuum. Further details are provided below.

**HL1·H<sub>2</sub>O.** Aldehyde L1-CHO (Supporting Information, 445 mg, 1.42 mmol), formic acid (3 mL, 3.66 g, 0.08 mol), and H<sub>2</sub>O<sub>2</sub> (0.85 mL of a 30% wt aqueous solution containing 283 mg of H<sub>2</sub>O<sub>2</sub>, 8.32 mmol)

gave after precipitation with 10 mL of water and after washing with water, hexane, and a small volume of 1:1 hexane/ether a white solid: 436 mg (1.26 mmol, 88%). Anal. Calcd for  $C_{20}H_{15}N_3O_2\cdot H_2O$  (MW 347.37): C, 69.15; H, 4.93; N, 12.10. Found: C, 69.14; H, 4.89; N, 11.77. <sup>1</sup>H NMR (400 MHz, DMSO- $d_6$ ):  $\delta$  = 8.55 (dd, J = 7.6, 1.2 Hz, 1H), 8.19–8.08 (m, 2H), 7.78 (d, J = 7.2 Hz, 1H), 7.71 (d, J = 7.2 Hz, 1H), 7.36–7.25 (m, 2H), 7.24–7.12 (m, 5H), 6.40 (s, 2H) ppm;  $CO_2H$  proton was not observed. ESI $^-$  TOF MS: m/z 328.1 {M  $^-$  H} $^-$ .

**HL2·0.5H<sub>2</sub>O.** Aldehyde L2-CHO (Supporting Information, 627 mg, 1.42 mmol), formic acid (4 mL, 4.88 g, 0.11 mol), and H<sub>2</sub>O<sub>2</sub> (0.85 mL of a 30% wt aqueous solution containing 283 mg of H<sub>2</sub>O<sub>2</sub>, 8.32 mmol) gave after precipitation with 15 mL of water and after washing with water and hexane a pale pink solid: 565 mg (1.21 mmol, 85%). Anal. Calcd for C<sub>28</sub>H<sub>31</sub>N<sub>3</sub>O<sub>3</sub>·0.5H<sub>2</sub>O (MW 466.57): C, 72.08; H, 6.91; N, 9.01. Found: C, 72.16; H, 6.89; N, 8.94. <sup>1</sup>H NMR (400 MHz, DMSO- $d_6$ ):  $\delta$  = 8.46 (dd, J = 7.6, 1.6 Hz, 1H), 8.12–8.02 (m, 2H), 7.62 (d, J = 8.8 Hz, 1H), 7.22 (d, J = 2.0 Hz, 1H), 7.21–7.10 (m, 5H), 6.89 (dd, J = 8.8, 2.4 Hz, 1H), 6.34 (s, 2H), 3.99 (t, J = 6.8 Hz, 2H), 1.75–1.65 (m, 2H), 1.46–1.18 (m, 10H), 0.85 (t, J = 6.8 Hz, 3H) ppm; CO<sub>2</sub>H proton not observed. ESI<sup>-</sup> TOF MS: m/z 456.2 {M – H}<sup>-</sup>.

**Synthesis of Complexes.** The reaction was performed under air. The ligand was suspended in ethanol (5 mL), followed by addition of NaOH dissolved in water (used as a stock solution with approximately 100 mg of NaOH per 10 mL of water) and stirring for 5 min to give a solution. The solution was warmed to 70-80 °C. After 5 min of stirring, a solution of LnCl<sub>3</sub>·nH<sub>2</sub>O in water (2 mL) was added dropwise over 5 min (a white precipitate may form on addition). Water (1 mL for LnL1 and EuL2; 2 mL for LaL2) was added to induce and complete precipitation of the complex. The suspension was stirred for 10 min at 70-80  $^{\circ}$ C, cooled to 40-50  $^{\circ}$ C, and filtered while warm (the strict control of time and temperature is not required in this synthesis). The product was washed with ethanol/water (1:1) and either ether (LnL1) or hexane (LnL2) in that order. The complexes were dried under vacuum at room temperature. All of the complexes are soluble in DMSO, hot ethanol, and hot acetonitrile and are insoluble in hexane, ether, and water. The complexes LnL2 (but not LnL1) are soluble in dichloromethane. Further details are provided

[La(L1)<sub>3</sub>]·4H<sub>2</sub>O: white solid; 48 mg (0.040 mmol, 84%) from HL1·H<sub>2</sub>O (50 mg, 0.144 mmol), NaOH (5.76 mg, 0.144 mmol), and LaCl<sub>3</sub>·Th<sub>2</sub>O (17.8 mg, 0.048 mmol). Anal. Calcd for C<sub>60</sub>H<sub>42</sub>LaN<sub>9</sub>O<sub>6</sub>·4H<sub>2</sub>O (MW 1196.00): C, 60.25; H, 4.21; N, 10.54. Found: C, 60.32; H, 4.24; N, 10.26. <sup>1</sup>H NMR (400 MHz, DMSO- $d_6$ , 373 K, [C] = 0.79 × 10<sup>-3</sup> M; the complex dissociates in DMSO, a coordinating solvent): δ = 8.17 (d, J = 7.6 Hz, 3H), 8.00 (t, J = 7.6 Hz, 3H), 7.95 (d, J = 7.6 Hz, 3H), 7.87 (d, J = 8.0 Hz, 3H), 7.61 (d, J = 8.0 Hz, 3H), 7.29 (t, J = 7.6 Hz, 3H), 7.27–7.07 (m, 18H), 6.18 (s, 6H) ppm.

[Eu(L1)<sub>3</sub>]·4H<sub>2</sub>O: white solid; 49 mg (0.041 mmol, 84%) from HL1·H<sub>2</sub>O (50 mg, 0.144 mmol), NaOH (5.76 mg, 0.144 mmol), and EuCl<sub>3</sub>·6H<sub>2</sub>O (17.5 mg, 0.048 mmol). Anal. Calcd for C<sub>60</sub>H<sub>42</sub>EuN<sub>9</sub>O<sub>6</sub>·4H<sub>2</sub>O (MW 1209.06): C, 59.60; H, 4.17; N, 10.43. Found: C, 59.66; H, 4.34; N, 10.16.

**[La(L2)<sub>3</sub>]·4H<sub>2</sub>O:** pale pink solid; 43 mg (0.027 mmol, 78%) from HL2·0.5H<sub>2</sub>O (50 mg, 0.107 mmol), NaOH (4.3 mg, 0.107 mmol), and LaCl<sub>3</sub>·7H<sub>2</sub>O (13.3 mg, 0.035 mmol). The <sup>1</sup>H NMR of the complex in CD<sub>2</sub>Cl<sub>2</sub>, a noncoordinating solvent, at room temperature was broad and noninformative. Anal. Calcd for  $C_{84}H_{90}LaN_{9}O_{9}\cdot4H_{2}O$  (MW 1580.63): C, 63.83; H, 6.25; N, 7.98. Found: C, 63.73; H, 6.44; N, 7.79. ESI<sup>+</sup> TOF MS: m/z 1531.7 {M + Na}<sup>+</sup>.

[Eu(L2)<sub>3</sub>]·5H<sub>2</sub>O: off-white solid; 44 mg (0.027 mmol, 78%) from HL2·0.5H<sub>2</sub>O (50 mg, 0.107 mmol), NaOH (4.3 mg, 0.107 mmol), and EuCl<sub>3</sub>·6H<sub>2</sub>O (13.1 mg, 0.035 mmol). Anal. Calcd for  $C_{84}H_{90}EuN_9O_9$ ·5 H<sub>2</sub>O (MW 1611.71): C, 62.60; H, 6.25; N, 7.82. Found: C, 62.64; H, 6.35; N, 7.63. ESI<sup>+</sup> TOF MS: m/z 1544.8 {M + Na}<sup>+</sup>.

### ASSOCIATED CONTENT

# Supporting Information

The Supporting Information is available free of charge on the ACS Publications website at DOI: 10.1021/acs.inorg-chem.5b01580.

Synthesis of precursors; excitation and emission spectra; <sup>1</sup>H NMR spectra; crystallographic data (PDF) CIF for the crystal structure CCDC 1409902 (CIF)

# **AUTHOR INFORMATION**

# **Corresponding Authors**

\*E-mail (N. M. Shavaleev): shava@mail.ru.

\*E-mail (J.-C. G. Bünzli): jean-claude.bunzli@epfl.ch. Tel: +41 21 693 9821. Fax: +41 21 693 5550.

#### Notes

The authors declare no competing financial interest.

### ACKNOWLEDGMENTS

This project was supported by the Swiss National Science Foundation (grant 200020 119866/1).

### REFERENCES

- (1) Bünzli, J.-C. G. Coord. Chem. Rev. 2015, 293-294, 19.
- (2) Bünzli, J.-C. G.; Chauvin, A.-S.; Kim, H. K.; Deiters, E.; Eliseeva, S. V. Coord. Chem. Rev. 2010, 254, 2623 and references therein.
- (3) (a) Tanner, P. A. Chem. Soc. Rev. **2013**, 42, 5090. (b) Binnemans, K. Coord. Chem. Rev. **2015**, 295, 1.
- (4) Vicentini, G.; Zinner, L. B.; Zukerman-Schpector, J.; Zinner, K. Coord. Chem. Rev. 2000, 196, 353.
- (5) (a) de Sá, G. F.; Malta, O. L.; de Mello Donegá, C.; Simas, A. M.; Longo, R. L.; Santa-Cruz, P. A.; da Silva, E. F., Jr. Coord. Chem. Rev. 2000, 196, 165. (b) Gawryszewska, P.; Sokolnicki, J.; Legendziewicz, J. Coord. Chem. Rev. 2005, 249, 2489. (c) Armelao, L.; Quici, S.; Barigelletti, F.; Accorsi, G.; Bottaro, G.; Cavazzini, M.; Tondello, E. Coord. Chem. Rev. 2010, 254, 487. (d) Ma, Y.; Wang, Y. Coord. Chem. Rev. 2010, 254, 972. (e) Reddy, M. L. P.; Sivakumar, S. Dalton Trans. 2013, 42, 2663. (f) de Bettencourt-Dias, A.; Barber, P. S.; Viswanathan, S. Coord. Chem. Rev. 2014, 273–274, 165. (g) Comby, S.; Surender, E. M.; Kotova, O.; Truman, L. K.; Molloy, J. K.; Gunnlaugsson, T. Inorg. Chem. 2014, 53, 1867.
- (6) (a) Chen, F.; Bian, Z.; Huang, C. J. Rare Earths 2009, 27, 345.(b) Katkova, M. A.; Bochkarev, M. N. Dalton Trans. 2010, 39, 6599.
- (7) van der Ende, B. M.; Aarts, L.; Meijerink, A. Phys. Chem. Chem. Phys. 2009, 11, 11081.
- (8) Andres, J.; Hersch, R. D.; Moser, J.-E.; Chauvin, A.-S. *Adv. Funct. Mater.* **2014**, 24, 5029.
- (9) Darmanyan, A. P.; Lazorchak, N.; Jardon, P. J. Photochem. Photobiol., A 1991, 58, 185.
- (10) (a) Sykes, D.; Tidmarsh, I. S.; Barbieri, A.; Sazanovich, I. V.; Weinstein, J. A.; Ward, M. D. *Inorg. Chem.* 2011, 50, 11323. (b) Caillé, F.; Bonnet, C. S.; Buron, F.; Villette, S.; Helm, L.; Petoud, S.; Suzenet, F.; Tóth, E. *Inorg. Chem.* 2012, 51, 2522. (c) Starck, M.; Ziessel, R. *Dalton Trans.* 2012, 41, 13298. (d) Fisher, C. M.; Fuller, E.; Burke, B. P.; Mogilireddy, V.; Pope, S. J. A.; Sparke, A. E.; Déchamps-Olivier, I.; Cadiou, C.; Chuburu, F.; Faulkner, S.; Archibald, S. J. *Dalton Trans.* 2014, 43, 9567. (e) Routledge, J. D.; Jones, M. W.; Faulkner, S.; Tropiano, M. *Inorg. Chem.* 2015, 54, 3337. (f) Placide, V.; Bui, A. T.; Grichine, A.; Duperray, A.; Pitrat, D.; Andraud, C.; Maury, O. *Dalton Trans.* 2015, 44, 4918. (g) Guanci, C.; Giovenzana, G.; Lattuada, L.; Platas-Iglesias, C.; Charbonnière, L. J. *Dalton Trans.* 2015, 44, 7654.
- (11) Nakamura, K.; Hasegawa, Y.; Kawai, H.; Yasuda, N.; Kanehisa, N.; Kai, Y.; Nagamura, T.; Yanagida, S.; Wada, Y. J. Phys. Chem. A 2007, 111, 3029.
- (12) Bortoluzzi, M.; Paolucci, G.; Polizzi, S.; Bellotto, L.; Enrichi, F.; Ciorba, S.; Richards, B. S. Inorg. Chem. Commun. 2011, 14, 1762.

(13) Akerboom, S.; van den Elshout, J. J. M. H.; Mutikainen, I.; Siegler, M. A.; Fu, W. T.; Bouwman, E. Eur. J. Inorg. Chem. 2013, 6137.

- (14) (a) Blasse, G. Chem. Phys. Lett. 1973, 20, 573. (b) Reisfeld, R.; Zigansky, E.; Gaft, M. Mol. Phys. 2004, 102, 1319.
- (15) (a) Kirby, A. F.; Foster, D.; Richardson, F. S. Chem. Phys. Lett. 1983, 95, 507. (b) Thompson, L. C.; Kuo, S. C. Inorg. Chim. Acta 1988, 149, 305.
- (16) Piguet, C.; Bocquet, B.; Hopfgartner, G. Helv. Chim. Acta 1994, 77, 931.
- (17) Shavaleev, N. M.; Eliseeva, S. V.; Scopelliti, R.; Bünzli, J.-C. G. Inorg. Chem. 2010, 49, 3927 and references therein.
- (18) Yang, D. L.; Fokas, D.; Li, J. Z.; Yu, L. B.; Baldino, C. M. Synthesis 2005, 47.
- (19) Dodd, R.; Le Hyaric, M. Synthesis 1993, 1993, 295.
- (20) Brown, I. D.; Altermatt, D. Acta Crystallogr., Sect. B: Struct. Sci. 1985, 41, 244.
- (21) (a) Trzesowska, A.; Kruszynski, R.; Bartczak, T. J. Acta Crystallogr., Sect. B: Struct. Sci. 2004, 60, 174. (b) Trzesowska, A.; Kruszynski, R.; Bartczak, T. J. Acta Crystallogr., Sect. B: Struct. Sci. 2005, 61, 429.
- (22) (a) Kottas, G. S.; Mehlstäubl, M.; Fröhlich, R.; De Cola, L. Eur. J. Inorg. Chem. 2007, 3465. (b) Botelho, M. B. S.; Gálvez-López, M. D.; De Cola, L.; Albuquerque, R. Q.; de Camargo, A. S. S. Eur. J. Inorg. Chem. 2013, 5064.
- (23) Yamauchi, S.; Hashibe, T.; Murase, M.; Hagiwara, H.; Matsumoto, N.; Tsuchimoto, M. *Polyhedron* **2013**, *49*, 105.
- (24) Andreiadis, E. S.; Imbert, D.; Pécaut, J.; Demadrille, R.; Mazzanti, M. Dalton Trans. 2012, 41, 1268.
- (25) Wei, H.; Yu, G.; Zhao, Z.; Liu, Z.; Bian, Z.; Huang, C. Dalton Trans. 2013, 42, 8951.
- (26) Bozoklu, G.; Marchal, C.; Pécaut, J.; Imbert, D.; Mazzanti, M. Dalton Trans. 2010, 39, 9112.
- (27) (a) Crosby, G. A.; Whan, R. E. J. Chem. Phys. 1960, 32, 614. (b) Crosby, G. A.; Whan, R. E. J. Chem. Phys. 1962, 36, 863.
- (28) Latva, M.; Takalo, H.; Mukkala, V. M.; Matachescu, C.; Rodríguez-Ubis, J. C.; Kankare, J. J. Lumin. 1997, 75, 149.
- (29) Carnall, W. T.; Fields, P. R.; Rajnak, K. J. Chem. Phys. 1968, 49, 4450
- (30) Walton, J. W.; Carr, R.; Evans, N. H.; Funk, A. M.; Kenwright, A. M.; Parker, D.; Yufit, D. S.; Botta, M.; De Pinto, S.; Wong, K.-L. *Inorg. Chem.* **2012**, *51*, 8042.
- (31) (a) Beeby, A.; Clarkson, I. M.; Dickins, R. S.; Faulkner, S.; Parker, D.; Royle, L.; de Sousa, A. S.; Williams, J. A. G.; Woods, M. J. Chem. Soc., Perkin Trans. 2 1999, 493. (b) Supkowski, R. M.; Horrocks, W. DeW., Jr. Inorg. Chim. Acta 2002, 340, 44.
- (32) Napier, G. D. R.; Neilson, J. D.; Shepherd, T. M. Chem. Phys. Lett. 1975, 31, 328.
- (33) (a) Werts, M. H. V.; Jukes, R. T. F.; Verhoeven, J. W. *Phys. Chem. Chem. Phys.* **2002**, *4*, 1542. (b) Aebischer, A.; Gumy, F.; Bünzli, J.-C. G. *Phys. Chem. Chem. Phys.* **2009**, *11*, 1346.
- (34) Bhaumik, M. L. J. Inorg. Nucl. Chem. 1965, 27, 243.
- (35) Petriček, S.; Demšar, A.; Golič, L.; Košmrlj, J. Polyhedron 2000, 19, 199.
- (36) Le Borgne, T.; Altmann, P.; André, N.; Bünzli, J.-C. G.; Bernardinelli, G.; Morgantini, P.-Y.; Weber, J.; Piguet, C. Dalton Trans. 2004. 723.
- (37) Nakamura, M.; Nakamura, R.; Nagai, K.; Shimoi, M.; Tomoda, S.; Takeuchi, Y.; Ouchi, A. Bull. Chem. Soc. Jpn. 1986, 59, 332.
- (38) (a) Holz, R. C.; Thompson, L. C. *Inorg. Chem.* **1993**, 32, 5251. (b) Thompson, L. C.; Atchison, F. W.; Young, V. G. *J. Alloys Compd.* **1998**, 275–277, 765.
- (39) Doffek, C.; Seitz, M. Angew. Chem., Int. Ed. 2015, 54, 9719.

# ■ NOTE ADDED AFTER ASAP PUBLICATION

Text corrections were made in the third paragraph in Conclusion section on September 21, 2015.