



Corrigendum

Analysis of tapered ENF specimen and characterization  
of bonded interface fracture under Mode-II loading  
[International Journal of Solids and Structures,  
40 (8), 1865–1884 (2003)] ☆

Pizhong Qiao <sup>a,\*</sup>, Jialai Wang <sup>a</sup>, Julio F. Davalos <sup>b</sup>

<sup>a</sup> Department of Civil Engineering, The University of Akron, Auburn Science and Engineering Center,  
244 Sumner Street, Akron, OH 44325-3905, USA

<sup>b</sup> Department of Civil and Environmental Engineering, West Virginia University, Morgantown, WV 26506-6103, USA

Received 25 March 2003; received in revised form 25 March 2003

The following two changes are made to “Analysis of tapered ENF specimen and characterization of bonded interface fracture under Mode-II loading,” International Journal of Solids and Structures, 40(8), 1865–1884 (2003).

- (1) On page 1868, after Eq. (9): change “ $x = 0$ ” to “ $x = a$ ”. It should read “where  $c_1$  and  $c_2$  are the rotation and deflection of the beam at  $x = a$ ”.
- (2) On page 1883, Table 2: some data given in Table 2 are not correct, and the modified table is given as:

Table 2  
Critical strain energy release rates of interface bonds

Interface	Crack propagation	$G_{IIc}$ , TBEF <sup>a</sup> N/m (lb/in)	$G_{IIc}$ , Experimental <sup>b</sup> N/m (lb/in)	$G_{Ic}$ (Qiao et al., 2000) N/m (lb/in)
Wood–wood	Crack initiation	1170 (6.68)	931 (5.32)	586.68 (3.35)
	Crack arrest	1088 (6.21)	867 (4.95)	339.75 (1.94)
Wood–FRP	Crack initiation	606 (3.46)	569 (3.25)	224.16 (1.28)
	Crack arrest	571 (3.26)	536 (3.06)	185.63 (1.06)

<sup>a</sup> Based on the  $dC/da$  values predicted by the TBEF model.

<sup>b</sup> Based on the experimental  $dC/da$  values.

☆ doi of original article 10.1016/S0020-7683(03)00031-3.

\* Corresponding author. Tel.: +1-330-972-5226; fax: +1-330-972-6020.

E-mail address: qiao@uakron.edu (P. Qiao).