

Corrigendum

Corrigendum to “Subsolidus phase relations in $\text{Na}_2\text{O}-\text{CuO}-\text{Sb}_2\text{O}_n$ system and crystal structure of new sodium copper antimonate $\text{Na}_3\text{Cu}_2\text{SbO}_6$ ” [J. Solid State Chem. 178 (2005) 1165–1170]

O.A. Smirnova^{a,b}, V.B. Nalbandyan^{b,*}, A.A. Petrenko^b, M. Avdeev^a

^aDepartment of Ceramics and Glass Engineering, CICECO, University of Aveiro, 3810-193 Aveiro, Portugal

^bChemistry Faculty, Department of General and Inorganic Chemistry, Rostov State University, Zorge 7, Rostov-on-Don 344090, Russian Federation

Received 27 January 2006; accepted 30 January 2006

In Table 2, a multiplier of 100 for the displacement parameters was inadvertently omitted. The corrected Table 2 is shown here.

Table 2

Atomic coordinates and displacement parameters for $\text{Na}_3\text{Cu}_2\text{SbO}_6$ structure

Atom	Wyckoff position	x	y	z	$U_{\text{iso}} (\text{\AA}^2)$			
Cu	4g	0	0.6667(1)	0	0.0054(3)			
Sb	2a	0	0	0	0.0028(3)			
O1	8j	0.2931(4)	0.3340(3)	0.7750(4)	0.0045(6)			
O2	4i	0.2404(7)	1/2	0.1774(8)	0.0045(6)			
						U_{11}	U_{22}	U_{33}
Na1	2d	0	1/2	1/2	0.011(1)	0.011(1)	0.010(1)	0.004(1)
Na2	4h	1/2	0.3280(3)	1/2	$= U_{11}(\text{Na1})$	$= U_{11}(\text{Na1})$	$= U_{22}(\text{Na1})$	$= U_{33}(\text{Na1})$

DOI of original article: 10.1016/j.jssc.2005.02.002

*Corresponding author.

E-mail address: vbn@rsu.ru (V.B. Nalbandyan).