

Inorganic Membranes and Membrane Reactors

Sun-Tak Hwang¹

Department of Chemical Engineering, University of Cincinnati, Cincinnati, OH 45221-0171

Abstract—The inorganic membrane reactor is a combined unit operation of chemical reactions and membrane separations. By having a membrane reactor, the downstream separation load can be reduced. Also, the yields can be increased and conversion can be improved for equilibrium limited reactions. However, many of the industrial chemical reactions take place at high temperature that the conventional polymeric membranes cannot withstand. A great deal of research has been done recently to develop ion-conducting ceramic membranes. Many of these have been successfully employed to form membrane reactors for many industrially relevant chemical reactions, such as hydrogenation, dehydrogenation, oxidation, coupled reactions, and decomposition reactions. An overview is given for the area of inorganic membrane preparations and membrane reactors. Many examples of petrochemical interests are presented, including hydrocarbon conversions and fuel cell applications.

Key words: Inorganic Membranes, Inorganic Membrane Reactions, Ceramic Membranes, Palladium Membranes, Fuel Cells

INTRODUCTION

The interest in inorganic membranes goes beyond the scientific curiosity. The long history of hydrogen purification with palladium foils, helium separation with fused quartz, and oxygen separation with silver represents the successful industrial applications of inorganic membranes. However, since the gas permeability through these metals is much lower than that through polymeric membranes, attention has largely been focused on polymer membranes for practical applications. The progress of inorganic membranes had been relatively dormant until the development of thin composite metal membranes and ion-conducting ceramic membranes. These membranes, unlike the polymeric membranes, offer virtually complete separation. Since the inorganic membranes can withstand high temperatures and hostile environments, their applications to membrane reactors for many industrial processes attracted considerable attention. The concept of a membrane reactor was first successfully proven in bioreactor applications with polymeric membranes and appropriate enzymes as catalysts. In this review paper, the recent development of inorganic membranes and their use in membrane reactor applications will be discussed with relevant references. For further details, readers are referred to other recent review papers in the field [Armor, 1998; Saracco et al., 1994, 1999; Saracco and Specchia, 1994; Drioli, 2001; Boddeker et al., 2001; Stoukides, 2000; Zaman and Chakma, 1994].

ADVANTAGES AND DISADVANTAGES

Inorganic membranes offer the following advantages:

- Ability to withstand high temperatures for a long time
- Resistance to hostile environments (organic solvents, large pH changes, detergents, steam, etc.)
- High mechanical strength (stable at high pressure and high pres-

sure drop)

- Resistance to microbial attacks
- High flux (throughput)
- Easy cleaning (steam or backflushes)
- Long life
- Easy modification to add catalytic activity

While there are so many advantages for inorganic membranes, some disadvantages are very critical and serious enough to hamper the progress of industrial application of inorganic membranes, as listed below:

- Brittleness (easy to crack)
- Difficult sealing problems at high temperature applications
- Low surface-to-volume ratio
- Few membranes with high selectivity
- Expensive capital and repair costs

METALLIC MEMBRANES

1. Palladium-Based Composite Membranes

The palladium-based membranes are the most frequently used metal membranes owing to their very high hydrogen selectivity [Nagamoto and Inoue, 1981, 1985, 1986]. They have been used for hydrogenation, dehydrogenation, dehydrogenation-oxidation and steam reforming reactions. The exclusive transport mechanism toward hydrogen is generally believed to be due to the interaction of hydrogen atoms and palladium metal. Molecular hydrogen is dissociated and chemisorbed on one side of the membrane and dissolved in the palladium matrix. The atomic hydrogen then diffuses to the other side of the membrane. There, the hydrogen atoms recombine and desorb as molecular hydrogen. Therefore the driving force for the permeation becomes the difference in the square root of pressures at both sides of the membrane [Hwang and Kammermeyer, 1975; Shu et al., 1991]. Only hydrogen gas can go through, while no other gas molecules are allowed to transfer through the dense palladium membrane.

¹To whom correspondence should be addressed.

E-mail: shwang@alpha.che.uc.edu

There are several problems with palladium membranes. The first is hydrogen embrittlement [Armor, 1992]. This is caused by the large distortion in lattice structure due to the alpha-beta phase transformation. When the cyclic stress is present by adsorption and desorption of hydrogen, the palladium becomes very brittle.

Another big problem with palladium membrane is its sensitivity to poisoning in the presence of CO , H_2S , SO_2 , sulfur, arsenic, chlorine, mercury, zinc, and unsaturated hydrocarbons, etc. The mechanical instability problem (hydrogen embrittlement) may be somewhat eased by making alloys with other metals such as Ag, Ru, Rh, or other rare earths [Armor, 1992]. Some alloy elements from the VI, VII, and VIII groups in the periodic table are also known to increase palladium membrane permeability [Gryaznov et al., 1987; Gryaznov, 1992].

In practice, it is a difficult challenge to select the best alloying metals and their amounts in order to achieve the high permeability, catalytic activity, and resistance to poisoning and hydrogen embrittlement.

Another major hurdle with palladium alloy membranes is the reduction of membrane thickness. The flux will increase as the membrane gets thinner, therefore the costs will decrease because of the reduced operating and material costs. Many methods have been developed to prepare a thin palladium-coated composite membrane, some of which will be briefly outlined and reviewed below.

1-1. Electroless Plating

One can produce thin palladium-based composite membranes by dipping porous support materials such as ceramic, metal, or glass in a bath of palladium salt complex solution. For uniform coating, the support material must be cleaned, sensitized, and activated before dipping. Palladium deposition takes place on the support surface by autocatalyzed reduction reaction of metastable metallic complexes. Uemiya et al. [1988, 1991a, b] and Kikuchi et al. [1989a, b] used porous glass tubes while Govind and Atnoor [1991] employed porous silver as supports. Shu et al. [1993] were successful in depositing palladium and silver on porous stainless steel. Also, alumina [Uemiya et al., 1990, 1991c, d, e; Matsuda et al., 1993] and stainless steel were coated with thin palladium layers by electroless plating.

1-2. Sputtering

This process removes atoms from a suitable target and deposits on the support surface in the form of a thin film by means of rapid ion bombardment from a high-energy plasma [Konno et al., 1988; Gryaznov et al., 1993; Jayaraman et al., 1995; Xomeritakis and Lin, 1997]. Thin films of binary and ternary alloys of palladium with manganese, cobalt, ruthenium, tin, and lead were deposited on polymeric, porous stainless steel and oxide supports by Gryaznov et al. [1993]. Sputter deposition on polymer membranes usually produces very fragile and defective membranes, which cannot function at high temperatures. Metallized porous ceramic membranes may allow operation at elevated temperatures if the adhesion of metal on the substrate is gas-tight.

1-3. Spray Pyrolysis

A solution of metal salts is sprayed into a heated gas stream and pyrolyzed. Li et al. [1993] produced palladium-silver alloy membrane by using spray pyrolysis of a palladium nitrate and silver nitrate solution in a hydrogen-oxygen flame. They obtained an alloy membrane with a thickness of less than $2\text{ }\mu\text{m}$, but the separation

factor between hydrogen and nitrogen gases was too low compared with those of membranes obtained by other methods.

1-4. Chemical Vapor Deposition (CVD)

The successful physical vapor deposition techniques used for the electronic industry do not offer gas-tight composite membranes. It is believed that in those methods film formation takes place on top of the support. It is difficult to control and produce uniformly thin metal films and good adhesion on the support materials. Also, they require cumbersome and time-consuming pretreatment steps. Thus, attention is growing for vapor phase processes such as reactive CVD producing good film quality and fast film growth. Yan et al. [1994], Morooka et al. [1995], Uemiya et al. [1994], and Xomeritakis and Lin [1996, 1997] used thermal decompositions of volatile metal-organic palladium precursors for fabrication of composite membranes. Dense palladium was deposited inside pores of ceramic support (α -alumina tubes) by CVD employing thermal decomposition of a metallorganic precursor (palladium acetate or palladium acetylacetone).

2. Silver Alloy Membranes

The only other metal membrane that has been studied in membrane reactors is silver alloy, which permits oxygen permeation [Anshits et al., 1989; Gryaznov et al., 1986, 1989]. Based on the poor performance, the silver alloy membranes have not been actively pursued for use in membrane reactors or separation devices.

SOLID ELECTROLYTE MEMBRANES

Although some novel solid electrolytes can selectively transfer specific elements such as F, C, N, S, etc., most of the recent studies have only focused on two types of solid electrolytes: one for oxygen-conducting and the other for hydrogen-conducting ceramics. The reasons are that these new ceramic materials offer very high permeabilities toward oxygen and hydrogen, respectively; with infinite separation factors. Thus, they are very suitable not only for gas separations but also for membrane reactors involving oxygenation, oxidative coupling of methane, hydrogenation, dehydrogenation, etc. If the as shown in Figs. 1 and 2. The impurities or dopants incorporated into these oxides during preparation may cause oxygen vacancies. Through these vacancies the oxygen anions are passed from one site to the next. Also, electrons may be transmitted by either n-electron conductivity is low, that particular ceramic material can be used for fuel cell application.




Fig. 1. Fluorite type structure.




Fig. 2. Perovskite-type structure.




Fig. 3. Four ways of making oxygen ion-conducting ceramic membranes.

1. Oxygen Ion-Electron Conducting Ceramics

The most widely studied materials as ion-conducting membranes are fluorite- and perovskite-type ceramics. Metal oxides in the form of fluorite and perovskite have crystalline structures with a simple cubic lattice type conduction or p-type conduction.

Four different ways of making oxygen ion-conducting membranes are illustrated in Fig. 3. The top left picture is the dual phase membrane. The top right picture shows the oxygen permeation by a mixed oxygen ion-electron conducting membrane. In both of these processes, the driving force for overall oxygen permeation is the difference of oxygen partial pressure raised some power across the membrane. The bottom left picture shows how an air-hydrogen fuel cell works with the oxide membrane sandwiched by two electrodes. It generates electric power as oxygen permeates to react with hydrogen. The bottom right picture depicts an oxygen pump. This arrangement requires external power to drive the oxygen from one side to the other.

1-1. Fluorite Type

The two most commonly studied oxygen ion-electron conduct-

ing ceramics of fluorite-type are based on yttria stabilized zirconia (YSZ) as shown by Dou et al. [1985] and Kim and Lin [1998], and δ -phase Bi_2O_3 as reported by Jurado et al. [1988] and Bouwmeester et al. [1992]. In spite of their high oxygen ion conductivity, their oxygen flux through dense membranes are still limited very low level due to the low electronic conductivity. Doping multivalent metal oxides can increase the electronic conductivity [Arashi and Naito, 1992; Nigara et al., 1995; Han and Worrell, 1995; Han et al., 1997]. A similar result was obtained by preparing dual-phase membrane [Chen et al., 1996; Kim and Lin, 2000]. Ceria has the highest oxygen-ion mobility, a large solubility for acceptor doping, a variable-valent cation, and an extensive range of nonstoichiometry. Pure CeO_2 exhibits n-type electronic conduction. Tuller [1992] showed that doping with acceptor Y_2O_3 increases the ionic conductivity at the expense of electronic conductivity. Thus, the doped ceria ceramics are good candidates for solid electrolytes for a fuel cell.

1-2. Perovskite Type

The oxygen flux attained by various fluorite type ceria membranes is still too low to be applicable for membrane reactors. Teraoka et al. [1985, 1988] first demonstrated that $\text{La}_{1-x}\text{Sr}_x\text{Co}_{1-x}\text{Fe}_x\text{O}_{3-\delta}$ based perovskite-type ceramic membranes possess considerably high oxygen fluxes at high temperatures suitable for membrane reactors. Since then there have been many reports [Kruidhof et al., 1993; Qiu et al., 1995; Stevenson et al., 1996; Tsai et al., 1998; Xu and Thomson, 1998; Zhang et al., 1999] on the same subject, but the oxygen flux hardly improved. Oxygen conducting perovskite-type membranes were used in membrane reactor for oxidative coupling of methane by Hamakawa et al. [1993], Teymouri et al. [1993], Zeng et al. [1998], and Zeng and Lin [2000].

Qi et al. [2000] summarized four different methods of preparing $\text{La}_{1-x}\text{Sr}_{12}\text{Co}_{10}\text{Fe}_{6-x}\text{O}_{3-\delta}$ powders to produce dense ceramic membranes: citrate method, solid-state method, spray-pyrolysis method, and co-precipitation method. Each method offered different compositions that changed the oxygen permeability and electronic conductivity. In general, perovskite-type membranes show higher oxygen flux, electronic conductivity, and mechanical strength than fluorite-type materials, because perovskite is capable of achieving high degree of doping while retaining good phase stability.

2. Proton-Electron Conducting Ceramics

Certain perovskite-type materials can transport hydrogen readily since they can host large amount of protons in their lattice structure.

2-1. Perovskite Type

Proton-conducting perovskite-type membranes were used in hydrogen separation from gas mixtures by Hamakawa et al. [1994] and Iwahara et al. [1986], and in hydrogen sensors by Yajima et al. [1995]. Qi and Lin [2000] reported two methods of preparing perovskite-type materials, the citrate method and the oxalic acid method.

2-2. Terbium Doped Strontium Cerate

Terbium doped strontium cerate (SrCeO_3), SCTb, showed high electrical and proton conductivity in hydrogen atmosphere. Also, Kreuer [1997], Iwahara et al. [1986], and Iwahara et al. [1990] reported that $\text{SrCe}_{0.95}\text{Yb}_{0.05}\text{O}_{3-\delta}$ (SCYb) and $\text{BaCe}_{0.9}\text{Nd}_{0.1}\text{O}_{3-\delta}$ (BCNd) have very high proton conductivity at 900°C in pure hydrogen. Since both SCYb and BCNd possess significant amount of oxygen vacancy, they exhibit high oxygen ion conductivity as much as proton

conductivity. It is interesting to note that SCYb is essentially a non-oxygen ionic conductor. The electronic conductivity of SCTb in oxygen is several orders of magnitude smaller than that of SCYb, allowing it to be an ideal proton-conducting electrolyte for fuel cell and sensor applications [Qi and Lin, 1999].

POROUS MEMBRANES

The majority of inorganic membranes that are being employed by industry now are porous metals and ceramic membranes such as alumina, silica, titania, zirconia, glass, etc. Since these materials have been known and used for a long time, there is abundant literature. In this review paper, hence, mainly the new types of ceramic membranes will be discussed.

TRANSPORT MECHANISMS

Since the transport mechanisms in conventional porous inorganic membranes are well described by viscous flow, Knudsen flow, surface diffusion, capillary condensate flow, and molecular sieving flow [Hwang and Kammermeyer, 1975], it will be omitted here. The hydrogen flux J_{H_2} through a thick palladium membrane is known to obey:

$$J_{H_2} = Q_{H_2} \left(\frac{(P_{H_2}^u)^{1/2} - (P_{H_2}^d)^{1/2}}{l} \right) \quad (1)$$

where l is membrane thickness and Q_{H_2} is hydrogen permeability, which can be expressed as a product of diffusivity and solubility. The upstream and downstream partial pressures of hydrogen are $P_{H_2}^u$ and $P_{H_2}^d$, respectively. The square root dependency of flux on

gas pressure is due to surface dissociation of hydrogen molecule. However, the hydrogen permeation rate is in general determined by the surface exchange rates and the proton ion diffusion rate through the bulk membrane [Hamakawa et al., 1994; Qi and Lin, 1999, 2000].

The oxygen permeation rate is in general determined by the surface exchange rates and the oxygen ion diffusion rate through the bulk membrane [Teraoka et al., 1985, 1988; Kruidhof et al., 1993; Qiu et al., 1995; Stevenson et al., 1996]. For a thick membrane, the surface exchange step may be ignored and the bulk diffusion becomes the controlling rate. In this case, the oxygen permeation flux through oxygen ion conducting ceramic membranes is expressed as:

$$J_{O_2} = Q_{O_2} \left(\frac{(P_{O_2}^u)^{-n} - (P_{O_2}^d)^{-n}}{l} \right) \quad (2)$$

where n is the power coefficient, which depends on the creation speed of oxygen vacancy with the change of ambient oxygen partial pressure, l is membrane thickness, and Q_{O_2} is oxygen permeability, which can be expressed as a product of diffusivity and solubility. The upstream and downstream partial pressures of oxygen are $P_{O_2}^u$ and $P_{O_2}^d$, respectively. As the membrane thickness decreases, the oxygen permeation rate will depend not only on the bulk diffusion but also on the surface kinetics.

MEMBRANE REACTORS (CATALYTIC MEMBRANE REACTORS)

Membrane reactors are chemical reactors in which membranes are used to combine two unit operations, namely reaction and separation, into a single one. When Michaels [1968] originally suggested

Table 1. Types of chemical reactions

Equilibrium shift reactions:	
Hydrogenation, Dehydrogenation, Oxidation, Coupling Reactions, and Decomposition.	
$H_2S \rightleftharpoons H_2 + S$,	$CO + H_2O \rightleftharpoons CO_2 + H_2$,
$CH_4 + H_2O \rightleftharpoons CO; CO_2; H_2; \dots$,	$CH_3OH \rightleftharpoons CH_2O + H_2$,
$CH_3OH + Toluene \rightleftharpoons$ Ethylbenzene; Propene,	
$C_2H_6 \rightleftharpoons C_2H_4 + H_2$,	Propane \rightleftharpoons Propene,
$Propene + H_2O \rightleftharpoons$ Acetone,	Butane \rightleftharpoons Butene,
$Isobutane \rightleftharpoons$ Isobutene,	$2-Butene + H_2 \rightleftharpoons$ Butane,
$Hexane \rightleftharpoons$ Ethane: Propene	$Cyclohexane \rightleftharpoons$ Benzene,
Hydrogenation (gas phase):	
$CO + H_2 \rightleftharpoons$ Hydrocarbons,	$CO_2 + H_2 \rightleftharpoons$ Hydrocarbons,
$C_2H_2 + H_2 \rightleftharpoons C_2H_4$,	$C_2H_4 + H_2 \rightleftharpoons C_3H_6$,
$1-Butene \rightleftharpoons$ Butane,	$Cyclohexene \rightleftharpoons$ Cyclohexane,
$Benzene \rightleftharpoons$ Cyclohexane,	$Nitrobenzene \rightleftharpoons$ Aniline,
$Furfural \rightleftharpoons$ Furfural Alcohol.	
Hydrogenation (liquid phase):	
$Acetone + H_2 \rightleftharpoons$ 2-Methylpentanone-4,	
$Acetone + H_2 \rightleftharpoons$ 2-Methylpenten-2-one-4,	
$2-Butyne-1,4-diol + H_2 \rightleftharpoons cis-trans-Butenediol$,	
$cis-trans-butene-1,4-diol + H_2 \rightleftharpoons cis\ trans-Butanediol$,	
$Quinone + Acetic\ Anhydride \rightleftharpoons$ Vitamin K,	
$Dehydrolinalool + H_2 \rightleftharpoons$ Linalool.	

Table 1. Continued

Dehydrogenation (gas phase):	
$\text{H}_2\text{S} \rightleftharpoons \text{H}_2 + \text{S}$,	$\text{CO} + \text{H}_2\text{O} \rightleftharpoons \text{CO}_2 + \text{H}_2$,
$\text{CH}_4 + \text{H}_2\text{O} \rightleftharpoons \text{CO} + 3\text{H}_2$,	$\text{CH}_3\text{OH} + \text{H}_2\text{O} \rightleftharpoons 3\text{H}_2 + \text{CO}_2$,
Propane \rightleftharpoons Aromatics,	Isopropanol \rightleftharpoons Acetone,
Butene \rightleftharpoons Butadiene,	n-Hexane \rightleftharpoons Benzene,
n-Hexane \rightleftharpoons Cyclic Hydrocarbons.	
Dehydrogenation (liquid phase):	
$\text{CH}_3\text{OH} \rightleftharpoons \text{HCOOCH}_3$;	$\text{CH}_3\text{OH} \rightleftharpoons \text{CH}_3\text{OCH}_2\text{OH}$; H_2 ; ...
(Nafion) $\text{CH}_3(\text{OCH}_3)_2$;	(H_3PO_4 ; Heteropolyacids, Pt)
Methylformate;	
Methylal; H_2 ; H_2O	
Oxydation:	
$\text{CH}_4 + \text{O}_2 \rightleftharpoons \text{C}_2 + \dots$,	$\text{C}_2\text{H}_4 + \text{O}_2 \rightleftharpoons$ Ethylene Oxide,
Propylene + $\text{O}_2 \rightleftharpoons$ Propylene Oxide,	Butene + $\text{O}_2 \rightleftharpoons$ Butadiene,
Propylene + $\text{O}_2 \rightleftharpoons$ Hexadiene; Benzene + ...,	
Benzyllic and Allylic Compounds + $\text{O}_2 \rightleftharpoons \dots$,	
$\text{SO}_2 + \frac{1}{2}\text{O}_2 \rightleftharpoons \text{SO}_3$,	$\text{CO} + \frac{1}{2}\text{O}_2 \rightleftharpoons \text{CO}_2$,
$\text{CH}_4 + \text{O}_2 \rightleftharpoons \text{C}_2 + \dots$,	$\text{CH}_4 + \text{O}_2 \rightleftharpoons \text{CO}_2 + \text{H}_2\text{O}$,
$\text{CH}_3\text{OH} + \text{O}_2 \rightleftharpoons \text{H}_2\text{CO}$; CO ; CH_3 ; ...,	$\text{C}_2\text{H}_4 + \frac{1}{2}\text{O}_2 \rightleftharpoons \text{C}_2\text{H}_4\text{O}$; CO_2 ; O_2 ,
Ethylbenzene + $\text{O}_2 \rightleftharpoons$ Styrene; CO_2 ; ...,	$\text{C}_3\text{H}_6 + \text{O}_2 \rightleftharpoons \text{C}_3\text{H}_6\text{O}$; CO_2 ; H_2O .
Coupling of reactions:	
$\text{C}_2\text{H}_6 \rightleftharpoons \text{C}_2\text{H}_4 + \text{H}_2$ and $\text{H}_2 + \frac{1}{2}\text{O}_2 \rightleftharpoons \text{H}_2\text{O}$,	
$2\text{CH}_4 \rightleftharpoons \text{C}_2\text{H}_6 + \text{H}_2$ and $\text{H}_2 + \frac{1}{2}\text{O}_2 \rightleftharpoons \text{H}_2\text{O}$,	
Butane \rightleftharpoons Butenes and $\text{H}_2 + \frac{1}{2}\text{O}_2 \rightleftharpoons \text{H}_2\text{O}$,	
Cyclohexanol \rightleftharpoons Cyclohexanone and Phenol \rightleftharpoons Cyclohexanol,	
2-Butene \rightleftharpoons Butadiene and Toluene \rightleftharpoons Benzene,	
Cyclohexane \rightleftharpoons Benzene and o-Xylene \rightleftharpoons Benzene; Methane,	
Cyclohexene \rightleftharpoons Benzene and Cyclohexene \rightleftharpoons Cyclohexane,	
Cyclohexane \rightleftharpoons Benzene and Toluene \rightleftharpoons Benzene; Methane.	
Liquid phase homogeneous and heterogeneous catalysis on porous membranes:	
$\text{NO} + \text{H}_2\text{S} + \text{O}_2 \rightleftharpoons 2\text{HNO}_3 + \text{S}$,	$\text{C}_2\text{H}_4 + \text{O}_2 \rightleftharpoons \text{CH}_3\text{CHO}$,
$\text{C}_3\text{H}_8 + \text{H}_2 + \text{CO} \rightleftharpoons \text{CH}_3\text{CH}_2\text{CHO}$,	$\text{CH}_4, \text{C}_2\text{H}_6, \text{C}_3\text{H}_8 + \text{H}_2\text{O}_2 \rightleftharpoons \dots$,
Methyl- <i>t</i> -butylether \rightleftharpoons Iso-butene Methanol,	Nitrobenzoic Acid + $\text{H}_2 \rightleftharpoons \dots$,
Oleic Acid + Ethanol \rightleftharpoons Ester + H_2O .	
More reactions:	
Dehydrogenation of Ethane; Propane; n-Butane; Cyclohexane; Ethylbenzene; Methanol,	
Reduction of Nitrogen Oxide with Ammonia,	
Steam Reforming of Methane.	
Fuel cell applications:	
Membranes: Oxygen Conductors (Low Electrical Conductivity).	
Fuels: H_2 , CO, CH_4 , CH_3OH , $\text{C}_2\text{H}_5\text{OH}$, and NH_3 ,	
Temperature Range: 627-1,094 °C.	

this to achieve greater conversion by shifting the equilibrium limited reactions through selective elimination of one of the products, only polymeric membranes were available for separations. A couple of drawbacks with polymer membranes have retarded wide usage of membrane reactors for industrial applications. Polymers exhibit only partial selectivity and cannot withstand high temperatures. Since then various inorganic membranes have been developed to overcome these shortcomings as discussed above. At present, only two

kinds of inorganic membranes attract most of the attention; one for hydrogen and the other for oxygen. For hydrogen separation membranes, metallic palladium and proton-permeating ceramics hold promise. For oxygen separation membranes, only oxygen ion-conducting ceramics have been considered as practical candidates for membrane reactor materials.

There are several different ways to construct a membrane reactor. A vessel of an inert membrane with permselectivity can be packed

with catalyst or the catalyst may be fluidized. Another method is to employ a catalytic membrane, which may be made of either the catalyst itself or an inert membrane impregnated with catalyst. This type is called a catalytic membrane reactor. The catalytic membrane reactor can be packed with catalysts or contain fluidized catalyst. Both tubular and flat disk membranes have been used for membrane reactors in laboratory in parallel or cross flow mode. For industrial reactors, the shell-and-tube type may be more feasible.

1. Types of Chemical Reactions

Table 1 lists some examples of typical chemical reactions that have been studied using various inorganic membranes in membrane reactor arrangement. Some potential candidates for industrial membrane reactor applications include: water-gas shift reaction, methane steam reforming, dehydrogenation of ethane, propane, butane, cyclohexane, ethylbenzene, etc. By using a membrane reactor, the selectivity towards desired products can be enhanced for many oxidative reactions. Also, numerous coupling reactions can take advantage of membrane reactor configuration. The role of membrane reactors is not limited to practical applications. Catalysis of many reactions and some oxidation reactions can be better understood, thus resulting in improved reaction mechanisms for those reactions.

2. Equilibrium Shift Using Membrane Reactors

As illustrated in Table 2, many of the equilibrium-limited reac-

tions were the favorite subjects of earlier studies applied to membrane reactors. Many of these reactions attracted a great deal of interest from the petrochemical industry [Armor, 1998]. In a membrane reactor, one of the products can be eliminated continuously, thus yielding a shift of equilibrium in a thermodynamically limited reaction. Even a small percentage of equilibrium conversion can result in a huge economic gain for industrial processes. If hydrogen is involved as one of the species in the equilibrium-limited reaction, the proton-conducting membrane can be effectively employed as the membrane that can supply or eliminate hydrogen to and from the reaction zone.

3. Palladium-Based Membrane Reactors

The palladium membranes are highly selective to hydrogen, and therefore have been widely used for hydrogenation, dehydrogenation, and steam reforming reactions. Decomposition of hydrogen sulfide was tested by both palladium membrane [Edlund and Pledger, 1993] and proton-conducting ceramic membrane [Peterson and Winnick, 1996]. Water-gas shift reaction and methane steam reforming were studied by using palladium-based membranes. Many dehydrogenations of hydrocarbons were also the subject of research by the palladium-based membranes as shown in Table 3, in which examples of other reactions are also given. The palladium membranes have several drawbacks that include hydrogen embrittlement, cor-

Table 2. Equilibrium shift using membrane reactors

Type of chemical reactions	References
$\text{CO} + \text{H}_2\text{O} \rightleftharpoons \text{CO}_2 + \text{H}_2$	Champagnie et al., 1992; Edlund et al., 1992; Kikuchi et al., 1989a; Seok and Hwang, 1990; Uemiy et al., 1991b.
$\text{CH}_4 + \text{H}_2\text{O} \rightleftharpoons \text{CO} + \text{CO}_2 + \text{H}_2 + \dots$	Adris et al., 1991; Guy, 1992; Oertel et al., 1987; Tsotsis et al., 1992, 1993; Uemiy et al., 1991a; Vayenas et al., 1992.
$\text{CH}_3\text{OH} \rightleftharpoons \text{CH}_2\text{O} + \text{H}_2$	Song and Hwang, 1991.
$\text{C}_2\text{H}_6 \rightleftharpoons \text{C}_2\text{H}_4 + \text{H}_2$	Bitter, 1988; Guy, 1992; Champagnie et al., 1992; Chan and Brownstein, 1991; Tsotsis et al., 1993; Ziaka et al., 1993.
$\text{C}_3\text{H}_8 \rightleftharpoons \text{C}_3\text{H}_6 + \text{H}_2$	Bitter, 1988; Roth, 1988; Tsotsis et al., 1993; Ziaka et al., 1993.
$\text{C}_5\text{H}_12 \rightleftharpoons \text{C}_2\text{H}_4; \text{C}_4\text{H}_8$	Seok and Hwang, 1990.
$\text{C}_4\text{H}_{10} \rightleftharpoons \text{C}_4\text{H}_8$	Zaspalis et al., 1991.
Isobutane \rightleftharpoons Isobutene	Ioannides and Gavalas, 1993.
Cyclohexane \rightarrow Dehydrogenation	Guy, 1992; Itoh, 1987; Okubo et al., 1991.
Ethyl Benzene \rightarrow Dehydrogenation	Michaels and Vayenas, 1984; Moser et al., 1992; Gallaher et al., 1993; Tiscareno-Lechuga et al., 1993.

Table 3. Palladium-based membrane reactors

Type of chemical reactions	References
$\text{H}_2\text{S} \rightleftharpoons \text{H}_2 + \text{S}$	Edlund and Pledger, 1993; Peterson and Winnick, 1996.
$\text{CO} + \text{H}_2\text{O} \rightleftharpoons \text{CO}_2 + \text{H}_2$	Kikuchi et al., 1989a; Uemiy et al., 1991b.
$\text{CH}_4 + \text{H}_2\text{O} \rightleftharpoons \text{CO} + \text{CO}_2 + \text{H}_2 + \dots$	Uemiy et al., 1991a.
Propane \rightarrow Aromatics	Uemiy et al., 1990; Uemiy et al., 1991a.
Isobutane \rightarrow Isobutene	Matsuda et al., 1993.
Isobutene Dehydrogenation	Raich and Foley, 1995.
1,3-Pentadien \rightarrow Cyclopentane; Cyclopentene	Gryaznov et al., 1993.
$\text{CO} + \text{H}_2\text{O} \rightleftharpoons$ Hydrocarbons	Gryaznov et al., 1993.
Paraffin, Olefin, Cyclohexane, Toluene Dehydrogenation	Armor et al., 1993; Farris and Armor, 1993; Raich and Foley, 1995; Gryaznov et al., 2001.
Ethanol \rightarrow Acetaldehyde	Raich and Foley, 1998.

Table 4. Oxygen-conducting ceramic membrane reactors

Type of chemical reactions	References
$\text{H}_2\text{S} \rightarrow \text{H}_2 + \text{S}$	Alqahtany et al., 1992.
$\text{CH}_4 + \text{O}_2 \rightarrow \text{C}_2 + \dots$	Eng and Stoukides, 1991a, b; Chiang et al., 1993; Eng et al., 1995; Jin et al., 2000; Lin and Zeng, 1996, 1997; Zeng et al., 1998; Zeng and Lin, 2000, 2001.
$\text{CH}_4 + \text{H}_2\text{O} \rightarrow \text{CO}; \text{CO}_2; \text{H}_2; \dots$	Alqahtany et al., 1993a, b.
$\text{CH}_4 + \text{O}_2 \rightarrow \text{H}_2\text{CO}$	Bafas et al., 2001.
$\text{CH}_4 + \text{O}_2 \rightarrow \text{H}_2; \text{CO}$	Hibino et al., 1995.
$\text{CH}_4 + \text{O}_2 \rightarrow \text{C}_2\text{H}_4; \text{C}_2 + \dots$	Jiang et al., 1994; Hibino et al., 1996.
$\text{C}_2\text{H}_6 + \text{O}_2 \rightarrow \text{CO}_2; \text{H}_2\text{O}$	Kaloyannis and Vayenas, 1997.
$\text{C}_2\text{H}_4 + \text{O}_2 \rightarrow \text{CO}_2; \text{H}_2\text{O}$	Petrolekas et al., 1998; Beatrice et al., 2000.
$\text{C}_3\text{H}_8 + \text{O}_2 \rightarrow \text{CO}_2; \text{H}_2\text{O}$	Beatrice et al., 2000.
$\text{CH}_3\text{OH} + \text{O}_2 \rightarrow \text{H}_2\text{CO}; \text{CO}_2$	Cavalca et al., 1993.
$\text{NO} + \text{C}_3\text{H}_8 + \text{O}_2 \rightarrow \text{N}_2; \text{CO}_2; \text{H}_2\text{O}; \dots$	Pliangos et al., 2000.
$\text{CO}_2 \rightarrow \text{O}_2; \text{C}; \text{CO}$	Itoh et al., 1993.
$\text{NO}_x \rightarrow \text{N}_2; \text{O}_2$	Cicero and Jarr, 1990.
$\text{SO}_x \rightarrow \text{S}; \text{O}_2$	Cicero and Jarr, 1990.
$\text{H}_2\text{O} \rightarrow \text{H}_2; \text{O}_2$	Nigara et al., 1997

Table 5. Proton-conducting ceramic membrane reactors

Type of chemical reactions	References
$\text{H}_2\text{O} \rightarrow \text{H}_2 + \frac{1}{2}\text{O}_2$	Iwahara et al., 2000.
$\text{NO} + \text{H}_2 \rightarrow \text{N}_2; \text{N}_2\text{O}$ (low current density); NH_3 (high current density)	Kobayashi et al., 1996, 2000a, b, c.
$\text{N}_2 + 3 \text{H}_2 \rightarrow 2 \text{NH}_3$	Marnellos et al., 2000; Panagos et al., 1996; Yiokari et al., 2000.
CH ₃ OH synthesis	Panagos et al., 1996.
$\text{CH}_4 \rightarrow \text{C}_2\text{H}_6; \text{C}_2\text{H}_4$	Chiang et al., 1992.
$\text{CH}_4 + \text{O}_2 \rightarrow \text{C}_2 + \dots$	Langguth et al., 1997a, b.
$\text{H}_2\text{S} + \text{O}_2 \rightarrow \text{SO}_2; \text{H}_2$	Peterson and Winnick, 1996.

rosion by sulfur compounds, and high cost. Composite palladium membranes have recently been synthesized and tested using many different techniques [Ziegler et al., 2001; Goto et al., 2000; Nam et al., 1999; Jun and Lee, 1999, 2000; Souleimanova et al., 2000; Li et al., 2000; Yeung et al., 1999; Cheng and Yeung, 1999].

4. Oxygen Conducting Ceramic Membrane Reactors

As mentioned earlier, membrane reactors for oxygenation reactions can be constructed by using oxygen ion-conducting ceramic membranes. Table 4 lists some of the popular oxygenation reactions reported in the literature that have been carried out in various dense ceramic membrane reactors. Cicero and Jarr [1990] reported the U.S. Department of Energy's demonstration and feasibility study of using high-temperature ceramic membranes to remove sulfur and nitrogen contaminants found in gas streams of coal-based power generation systems. Eng, Stoukides, and their coworkers published many papers on ceramic membrane reactors, as shown in the references. Their studies on the oxidation of methane and methane steam reforming are especially noteworthy and very relevant in applications to fuel cells and sensors. Itoh et al. [1993] applied an yttria stabilized zirconia (YSZ) membrane reactor system to enhance the direct thermal decomposition of carbon dioxide at high temperature. Nigara et al. [1997] split water to generate oxygen and separated it through a high temperature oxygen permeation membrane: calucia-stabilized zirconia doped with cerium oxide. Bafas et al.

[2001] studied the partial oxidation of methane to formaldehyde in a continuous gas recycle membrane reactor/sePARATOR. They achieved 56% selectivity with 89% methane conversion.

5. Proton-Conducting Ceramic Membrane Reactors

The proton-conducting ceramic membrane reactors have been investigated for many industrially attractive chemical reactions. Table 5 lists some examples: hydrogen generation by water splitting, hydrogenation of NO, ammonia synthesis, methanol synthesis, hydrogenation and dehydrogenation of alkanes and alkenes, dimerization of methane, and oxidation of hydrogen sulfide.

6. Fuel Cell Applications

The recent flurry of activities in fuel cell research and the advent of inorganic membranes created a perfect environment conducive to developing efficient fuel cells. All kinds of hydrocarbons as well as hydrogen were studied as the fuel and some examples are shown in Table 6. Both oxygen ion- and proton-conducting ceramic membranes have been employed in fuel cell research. The yttria stabilized zirconia (YSZ) membranes received considerable attention among many researchers for carrying out oxidation reactions.

7. Porous Membrane Reactors

Porous inorganic membranes were among the first inorganic materials that were made into reactors and tested. In the early days, no ion-conducting ceramic membranes were available. These included porous Vycor glass, which is an intermediate product of Vycor brand

Table 6. Fuel cell applications

Chemical reactions	Membranes	References
$H_2 + O_2 \rightarrow H_2O$	Zirconia Cermet; Ceria-based	Bieberle et al., 2001.
$CH_4 + O_2 \rightarrow CO; H_2; \dots$	YSZ; BaCeY	Alqahtany et al., 1993a; Asano et al., 1995.
$CH_4 + H_2O \rightarrow CO; H_2; \dots$	YSZ	Alqahtany et al., 1993b.
$CH_4 + NH_3 + O_2 \rightarrow HCN; \dots$	YSZ	McKenna et al., 1993.
Oxidation of n-Hexane; Benzene; Toluene	YSZ	Yamanaka and Otsuka, 1993a, b.
Oxidation of Alkanes; Alkenes; Benzene	YSZ	Otsuka and Yamanaka, 1998.
Oxidation of Toluene; n-Decane; Synthetic Diesel Fuel	YSZ	Kim et al., 2001.
Oxidation of CH_3OH	YSZ	Jiang and Virkar, 2001.
Oxidation of CH_3OH	Zirconium sulfoarylphosphonate	Alberti et al., 2000.
Oxidation of $C_2H_5OH + H_2O$	YSZ	Jiang and Virkar, 2001.
$C_4H_8 + O_2 \rightarrow CO; H_2; CH_4; \dots$	SmSrCo	Hibino et al., 2001.
Toluene + $O_2 \rightarrow$ Cresol	YSZ	Otsuka et al., 1992.
$H_2S + O_2 \rightarrow SO_2; H_2$	Lithium sulfate	Peterson and Winnick, 1996.

Table 7. Porous membrane reactors

Chemical reactions	Membranes	References
$CO + H_2O \rightarrow CO_2 + H_2$	Porous Vycor Glass	Seok and Hwang, 1990.
$CH_4 + H_2O \rightarrow CO; CO_2; H_2; \dots$	Alumina	Tsotsis et al., 1992, 1993.
$CH_4 + O_2 \rightarrow CO_2 + H_2O$	Pt/gamma-Alumina	Neomagus et al., 2000.
$CH_3OH \rightarrow CH_2O + H_2$	Porous Vycor Glass	Song and Hwang, 1991.
$C_2H_6 \rightarrow C_2H_4 + H_2$	Pt/Alumina	Champagnie et al., 1992; Tsotsis et al., 1993.
$C_3H_8 \rightarrow C_3H_6 + H_2$	Alumina	Bitter, 1988; Tsotsis et al., 1993; Ziaka et al., 1993.
$C_3H_8 \rightarrow C_2H_4; C_4H_8$	Porous Vycor Glass	Seok and Hwang, 1990.
$C_4H_{10} \rightarrow C_4H_8$	Alumina; Pt-SiO ₂	Zaspalis et al., 1991.
Isobutane \rightarrow Isobutene	Dense SiO ₂ on Vycor	Ioannides and Gavalas, 1993.
Oxidation of H_2S	Sintered Stainless Steel	Neomagus et al., 1998.
Hydrogenation of nitrate in water	Pd/Alumina; Tin/Alumina	Daub et al., 2001.
Reduction of aqueous nitrate	Pd-Cu/Alumina	Hinitch et al., 2000.
Cinnamaldehyde hydrogenation	Cu-Pt/gamma-Alumina	Pan et al., 2000.
Dehydrogenation of ethylbenzene to styrene	Fluidized Bed in Metal Reactor	Abdalla and Elnashaie, 1995.
Dehydrogenation of ethylbenzene to styrene	Pd/Porous Stainless Steel	She et al., 2001.

glass by Corning Glass, porous alumina (both alpha and gamma), porous stainless steel, and their modified or composite membranes. Although membrane selectivity was generally poor, permeation flux was adequate enough to test the very concept of membrane reactor for many of the industrial chemical reactions as shown in Table 7.

8. Other Applications (Sensors and Separation Devices)

Besides the industrial membrane reactors, many of the membrane reactor concepts (cited references in this review) can be utilized in producing oxygen and hydrogen gases as well as manufacturing chemical sensors, but they will not be discussed here since it is beyond the scope of the present review.

CONCLUSIONS

The concept of the membrane reactor is a novel idea. By combining the chemical reaction with the separation process in a single unit operation, many advantages over the conventional reactor/separators can be realized. At the same time, there are still many obstacles before this new device can become fully operational in industry. Most of the research published so far deals with laboratory scale

experiments. The potential applications involve high-temperature industrial reactions, separations of oxygen and hydrogen gases, fuel cells, and sensors. The latest developments of ion-conducting ceramic membranes raise much hope of future success. However, more efforts should be made to address sealing problems, high cost, low permeability, membrane defects, stability of membranes, and long-term performance data.

REFERENCES

- Abdalla, B. K. and Elnashaie, S. S. E. H., "Fluidized-Bed Reactors Without and With Selective Membranes for the Catalytic Dehydrogenation of Ethylbenzene to Styrene," *J. Membr. Sci.*, **101**(1-2), 31 (1995).
- Adris, A. M., Elnashaie, S. S. E. H. and Hughes, R., "A Fluidized Bed Methane," *Can. J. Chem. Eng.*, **69**, 1061 (1991).
- Alberti, G., Casciola, M. and Palombari, R., "Inorgano-Organic Proton Conducting Membranes for Fuel Cells and Sensors at Medium Temperatures," *J. Membr. Sci.*, **172**(1-2), 233 (2000).
- Alqahtany, H., Chiang, P. H., Eng, D., Stoukides, M. and Robbat, A., "Electrocatalytic Decomposition of Hydrogen-Sulfide," *Catal. Lett.*,

13(3), 289 (1992).

Alqahtany, H., Eng, D. and Stoukides, M., "Synthesis Gas-Production from Methane over an Iron Electrode in a Solid-Electrolyte Cell," *J. Electrochem. Soc.*, **140**(6), 1677 (1993a).

Alqahtany, H., Eng, D. and Stoukides, M., "Methane Steam Reforming over Fe Electrodes in a Solid-Electrolyte Cell," *Energ. Fuel*, **7**(4), 495 (1993b).

Anshits, A. G., Shigapov, A. N., Vereshchagin, S. N. and Shevchenko, V. N., "Oxidative Conversion of Methane into C-2 Hydrocarbons on Silver Membrane Catalysts," *Kinet. Catal.*, **30**(5), 1103 (1989).

Arashi, H. and Naito, H., "Oxygen Permeability in $ZrO_2-TiO_2-Y_2O_3$ System," *Solid State Ionics*, **53**, 431 (1992).

Armor, J. N., "Applications of Catalytic Inorganic Membrane Reactors to Refinery Products," *J. Membr. Sci.*, **147**(2), 217 (1998).

Armor, J. N., "Challenges in Membrane Catalysis," *Chem-tech*, **22**, 557 (1992).

Armor, J. N., Farris, T. S., Silveston, P. L., Hightower, J. W., Haag, W. O., Ross, J. R. H., Kaliaguine, S., Sarkany, A. and Geus, J. W., "Membrane Catalysis over Palladium and Its Alloys," *Stud. Surf. Sci. Catal.*, **75**, Part B, 1362 (1993).

Asano, K., Hibino, T. and Iwahara, H., "A Novel Solid Oxide Fuel-Cell System Using the Partial Oxidation of Methane," *J. Electrochem. Soc.*, **142**(10), 3241 (1995).

Bafas, I. C., Constantinou, I. E. and Vayenas, C. G., "Partial Oxidation of Methane to Formaldehyde with 50% Yield in a Continuous Recycle Reactor Separator (CRRS)," *Chem. Eng. J.*, **82**(1-3)(Sp. Iss. Si.), 109 (2001).

Beatrice, P., Pliangos, C., Worrell, W. L. and Vayenas, C. G., "Electrochemical Promotion of Ethylene and Propylene Oxidation on Pt Deposited on Yttria-Titania-Zirconia," *Solid State Ionics*, **136**(Sp. Iss. Si.), 833 (2000).

Bieberle, A., Meier, L. P. and Gauckler, L. J., "The Electrochemistry of Ni Pattern Anodes Used as Solid Oxide Fuel Cell Model Electrodes," *J. Electrochem. Soc.*, **148**(6), A646 (2001).

Bitter, J. G. A., "Process and Apparatus for the Dehydration of Organic Compounds," *Br. Pat. Appl.*, 2,201,159A (1988).

Boddeker, K. W., Peinemann, K.-V. and Nunes, S. P. (Guest Editors), "Membranes in Fuel Cells," *J. Membr. Sci.*, **185**(1)(Special Issue), 1 (2001).

Bouwmeester, H. J. M., Kruidhof, H., Burggraaf, A. J. and Gellings, P. J., "Oxygen Semipermeability of Erbia-Stabilized Bismuth Oxide," *Solid State Ionics*, **53**, 460 (1992).

Cavalea, C. A., Larsen, G., Vayenas, C. G. and Haller, G. L., "Electrochemical Modification of CH_3OH Oxidation Selectivity and Activity on a Pt Single-Pellet Catalytic Reactor," *J. Phys. Chem.*, **97**(23), 6115 (1993).

Champagnie, A. M., Tsotsis, T. T., Minet, R. G. and Wagner, E., "The Study of Ethane Dehydrogenation in a Catalytic Membrane Reactor," *J. Catal.*, **134**, 713 (1992).

Chan, K. K. and Brownstein, A. M., "Ceramic Membranes-Growth Prospects and Opportunities," *Ceram. Bull.*, **70**, 703 (1991).

Chen, C. S., Kruidhof, H., Bouwmeester, H. J. M., Verweij, H. and Burggraaf, A. J., "Oxygen Permeation through Oxygen Ion Oxide-Noble Metal Dual Phase Composites," *Solid State Ionics*, **86**, 569 (1996).

Cheng, Y. S. and Yeung, K. L., "Palladium-Silver Composite Membranes by Electroless Plating Technique," *J. Membr. Sci.*, **158**(1-2), 127 (1999).

Chiang, P. H., Eng, D. and Stoukides, M., "Solid Electrolyte Aided Direct Coupling of Methane," *J. Catal.*, **139**(2), 683 (1993).

Chiang, P. H., Eng, D., Alqahtany, H. and Stoukides, M., "Nonoxidative Methane Coupling with the Aid of Solid Electrolytes," *Solid State Ionics*, **53**, Part 1, 135 (1992).

Cicero, D. C. and Jarr, L. A., "Application of Ceramic Membranes in Advanced Coal-Based Power-Generation Systems," *Separ. Sci. Technol.*, **25**(13-15), 1455 (1990).

Daub, K., Wunder, V. K. and Dittmeyer, R., "CVD Preparation of Catalytic Membranes for Reduction of Nitrates in Water," *Catal. Today*, **67**(1-3), 257 (2001).

Dou, S., Mason, C. R. and Pacey, P. D., "Mechanism of Oxygen Permeation through Lime-stabilized Zirconia," *J. Electrochem. Soc.*, **132**, 1843 (1985).

Dirolli, E. (Guest Editor), "Catalytic Membrane Reactors and Membrane Operations," *J. Membr. Sci.*, **181**(1)(Special Issue: 1999 Ravello Conference), 1 (2001).

Edlund, D. J. and Pledger, W. A., "Thermolysis of Hydrogen-Sulfide in a Metal-Membrane Reactor," *J. Membr. Sci.*, **77**(2-3), 255 (1993).

Edlund, D. J., Pledger, W. A., Johnson, B. M. and Friesen, D. T., "Toward Economical and Energy Efficient Production of Hydrogen from Coal using Metal-Membrane Reactors," 5th Annu. Meet. NAMS, Lexington, KY., paper 11F (1992).

Eng, D. and Stoukides, M., "The Catalytic and Electrocatalytic Coupling of Methane over Yttria-Stabilized Zirconia," *Catal. Lett.*, **9**(1-2), 47 (1991a).

Eng, D. and Stoukides, M., "Catalytic and Electrocatalytic Methane Oxidation with Solid Oxide Membranes," *Catal. Rev.*, **33**(3-4), 375 (1991b).

Eng, D., Chiang, P. H. and Stoukides, M., "Methane Oxidative Coupling - Technical and Economic-Evaluation of a Chemical Cogenerative Fuel-Cell," *Energ. Fuel*, **9**(5), 794 (1995).

Farris, T. S. and Armor, J. N., "Liquid-Phase Catalytic-Hydrogenation Using Palladium Alloy Membranes," *Appl. Catal., A-Gen.*, **96**(1), 25 (1993).

Gallaher, G. R., Gerdes, T. E. and Liu, P. K. T., "Experimental Evaluation of Dehydrogenations Using Catalytic Membrane Processes," *Separ. Sci. Technol.*, **28**, 309 (1993).

Goto, S., Assabumrungrat, S., Tagawa, T. and Praserthdam, P., "The Effect of Direction of Hydrogen Permeation on the Rate through a Composite Palladium Membrane," *J. Membr. Sci.*, **175**(1), 19 (2000).

Govind, R. and Attoor, D., "Development of a Composite Palladium Membrane for Selective Hydrogen Separation at High Temperature," *Ind. Eng. Chem. Res.*, **30**, 591 (1991).

Gryaznov, V. M., "Platinum Metals as Components of Catalyst-Membrane Systems," *Platinum Met. Rev.*, **36**, 70 (1992).

Gryaznov, V. M., Ermilova, M. M. and Orekhova, N. V., "Membrane-Catalyst Systems for Selectivity Improvement in Dehydrogenation and Hydrogenation Reactions," *Catal. Today*, **67**(1-3), 185 (2001).

Gryaznov, V. M., Gulianova, S. G. and Serov, Y. M., "Role of Adsorbed Hydrogen and Oxygen Forms in Conversions of Oxygen-Containing Monocarbon Molecules on Membrane Catalysts," *USSR Khim.*, **58**(1), 58 (1989).

Gryaznov, V. M., Mischenko, A. P. and Sarylova, M. E., "Catalyst for Cyclization of Pentadiene-1,3 into Cyclopentene and Cyclopentane," *GB Pat. 2,187,758 A* (1987).

Gryaznov, V. M., Serebryannikova, O. S. and Serov, Y. M., "Prepara-

tion and Catalysis over Palladium Composite Membranes," *Appl. Catal., A-Gen.*, **96**, 15 (1993).

Gryaznov, V. M., Vedernikov, V. I. and Gulianova, S. G., "Participation of Oxygen, Having Diffused through a Silver Membrane Catalyst, in Heterogeneous Oxidation Processes," *Kinet. Catal.*, **27**(1), 129 (1986).

Guy, C., "Le Reacteur à Membrane: Possibilités d'application dans l'Industrie Petrolière et Petrochimique," *Rev. Inst. Fr. Pet.*, **47**, 133 (1992).

Hamakawa, S., Hibino, T. and Iwahara, H., "Electrochemical Methane Coupling Using Protonic Conductors," *J. Electrochem. Soc.*, **140**, 459 (1993).

Hamakawa, S., Hibino, T. and Iwahara, H., "Electrochemical Hydrogen Permeation in a Proton-Hole Mixed Conductor and Its Application to a Membrane Reactor," *J. Electrochem. Soc.*, **141**, 1720 (1994).

Han, P. and Worrell, W. L., "Mixed Oxygen Ion and p-type Conductivity in Yttria-Stabilized Zirconia Containing Terbia," *J. Electrochem. Soc.*, **142**(12), 4235 (1995).

Han, J., Zeng, Y. and Lin, Y. S., "Oxygen Permeation through Fluorite-Type Bismuth-Yttrium-Copper Oxide Membranes," *J. Membr. Sci.*, **132**, 235 (1997).

Hibino, T., Masegi, A. and Iwahara, H., "Electrocatalytic Oxidation of Methane by Alternating-Current Electrolysis Using Yttria-Stabilized Zirconia," *J. Electrochem. Soc.*, **142**(10), 3262 (1995).

Hibino, T., Ushiki, K., Kuwahara, Y., Masegi, A. and Iwahara, H., "Oxidative Coupling of CH_4 Using Alkali-Metal Ion Conductors as a Solid Electrolyte," *J. Chem. Soc. Faraday - T.*, **92**(13), 2393 (1996).

Hibino, T., Hashimoto, A., Inoue, T., Tokuno, J., Yoshida, S. and Sano, M., "A Solid Oxide Fuel Cell Using an Exothermic Reaction as the Heat Source," *J. Electrochem. Soc.*, **148**(6), A544 (2001).

Hwang, S. T. and Kammermeyer, K., "Techniques of Chemistry, VII: Membranes in Separations," Wiley Interscience, New York (1975).

Ilinitch, O. M., Cuperus, F. P. and Nosova, L. V., et al., "Catalytic Membrane in Reduction of Aqueous Nitrates: Operational Principles and Catalytic Performance," *Catal. Today*, **56**(1-3), 137 (2000).

Ioannides, T. and Gavalas, G. R., "Catalytic Isobutane Dehydrogenation in a Dense Silica Membrane Reactor," *J. Membr. Sci.*, **77**(2-3), 207 (1993).

Itoh, N., "A Membrane Reactor Using Palladium," *AIChE J.*, **33**, 1576 (1987).

Itoh, N., Sanchez, M. A. and Xu, W. C., et al., "Application of a Membrane Reactor System to Thermal-Decomposition of CO_2 ," *J. Membr. Sci.*, **77**(2-3), 245 (1993).

Iwahara, H., Esaka, T., Uchida, H., Yamauchi, T. and Okaki, K., "High Temperature Type Protonic Conductor Based on SrCeO_3 and Its Application to the Extraction of Hydrogen Gas," *Solid State Ionics*, **18**, 1003 (1986).

Iwahara, H., Uchida, H. and Morimoto, K., "High Temperature Solid Electrolyte Fuel Cells Using Perovskite-Type Oxide Based on BaCeO_3 ," *J. Electrochem. Soc.*, **137**, 462 (1990).

Iwahara, H., Matsumoto, H. and Takeuchi, K., "Electrochemical Dehumidification Using Proton Conducting Ceramics," *Solid State Ionics*, **136**(Sp. Iss. Si.), 133 (2000).

Jayaraman, V., Lin, Y. S., Pakala, M. and Lin, R. Y., "Fabrication of Ultrathin Metallic Membranes on Ceramic Supports by Sputter Deposition," *J. Membr. Sci.*, **99**, 89 (1995).

Jiang, Y. and Virkar, A. V., "A High Performance, Anode-Supported Solid Oxide Fuel Cell Operating on Direct Alcohol," *J. Electrochem. Soc.*, **148**(7), A706 (2001).

Jiang, Y., Yentekakis, I. V. and Vayenas, C. G., "Methane to Ethylene with 85-Percent Yield in a Gas Recycle Electrocatalytic Reactor-Separator," *Science*, **264**(5165), 1563 (1994).

Jin, W., Li, S., Huang, P., Xu, N., Shi, J. and Lin, Y. S., "Tubular Lanthanum Cobaltite Pervoskite-Type Membrane Reactors for Partial Oxidation of Methane to Syngas," *J. Membr. Sci.*, **166**, 13 (2000).

Jun, C. S. and Lee, K. H., "Preparation of Palladium Membranes from the Reaction of $\text{Pd}(\text{C}_2\text{H}_5)_4(\text{C}_2\text{H}_5)_2$ with H-2: Wet-Impregnated Deposition," *J. Membr. Sci.*, **157**(1), 107 (1999).

Jun, C. S. and Lee, K. H., "Palladium and Palladium Alloy Composite Membranes Prepared by Metal-Organic Chemical Vapor Deposition Method (Cold-Wall)," *J. Membr. Sci.*, **176**(1), 121 (2000).

Jurado, J. R., Moure, C., Duran, P. and Valverde, N., "Preparation and Electrical Properties of Oxygen Conductors in the $\text{Bi}_2\text{O}_3\text{-Y}_2\text{O}_3$ System," *Solid State Ionics*, **28**, 518 (1988).

Kaloyannnis, A. and Vayenas, C. G., "Non-Faradaic Electrochemical Modification of Catalytic Activity. 11. Ethane Oxidation on Pt," *J. Catal.*, **171**(1), 148 (1997).

Kikuchi, E., Uemiya, S., Sato, N., Inoue, H., Ando, H. and Matauda, T., "Reactor Using Microporous Glass-Supported Thin Film of Palladium Application to the Water Gas Shift Reaction," *Chem. Lett.*, 489 (1989a).

Kikuchi, E., Uemiya, S., Sato, N., Inoue, H., Ando, H. and Matsuda, T., "Membrane Reactor Using Microporous Glass Supported Thin Film of Palladium," *Chem. Lett.*, 489 (1989b).

Kim, J. and Lin, Y. S., "Sol-Gel Synthesis and Characterization of Yttria Stabilized Zirconia Membranes," *J. Membr. Sci.*, **139**, 75 (1998).

Kim, J. and Lin, Y. S., "Synthesis and Oxygen Permeation Properties of Ceramic-Metal Dual-Phase Membranes," *J. Membr. Sci.*, **67**, 123 (2000).

Kim, H., Park, S., Vohs, J. M. and Gorte, R. J., "Direct Oxidation of Liquid Fuels in a Solid Oxide Fuel Cell," *J. Electrochem. Soc.*, **148**(7), A693 (2001).

Kobayashi, T., Morishita, S., Abe, K. and Iwahara, H., "Reduction of Nitrogen Oxide by a Steam Electrolysis Cell Using a Proton Conducting Electrolyte," *Solid State Ionics*, **86**(8)(Part 1), 603 (1996).

Kobayashi, T., Abe, K., Ukyo, Y. and Iwahara, H., "Reduction of Nitrogen Oxide Using a Perovskite-Type Protonic Conductor $\text{SrZr}_{0.9}\text{Yb}_{0.1}\text{O}_3\text{-}\alpha'$," *Electrochem.*, **68**(6), 494 (2000a).

Kobayashi, T., Yamazaki, K., Abe, K., Ukyo, Y. and Iwahara, H., "Removal of Nitrogen Oxide by Steam Electrolysis Cell with Proton Conducting Ceramics and a $\text{Co}/\text{Al}_2\text{O}_3$ Catalyst," *J. Ceram. Soc. Jpn.*, **108**(6), 554 (2000b).

Kobayashi, T., Abe, K., Ukyo, Y. and Iwahara, H., "Reduction of Nitrogen Oxide by Steam Electrolysis Cell Using a Protonic Conductor $\text{SrZr}_{0.9}\text{Yb}_{0.1}\text{O}_3\text{-}\alpha'$ and the Catalyst $\text{Sr}/\text{Al}_2\text{O}_3$," *Solid State Ionics*, **134**(3-4), 241 (2000c).

Konno, M., Shindo, M., Sugawara, S. and Saito, S., "A Composite Palladium and Porous Aluminum Oxide Membrane for Hydrogen Gas Separation," *J. Membr. Sci.*, **37**, 193 (1988).

Kreuer, K. D., "On the Development of Proton Conducting Materials for Technological Applications," *Solid State Ionics*, **97**, 1 (1997).

Kruidhof, H., Bouwmeester, H. J. M. V., Doorn, R. H. E. and Burggraaf, A. J., "Influence of Order-Disorder Transition on Oxygen Permeability Through Selected Nonstoichiometric Perovskite-Type Oxi-

des," *Solid State Ionics*, **63-65 B**, 816 (1993).

Langguth, J., Dittmeyer, R., Hofmann, H. and Tomandl, G., "Studies on Oxidative Coupling of Methane Using High-Temperature Proton-Conducting Membranes," *Appl. Catal., A-Gen.*, **158**(1-2), 287 (1997a).

Langguth, J., Dittmeyer, R., Hofmann, H. and Tomandl, G., "Ceramic High Temperature Proton Conductors as a Membrane Concept for Oxidative Coupling of Methane," *Chem.-Ing.-Tech.*, **69**(3), 354 (1997b).

Li, A., Liang, W. and Hughes, R., "The Effect of Carbon Monoxide and Steam on the Hydrogen Permeability of a Pd/Stainless Steel Membrane," *J. Membr. Sci.*, **165**(1), 135 (2000).

Li, Z. Y., Maeda, H., Kusakabe, K., Morooka, S., Anzai, H. and Akiyama, S., "Preparation of Palladium-Silver Alloy Membranes for Hydrogen Separation by the Spray Pyrolysis Method," *J. Membr. Sci.*, **78**, 247 (1993).

Lin, Y. S. and Zeng, Y., "Catalytic Properties of Oxygen Semipermeable Perovskite-Type Ceramic Membrane Materials for Oxidative Coupling of Methane," *J. Catal.*, **164**(1), 220 (1996).

Lin, Y. S. and Zeng, Y., "Catalytic Properties of Oxygen Semipermeable Perovskite-Type Ceramic Membrane Materials for Oxidative Coupling of Methane [164 (1), 220 (1996)]," *J. Catal.*, **168**(2), 546 (1997).

Marnellos, G., Zisekas, S. and Stoukides, M., "Synthesis of Ammonia at Atmospheric Pressure with the Use of Solid State Proton Conductors," *J. Catal.*, **193**(1), 80 (2000).

Matsuda, T., Koike, I., Kubo, N. and Kikuchi, E., "Dehydrogenation of Isobutane to Isobutene in a Palladium Membrane Reactor," *Appl. Catal., A-Gen.*, **96**, 3 (1993).

McKenna, E. A., Othonos, A., Kiratzis, N. and Stoukides, M., "Synthesis of HCN in a Solid-Electrolyte-Cell Reactor," *Ind. Eng. Chem. Res.*, **32**(9), 1904 (1993).

Michaels, A. S., "New Separation Technique for the CPI," *Chem. Eng. Prog.*, **64**(12), 31 (1968).

Michaels, J. N. and Vayenas, C. G., "Kinetics of Vapor-Phase Electrochemical Oxidative Dehydrogenation of Ethylbenzene," *J. Catal.*, **85**, 477 (1984).

Morooka, S., Yan, S. C., Yokoyama, S. and Kusakabe, K., "Palladium Membrane Formed in Macropores of Support Tube by Chemical Vapor Deposition with Crossflow Through a Porous Wall," *Separ. Sci. Technol.*, **30**, 2877 (1995).

Moser, W. R., Becker, Y., Dixon, A. G. and Ma, Y. H., "Catalytic Inorganic Membranes, and Their Modification for Use in Catalyzed Chemical Processes," 5th Annu. Meet. NAMS, Lexington, KY, paper 11E (1992).

Nagamoto, H. and Inoue, H., "Analysis of Mechanism of Ethylene Hydrogenation by Hydrogen Permeating Palladium Membrane," *J. Chem. Eng. Jpn.*, **14**, 377 (1981).

Nagamoto, H. and Inoue, H., "A Reactor with Catalytic Membrane Permeated by Hydrogen," *Chem. Eng. Commun.*, **34**, 315 (1985).

Nagamoto, H. and Inoue, H., "The Hydrogenation of 1,3-Butadiene over a Palladium Membrane," *Bull. Chem. Soc. Jpn.*, **59**, 3935 (1986).

Nam, S. E., Lee, S. H. and Lee, K. H., "Preparation of a Palladium Alloy Composite Membrane Supported in a Porous Stainless Steel by Vacuum Electrodeposition," *J. Membr. Sci.*, **153**(2), 163 (1999).

Neomagus, H. W. J. P., van Swaaij, W. P. M. and Versteeg, G. F., "The Catalytic Oxidation of H₂S in a Stainless Steel Membrane Reactor with Separate Feed of Reactants," *J. Membr. Sci.*, **148**(2), 147 (1998).

Neomagus, H. W. J. P., Saracco, G., Wessel, H. F. W. and Versteeg, G. F., "The Catalytic Combustion of Natural Gas in a Membrane Reactor with Separate Feed of Reactants," *Chem. Eng. J.*, **77**(3), 165 (2000).

Nigara, Y., Mizusaki, J. and Ishigame, M., "Measurement of Oxygen Permeability in CeO₂ Doped CSZ," *Solid State Ionics*, **79**, 208 (1995).

Nigara, Y., Watanabe, K., Kawamura, K., Mizusaki, J. and Ishigame, M., "Oxygen Permeation in ZrO₂-CeO₂-CaO for Application to Oxygen Separation from Thermally Decomposed H₂O," *J. Electrochem. Soc.*, **144**(3), 1050 (1997).

Oertel, M., Schmitz, J., Weirich, W., Jendrysek-Neumann, D. and Schulten, R., "Steam Reforming of Natural Gas with Integrated Hydrogen Separation for Hydrogen Production," *Chem. Eng. Technol.*, **10**, 248 (1987).

Okubo, T., Haruta, K., Kusakabe, K., Morooka, S., Anzai, H. and Akiyama, S., "Equilibrium Shift of Dehydrogenation at Short Space-Time with Hollow Fiber Ceramic Membrane," *Ind. Eng. Chem. Res.*, **30**, 614 (1991).

Otsuka, K. and Yamanaka, I., "Electrochemical Cells as Reactors for Selective Oxygenation of Hydrocarbons at Low Temperature," *Catal. Today*, **41**(4), 311 (1998).

Otsuka, K., Ishizuka, K. and Yamanaka, I., "Synthesis of Cresols by Applying H₂-O₂ Fuel-Cell Reaction," *Electrochim. Acta*, **37**(13), 2549 (1992).

Pan, X. L., Liu, B. J., Xiong, G. X., Sheng, S. S., Liu, J. and Yang, W. S., "Exploration of Cinnamaldehyde Hydrogenation in Co-Pt/Gamma-Al₂O₃ Catalytic Membrane Reactors," *Catal. Lett.*, **66**(3), 125 (2000).

Panagos, E., Voudouris, I. and Stoukides, M., "Modelling of Equilibrium Limited Hydrogenation Reactions Carried Out in H⁺ Conducting Solid Oxide Membrane Reactors," *Chem. Eng. Sci.*, **51**(11), 3175 (1996).

Peterson, D. and Winnick, J., "A Hydrogen Sulfide Fuel Cell Using a Proton-Conducting Solid Electrolyte," *J. Electrochem. Soc.*, **143**(3), L55 (1996).

Petrolekas, P. D., Balomenou, S. and Vayenas, C. G., "Electrochemical Promotion of Ethylene Oxidation on Pt Catalyst Films Deposited on CeO₂," *J. Electrochem. Soc.*, **145**(4), 1202 (1998).

Pliangos, C., Raptis, C., Badas, T. and Vayenas, C. G., "Electrochemical Promotion of NO Reduction by C₃H₆ on Rh/YSC Catalyst-Electrodes," *Solid State Ionics*, **136**(Sp. Iss. Si.), 767 (2000).

Qi, X. W. and Lin, Y. S., "Electrical Conducting and Proton-Conducting Terbium-Doped Strontium Cerate Membrane," *Solid State Ionics*, **120**(1-4), 85 (1999).

Qi, X. W., Lin, Y. S. and Swartz, S. L., "Electric Transport and Oxygen Permeation Properties of Lanthanum Cobaltite Membranes Synthesized by Different Methods," *Ind. Eng. Chem. Res.*, **39**(3), 646 (2000).

Qi, X. W. and Lin, Y. S., "Electrical Conduction and Hydrogen Permeation Through Mixed Proton-Electron Conducting Strontium Cerate Membranes," *Solid State Ionics*, **130**(1-2), 149 (2000).

Qiu, L., Lee, T. H., Liu, L. M., Yang, Y. L. and Jacobson, A. J., "Oxygen Permeation Studies of SrCo_{0.8}Fe_{0.2}O_{3-x}," *Solid State Ionics*, **76**, 321 (1995).

Raich, B. A. and Foley, H. C., "Supra-Equilibrium Conversion in Palladium Membrane Reactors - Kinetic Sensitivity and Time-Dependence," *Appl. Catal., A-Gen.*, **129**(2), 167 (1995).

Raich, B. A. and Foley, H. C., "Ethanol Dehydrogenation with a Palladium Membrane Reactor: An Alternative to Wacker Chemistry," *Ind. Eng. Chem. Res.*, **37**(10), 3888 (1998).

Roth, J. F., "Future Catalysis for the Production of Chemicals," *Stud. Surf. Catal.*, **38**, 925 (1988).

Saracco, G., Versteeg, G. F. and Vanswaaij, W. P. M., "Current Hurdles to the Success of High-Temperature Membrane Reactors," *J. Membr. Sci.*, **95**(2), 105 (1994).

Saracco, G. and Specchia, V., "Catalytic Inorganic-Membrane Reactors - Present Experience and Future Opportunities," *Catal. Rev.*, **36**(2), 305 (1994).

Saracco, G., Neomagus, H. W. J. P., Versteeg, G. F. and van Swaaij, W. P. M., "High-Temperature Membrane Reactors: Potential and Problems," *Chem. Eng. Sci.*, **54**(13-14), 1997 (1999).

Seok, D. R. and Hwang, S. T., "Recent Development in Membrane Reactors," *Stud. Surf. Sci. Catal.*, **54**, 248 (1990).

She, Y., Han, J. and Ma, Y. H., "Palladium Membrane Reactor for the Dehydrogenation of Ethylbenzene to Styrene," *Catal. Today*, **67**(1-3), 43 (2001).

Shu, J., Grandjean, B. P. A., Ghali, E. and Kaliaguine, S., "Simultaneous Deposition of Pd and Ag on Porous Stainless Steel by Electroless Plating," *J. Membr. Sci.*, **77**, 181 (1993).

Shu, J., Grandjean, B. P. A., van Seste, A. and Kaliaguine, S., "Catalytic Palladium-based Membrane Reactors: A Review," *Can. J. Chem. Eng.*, **69**, 1036 (1991).

Song, J. Y. and Hwang, S. T., "Formaldehyde Production from Methanol Using a Porous Vycor Glass Membrane Reactor," *J. Membr. Sci.*, **57**, 95 (1991).

Souleimanova, R. S., Mukasyan, A. S. and Varma, A., "Effects of Osmosis on Microstructure of Pd-Composite Membranes Synthesized by Electroless Plating Technique," *J. Membr. Sci.*, **166**(2), 249 (2000).

Stevenson, J. W., Armstrong, T. R., Carmein, R. D., Pederson, L. R. and Weber, L. R., "Electrochemical Properties of Mixed Conducting Perovskite $\text{La}_{1-x}\text{M}_{x}\text{Co}_{1-y}\text{Fe}_y\text{O}_{3-\delta}$ ($\text{M}=\text{Sr, Ba, Ca}$)", *J. Electrochem. Soc.*, **143**, 2722 (1996).

Stoukides, M., "Solid-Electrolyte Membrane Reactors: Current Experience and Future Outlook," *Catal. Rev.*, **42**(1-2), 1 (2000).

Teraoka, Y., Nobunaga, T. and Yamazoe, N., "Effect of Cation Substitution on the Oxygen Semipermeability of Perovskite-Type Oxides," *Chem. Lett.*, 503 (1988).

Teraoka, Y., Zhang, H. M., Furukawa, S. and Yamazoe, N., "Oxygen Permeation through Perovskite-type Oxides," *Chem. Lett.*, 1745 (1985).

Teymouri, E., Bagherzadeh, E., Petit, C., Rehspringer, J. L., Libs, S. and Kienneman, A., "Reactivity of Perovskites on Oxidative Coupling of Methane," *J. Material Sci.*, **30**, 3005 (1993).

Tiscareno-Lechuga, F., Hill, G. C., Jr. and Anderson, M. A., "Experimental Studies of the Non-Oxidative Dehydrogenation of Ethylbenzene Using a Membrane Reactor," *Appl. Catal. A-Gen.*, **96**, 33 (1993).

Tsai, C. Y., Dixon, A. G., Ma, Y. H., Moser, W. R. and Pascucci, M. R., "Dense Perovskite $\text{La}_{1-x}\text{M}_{x}\text{Co}_{1-y}\text{Fe}_y\text{O}_{3-\delta}$ ($\text{M}=\text{Sr, Ba, Ca}$) Membrane Synthesis, Application, and Characterization," *J. Am. Ceram. Soc.*, **81**, 1437 (1998).

Tsotsis, T. T., Champagnie, A. M., Vasileiadis, S. P., Ziaka, Z. D. and Minet, R. G., "Packed-Bed Catalytic Membrane Reactors," *Chem. Eng. Sci.*, **47**(9-11), 2903 (1992).

Tsotsis, T. T., Champagnie, A. M., Vasileiadis, S. P., Ziaka, A. D. and Minet, R. G., "The Enhancement of Reaction Yield through the Use of High Temperature Membrane Reactors," *Separ. Sci. Technol.*, **28**, 397 (1993).

Tuller, H. L., "Mixed Ionic-Electronic Conduction in a Number of Fluorite and Pyrochlore Compounds," *Solid State Ionics*, **52**, 135 (1992).

Uemiya, S., Kude, Y., Sugino, K., Sato, N., Matsuda, T. and Kikuchi, E., "A Palladium/Porous-Glass Composite Membrane for Hydrogen Separation," *Chem. Lett.*, 1687 (1988).

Uemiya, S., Matsuda, H. and Kikuchi, E., "Aromatization of Propane Assisted by Palladium Membrane Reactor," *Chem. Lett.*, 1335 (1990).

Uemiya, S., Sato, N., Ando, H., Matsuda, T. and Kikuchi, E., "Steam Reforming of Methanol in a Hydrogen Permeable Membrane Reactor," *Appl. Catal. A-Gen.*, **67**, 223 (1991a).

Uemiya, S., Sato, N., Ando, N. and Kikuchi, E., "The Water Gas Shift Reaction Assisted by a Palladium Membrane Reactor," *Ind. Eng. Chem. Res.*, **30**, 585 (1991b).

Uemiya, S., Matsuda, T. and Kikuchi, E., "Hydrogen Permeable Palladium-Silver Alloy Membrane Supported on Porous Ceramics," *J. Membr. Sci.*, **56**, 325 (1991c).

Uemiya, S., Sato, N., Ando, H., Kude, Y., Matsuda, T. and Kikuchi, E., "Separation of Hydrogen Through Palladium Thin Film Supported on a Porous Glass Tube," *J. Membr. Sci.*, **56**, 303 (1991d).

Uemiya, S., Koike, I. and Kikuchi, E., "Promotion of the Conversion of Propane to Aromatics by Use of a Palladium Membrane," *Appl. Catal. A-Gen.*, **76**, 171 (1991e).

Uemiya, S., Koseki, M. and Kojima, T., "Preparation of Highly Permeable Membranes for Hydrogen Separation Using a CVD Technique," in Ma, Y. H. (Ed.), *Proceedings of the Third International Conference on Inorganic Membranes*, Worcester, MA, 545 (1994).

Vayenas, C. G., Bebelis, S., Yentekakis, I. V. and Linz, H. G., "Non-Faradaic Electrochemical Modification of Catalytic Activity: A Status Report," *Catal. Today*, **11**, 303 (1992).

Xomeritakis, G. and Lin, Y. S., "Fabrication of Thin Palladium Membrane Support in a Porous Ceramic Substrate by Chemical Vapor Deposition," *J. Membr. Sci.*, **120**, 261 (1996).

Xomeritakis, G. and Lin, Y. S., "Fabrication of Thin Membranes by MOCVD and Sputtering," *J. Membr. Sci.*, **133**, 217 (1997).

Xu, S. J. and Thomson, W. J., "Stability of $\text{La}_{1-x}\text{Sr}_x\text{Co}_{1-y}\text{Fe}_y\text{O}_{3-\delta}$ Perovskite Membranes in Reducing and Nonreducing Environments," *Ind. Eng. Chem. Res.*, **37**, 1290 (1998).

Yajima, T., Koide, K., Takai, H., Fukatsu, N. and Iwahara, H., "Application of Hydrogen Sensor Using Proton Conductive Ceramics as a Solid Electrolyte to Aluminum Casting Industries," *Solid State Ionics*, **79**, 333 (1995).

Yamanaka, I. and Otsuka, K., "Partial Oxidation of Cyclohexane with Reductively Activated Dioxygen on SmCl_3 Supported on Graphite During $\text{H}_2\text{-O}_2$ Fuel-Cell Reactions," *J. Chem. Soc. Faraday-T.*, **89**(11), 1791 (1993a).

Yamanaka, I. and Otsuka, K., "Partial Oxidation of Alkanes and Aromatics with Activated Oxygen over an SmCl_3 -Embedded Graphite Cathode," *J. Alloy Compd.*, **193**(1-2), 56 (1993b).

Yan, S. et al., "Thin Palladium Membrane Formed in Support Pores by Metal-Organic Chemical Vapor Deposition Method and Application to Hydrogen Separation," *Ind. Eng. Chem. Res.*, **33**, 616 (1994).

Yeung, K. L., Christiansen, S. C. and Varma, A., "Palladium Composite Membranes by Electroless Plating Technique - Relationships Be-

tween Plating Kinetics, Film Microstructure and Membrane Performance," *J. Membr. Sci.*, **159**(1-2), 107 (1999).

Yiokari, C. G., Pitselis, G. E., Polydoros, D. G., et al., "High-Pressure Electrochemical Promotion of Ammonia Synthesis over an Industrial Iron Catalyst," *J. Phys. Chem., A* **104**(46), 10600 (2000).

Zaman, J. and Chakma, A., "Inorganic Membrane Reactors," *J. Membr. Sci.*, **92**(1), 1 (1994).

Zaspalis, V. T., van Praag, W., Keizer, K., van Ommen, J. G., Ross, J. H. R. and Burggraaf, A. J., "Reactor Studies Using Alumina Separation Membranes for the Dehydrogenation of Methanol and Normal-Butane," *Appl. Catal., A-Gen.*, **74**(2), 223 (1991).

Zeng, Y. and Lin, Y. S., "Oxidative Coupling of Methane on Improved Bismuth Oxide Membrane Reactors," *AIChE J.*, **47**(2), 436 (2001).

Zeng, Y. and Lin, Y. S., "Oxygen Permeation and Oxidative Coupling of Methane in Yttria Doped Bismuth Oxide Membrane Reactor," *J. Catal.*, **193**(1), 58 (2000).

Zeng, Y. and Lin, Y. S., "Oxidative Coupling of Methane on Improved Bismuth Oxide Membrane Reactors," *AIChE J.*, **47**(2), 436 (2001).

Zhang, K., Yang, Y. L., Ponnusamy, D., Jacobson, A. J. and Salama, K., "Effect of Microstructure on Oxygen Permeation in $\text{SrCo}_{0.8}\text{Fe}_{0.2}\text{O}_{3-\delta}$," *J. Material Sci.*, **34**, 1367 (1999).

Ziaka, Z. D., Minet, R. G. and Tsotsis, T. T., "A High Temperature Catalytic Membrane Reactor for Propane Dehydrogenation," *J. Membr. Sci.*, **77**, 221 (1993).

Ziegler, S., Theis, J. and Fritsch, D., "Palladium Modified Porous Polymeric Membranes and Their Performance in Selective Hydrogenation of Propyne," *J. Membr. Sci.*, **187**(1-2), 71 (2001).