

Efficient Synthesis of Narrowly Dispersed Brush Polymers via Living Ring-Opening Metathesis Polymerization of Macromonomers

Yan Xia, Julia A. Kornfield, and Robert H. Grubbs*

Arnold and Mabel Beckman Laboratory of Chemical Synthesis, Division of Chemistry and Chemical Engineering, California Institute of Technology, Pasadena, California 91125

Received February 6, 2009; Revised Manuscript Received March 19, 2009

ABSTRACT: Various macromonomers (MMs) were efficiently synthesized through the copper-catalyzed “click” coupling of a norbornene moiety to the chain end of poly(methylacrylate), poly(*t*-butylacrylate), and polystyrene that were prepared using atom transfer radical polymerization. Ring-opening metathesis polymerization (ROMP) of these MMs was carried out using the highly active, fast-initiating ruthenium catalyst (H₂IMes)(pyr)₂(Cl)₂RuCHPh in THF at room temperature. ROMP of MMs was found to be living with almost quantitative conversions (>90%) of MMs, producing brush polymers with very low polydispersity indices of 1.01–1.07 and high *M_n*'s of 200–2600 kDa. The efficient ROMP of such MMs provides facile access to a variety of brush polymers and overcomes previous difficulties in the controlled polymerization of MMs. Atomic force microscopy of the brush polymer products revealed extended, wormlike shapes as a result of significant steric repulsion of densely grafted side chains.

Introduction

Bottle brush polymers are a unique type of macromolecules with a high density of side chains grafted to the backbone.^{1–3} The compact structure leads to an extended backbone conformation, causing the polymer to adopt a cylindrical or wormlike structure.^{4,5} However, facile and precise control over the architecture, size, and functionality of bottle brush polymers remains a central challenge.


Brush polymers are usually prepared by three grafting methods: “grafting from”, “grafting onto”, and “grafting through” (the macromonomer (MM) approach).^{2,3} The “grafting from” approach involves the growth of side chains from backbone polymers with pendent initiation sites (macroinitiators). This approach has been the most widely explored route to brush polymers, and a variety of monomers have been used for both the backbone and the side chain.^{6–11} Importantly, the initiation efficiency from the macroinitiators may be limited due to the high density of initiation sites.^{12,13} The “grafting onto” method has the advantage that it allows for individual preparation of backbone polymers and side chains.^{14–17} The down side is that grafting becomes progressively more difficult as conversion increases, leading to limited grafting density, even when a large molar excess of side chains is used.¹⁶ Among these three methods, only the MM approach guarantees complete grafting (e.g., one side chain per repeating unit). Additionally, the MM approach can afford the most precise and easiest control of side chain length and main chain length, provided that the polymerization of MM is efficient and controlled. However, synthesis of polymacromonomers (polyMM) with a high degree of polymerization (DP) and low polydispersity index (PDI) remains synthetically challenging, largely because of the inherently low concentration of polymerizable groups and the demanding steric hindrance of side chains.

Conventional radical polymerization of highly concentrated MM solution^{18–20} and metallocene-catalyzed polymerization of MM^{21,22} have been shown to yield high molecular weight (MW) polyMM, but with limited conversion and high PDI. Controlled radical,²³ anionic,²⁴ and metathesis polymerizations^{25–30} of MMs have shown limited success, and only low DP's for the backbone of graft polymers were obtained. In several examples,

ring-opening metathesis polymerization (ROMP) of MMs using early transition metals, such as molybdenum, has been used to produce narrowly dispersed polyMMs. However, the DP of the backbone of these polyMMs remained low (typically 5–20).^{25–30} Therefore, these graft polymers were believed to resemble star architectures instead of brushlike structures. In addition, the limited functional group tolerance and air and moisture sensitivity of these catalysts narrow their applications. More recently, Ru-based catalyst **1** was used in the ROMP of MMs (Scheme 1). Although narrowly dispersed graft polymers were obtained, the relatively low reactivity of **1** limited the DP of these graft polymers.^{31,32} To our knowledge, there exists only one example of a narrowly dispersed polyMM with high MW, which was prepared by the ROMP of a polylactide norbornenyl MM using catalyst **1**.³³ Ru catalyst **2** shows greatly increased reactivity as compared to **1**, but the resulting polymers are generally polydisperse due to its slow initiation.³⁴ We have recently reported on a class of pyridine-containing catalysts, including catalyst **3**, that mediate living polymerization. These catalysts exhibit both fast initiation and high reactivity.^{35–37} Catalyst **3** has been shown to polymerize sterically demanding monomers, as Fréchet and co-workers have recently demonstrated the block copolymerization of dendronized norbornenes.³⁸ The fast initiation, high reactivity, and high functional group tolerance of catalyst **3** make it ideal for the polymerization of MMs.


The synthesis of MMs presents another challenge. Most of the reported preparations of norbornenyl MMs involve anionic polymerization using either a functionalized norbornene as the initiator^{25,26} or end-capping of a “living” polymer chain to install the norbornenyl group.^{27–30} However, these routes generally require stringent experimental conditions and limit functionality in the polymer. Over the last 15 years, controlled radical polymerization (CRP) has emerged as a powerful and versatile

Scheme 1. Ru-Based Metathesis Catalysts



* To whom correspondence should be addressed. E-mail: rhg@caltech.edu.

Scheme 2. Synthesis of Monomer 4



technique for the preparation of a variety of functionalized polymers with controlled MW and end group functionality.^{39–41} Wooley and co-workers⁴² and Advincula and co-workers⁴³ have recently studied the syntheses of norbornenyl MMs by atom transfer radical polymerization (ATRP) and reversible addition–fragmentation chain transfer (RAFT) polymerization, respectively, using functionalized norbornenes as the initiator or chain transfer agent. However, the norbornenyl functionality led to bimodal MW distributions with high MW components in both the ATRP and the RAFT polymerization of acrylates even in large excess of monomer. This was attributed to the copolymerization of the norbornene functionality with acrylate monomers. Therefore, we sought a more versatile approach to obtain well-defined norbornenyl MMs prepared via CRP.

The combination of ATRP and “click” functionalization has been demonstrated to be a highly efficient way to synthesize polymers with controlled MW and desired end group functionality for subsequent modifications.^{44–48} Recently, Sumerlin and co-workers reported the synthesis of MMs through the “click” coupling of azido-terminated polymers with propargyl (meth)acrylate with a high degree of end group functionalization.⁴⁹ Considering the reported compatibility of ruthenium catalysts with the triazole group resulted from the “click” reaction,⁵⁰ we sought to extend this approach to the preparation of a variety of norbornenyl MMs by coupling azido-terminated polymers made by ATRP with alkyne-functionalized norbornene. Herein, we report the facile synthesis of various high MW brush polymers with controlled MW and narrow PDI in both the side chain and the backbone from norbornenyl MMs that were prepared efficiently by ATRP and “click” functionalization.

Results and Discussion

Synthesis of Norbornenyl Macromonomers. Norbornene-based monomers (versus cyclobutene- or cyclooctene-based monomers) were chosen as the reactive group on the MMs due to their high ring strains, commercial availability, and the lack of chain transfer in ROMP. Particularly, *exo*-norbornenes were used in this study because they are known to exhibit significantly higher reactivity than their *endo*-norbornenyl analogues due to reduced steric hindrance at the olefin.^{51–53}

To avoid the undesirable copolymerization of norbornene during the preparation of the side chains by ATRP, the norbornenyl functionality was attached to a preformed polymer chain end using copper-catalyzed azide–alkyne “click” chemistry. *exo*-Norbornene monomer **4** bearing a terminal acetylene group was synthesized by condensation of *exo*-norbornene anhydride with 10-amino-1-decanol, followed by esterification with propargylacetic acid mediated by EDC/DMAP (Scheme 2). Both reactions gave clean products in good yields. The long alkyl spacer between norbornene and acetylene is designed to reduce the steric congestion during the ROMP of MMs.

ATRP of methyl acrylate (MA), *tert*-butyl acrylate (*t*BA), and styrene (St) were conducted using a CuBr/PMDETA catalytic system to produce a variety of side chain polymers with different MWs and functionalities. Polymerizations were stopped before 70% conversion was reached to retain the bromine chain-end functionality. Narrowly dispersed polymers were obtained in all cases, and their bromine end groups were subsequently transformed to azides quantitatively through

nucleophilic substitution reaction with NaN₃ in DMF (Figure 1). Absolute polymer MWs were measured using GPC coupled with a multiangle laser light scattering (MALLS) detector (Table 1).

Next, the azido-terminated polymers were coupled with a stoichiometric amount of norbornene monomer **4** in THF at 50 °C in the presence of a catalytic amount of CuBr with PMDETA as the ligand (Scheme 3). Regardless of the type of polymer or the MW, all ATRP polymers were furnished with norbornene end group quantitatively without the need for excess **4**. ¹H NMR spectroscopy clearly showed the end group transformation. When the terminal azide group was transformed to a triazole ring, the ω -terminal methine proton (H_a) resonance of the prepolymer completely shifted from 3.9–4.0 ppm to 4.9–5.1 ppm for PS and from 3.7–3.8 ppm to 5.1–5.3 ppm for PMA and PrBA, respectively. Concomitant appearance of signals from the norbornenyl moiety also confirmed that the desired reaction had taken place (Figure 1). The newly formed triazole proton was also observed to resonate at 7.4–7.5 ppm for PMA and PrBA, but was overlapped with broad aromatic proton signals in the case of PS. Integrations of norbornenyl olefin peak (H_c at 6.25 ppm) and the ω -terminal methine proton (H_a) peak gave a 2:1 ratio, indicating complete “click” coupling. Furthermore, the integrations of norbornenyl olefin and polymer backbone signals were compared to calculate the DP of the polymer. The DPs calculated by ¹H NMR spectroscopy (DP_{NMR}) were in good agreement with the DPs calculated by MALLS-GPC (DP_{GPC}), indicating an overall high degree of end group functionalization of these polymers (Table 1). Furthermore, the GPC peak shape of the prepolymer and its corresponding MM remained unchanged. Interestingly, a difference in elution time of the GPC trace before and after “click” coupling could also be observed for smaller MMs (i.e., NB-PS, M_n = 2.2 kDa, see the Supporting Information, Figure S1). The difference in their elution times may reflect the effect of the relatively large substituted norbornenyl end group (MW = 399.2 Da) on the size of the polymer coil.

ROMP of Macromonomers. We first investigated the ROMP of PrBA-macromonomer (PrBA-MM) as the *tert*-butyl group can be readily hydrolyzed to yield water-soluble poly(acrylic acid) side chains, which can be used as polyelectrolytes and biomaterials, or further modified.¹⁰ NB(PrBA)4700 was dissolved in THF at 0.05 M, and catalyst **3** was injected from a stock solution at different MM to catalyst ratios ([M/C]) at room temperature. The solution became more viscous within a few minutes, and aliquots were withdrawn from the polymerization solutions at different time intervals and terminated immediately with excess vinyl ether. GPC analyses of the aliquots all showed narrow and monomodal peaks for the polyMM, and the MW increased linearly with conversion. The PDIs remained very low throughout the polymerization. Clean first-order kinetics were also observed from the linear logarithmic plots of conversion versus time ($\ln[M]_0/[M]_t$ versus time), indicating a constant concentration of propagating species (Figure 2). The polymerization rates measured by the slopes in the kinetic plot were also proportional to the catalyst loading (Figure 2C). The first-order kinetics and linear MW growth profile both suggest that the living nature of ROMP was





Figure 1. ^1H NMR spectra of end group transformations: (A) PS-Br (top), PS- N_3 (middle), NB(PS)2200 (bottom); (B) PrBA-Br (top), PS- N_3 (middle), NB(PrBA)4700 (bottom).

Table 1. Characteristics of ω -Norbornenyl Macromonomers

sample name ^a	polymer type	$M_{n,\text{GPC}}$ ^b (kDa)	DP_{GPC} ^c	DP_{NMR} ^d	PDI ^b
NB(PMA)3700	PMA	3.7	38	36	1.03
NB(PrBA)4700	PrBA	4.7	33	33	1.03
NB(PS)2200	PS	2.2	17	19	1.03
NB(PS)6600	PS	6.6	60	66	1.02

^a Macromonomers were named using a format of NB(X)Y, with X designating the type of prepolymer and Y designating the M_n of macromonomer. ^b Determined by GPC in THF using RI and MALLS detectors. ^c Calculated by $(M_{n,\text{GPC}} - \text{molar mass of } \mathbf{4} (399.2 \text{ Da}) / \text{molar mass of monomer}$. ^d Calculated by comparing the integrations of norbornenyl olefin and polymer backbone proton signals from ^1H NMR spectra in CDCl_3 .

Scheme 3. Synthesis of Macromonomers



maintained even for MMs with large MWs. Moreover, very high conversions (>90%) were achieved within 5 min for $[\text{M}/\text{C}] = 50$ and within 20 min for $[\text{M}/\text{C}] = 200$ at room temperature, further revealing the extraordinary activity of catalyst **3**. Longer reaction times resulted in almost quantitative conversion (>97%) of MMs to brush polymers, while PDIs remained very low (≤ 1.02).

The MW of the brush polymer, PNB-g-PrBA, could be controlled by the $[\text{M}/\text{C}]$ ratio and was slightly higher than the theoretical values, especially when high $[\text{M}/\text{C}]$ ratios were used. However, the MW was still proportional to the $[\text{M}/\text{C}]$ ratio (entries 1–4 in Table 2). GPC traces of the brush polymers obtained at different $[\text{M}/\text{C}]$ ratios showed a consistent shift toward high MW with increasing the $[\text{M}/\text{C}]$ ratio, while the

peak remained as narrowly dispersed as the macromonomer (Figure 3).

All other types of MMs were polymerized similarly using catalyst **3** at varying $[\text{M}/\text{C}]$ ratios with olefin concentrations of 0.05–0.1 M in THF at room temperature (Scheme 4). As shown in Table 2, all of the brush polymers obtained had very narrow PDIs between 1.0 and 1.1 up to MWs of over 2000 kDa, regardless of the MW, functionality, and conversion of the MMs. The very low PDIs of these brush polymers are likely a result of the narrowly dispersed side chains and the highly efficient polymerization of MMs, leading to complete grafting coverage on the polymer backbone. Conversions of MMs to brush polymers were very high (i.e., >90%) in most cases, and only weak residual MM peaks were noticeable by GPC. Conversions decreased slightly with increasing $[\text{M}/\text{C}]$ ratios and increasing MWs of the MMs. However, the small amount of residual MMs can be easily removed simply through precipitation of the polymer solutions into selective solvents due to the large difference in MW between MMs and brush polymers (see the Supporting Information, Figure S2).

AFM of Brush Polymers. Finally, we used tapping-mode atomic force microscopy (AFM) to directly visualize individual brush polymers. Visualization of densely grafted brush polymers is facilitated by the large side chains, which prevent coiling of the brush polymer backbone due to the high steric congestion. Spin-casting a dilute polymer solution is necessary to disperse individual polymers on the surface for imaging. PS grafted polynorbornene (PNB-g-PS) with the highest MW prepared (entry 14 in Table 2) was spin-cast on highly oriented pyrolytic graphite (HOPG) (Figure 4). AFM revealed cylindrical shapes, which were expected from the densely grafted nature of the polyMMs. These wormlike polymer brushes also had uniform length and width distributions as a result of their low PDI. Measuring multiple polymer brushes gave an average contour length of 140 nm, a width of 30 nm, and a height of 1 nm.




Figure 2. (A) Evolution of GPC traces during ROMP of NB(PtBA)4700; (B) dependence of M_n and PDI on MM conversion; and (C) dependence of $\ln([M]_0/[M]_t)$ on time. Conditions: $[M]_0 = 0.05$ M in THF at room temperature.

Table 2. ROMP of Macromonomers Using Catalyst 3

entry	macromonomer	$[M/C]^a$	$M_{n,theo}$ (kDa) ^b	$M_{n,GPC}$ (kDa) ^c	PDI ^c	DP _{GPC} ^d	conversion ^e
1	NB(PtBA)4700	50	230	267	1.02	57	98%
2	NB(PtBA)4700	100	461	647	1.01	137	98%
3	NB(PtBA)4700	200	921	1140	1.01	242	98%
4	NB(PtBA)4700	400	1842	2620	1.03	557	97%
5	NB(PMA)3700	50	176	202	1.02	55	95%
6	NB(PMA)3700	100	348	420	1.02	114	94%
7	NB(PMA)3700	200	703	891	1.03	241	95%
8	NB(PMA)3700	400	1287	1687	1.05	456	87%
9	NB(PS)2200	100	210	231	1.02	105	93%
10	NB(PS)2200	200	427	534	1.03	243	97%
11	NB(PS)2200	400	836	1271	1.07	578	95%
12	NB(PS)6600	50	330	348	1.01	53	93%
13	NB(PS)6600	100	607	701	1.01	106	92%
14	NB(PS)6600	200	1162	1478	1.02	224	88%

^a MM to catalyst **3** ratio. ^b $M_{n,theo} = M_{n,GPC}(\text{MM}) \times [M/C] \times \text{conversion}$.

^c Determined by GPC in THF using RI and MALLS detectors. ^d DP of brush polymer = $M_{n,GPC}(\text{brush polymer})/M_{n,GPC}(\text{MM})$. ^e Conversion of MM to brush polymer is determined by comparing the peak areas of brush polymer and residual MM from GPC measurement of the crude product.

With a backbone DP = 224, the length per monomeric unit, l_m , was calculated to be 0.62 nm. Considering each polynorbornene repeating unit has five backbone carbons, an average two-carbon distance in the polynorbornene brush polymer is 0.25 nm, corresponding to the value for a fully stretched all trans $-\text{CH}_2-\text{CH}_2-$ bond conformation, l_{max} , of 0.25 nm.⁵ Therefore,





Figure 3. GPC traces of macromonomer NB(PtBA)4700 (black) and crude brush polymers PNB-g-PtBA obtained at $[M/C] = 50$ (blue), 100 (green), and 400 (red). Conditions: $[M]_0 = 0.05$ M in THF at room temperature.

Scheme 4. Synthesis of Polymacromonomer from ω -Norbornenyl MM



the dimensions of the brush polymers suggest an almost fully extended backbone conformation with side chains stretched and flattened on the surface, presumably as a result of significant steric repulsion of side chains that are grafted on every repeating unit of the backbone.

Conclusions

We have efficiently synthesized a series of MMs by “click” coupling of narrowly dispersed azido-terminated prepolymers




Figure 4. Tapping-mode AFM images of brush polymer PNB-g-PS (entry 14 in Table 2) spin-cast from chloroform solution onto HOPG. (a,b) Large-scale height and phase images, bar = 300 nm; (c,d) enlarged height and phase images, bar = 100 nm.

with propargyl norbornene. The ROMP of MMs using pyridine-containing ruthenium catalyst **3** has been found to be a general and highly efficient "grafting through" route for the synthesis of a variety of narrowly dispersed brush polymers. The ROMP of MMs exhibited first-order kinetics with respect to the MM concentration up to almost quantitative conversions (>95%) of MMs. MWs of brush polymers increased linearly with MM conversions and were approximately proportional to the ratios of MM to catalyst. Because of the high efficiency, easy experimental procedure, and high functional group tolerance of the reported modular approach involving ROMP and "click" chemistry, it allows facile access to a variety of well-defined brush polymers with a broad range of functionalities and MWs.

Experimental Section

Materials. THF was purified by passing through solvent purification columns. $(\text{H}_2\text{IMes})(\text{pyr})_2(\text{Cl})_2\text{RuCHPh}$ (**3**) was prepared according to a literature procedure.⁵⁴ *cis*-5-Norbornene-*exo*-2,3-dicarboxylic anhydride was prepared as described previously.³⁷ St, MA, and *t*-BA were passed through a column of basic alumina immediately before use. All other materials were obtained from commercial sources and used as received. Azido-terminated prepolymers, PMA ($M_n = 3270$ g/mol and PDI = 1.03), PrBA ($M_n = 4100$ g/mol and PDI = 1.03), and PS ($M_n = 1800$ g/mol and PDI = 1.03; $M_n = 6200$ g/mol and PDI = 1.03) were synthesized according to literature procedures.^{16,49}

Characterizations. ^1H and ^{13}C NMR spectra were recorded in CDCl_3 using a Varian Mercury 300 or Varian Inova 500 spectrometer. Chemical shifts are reported in ppm relative to CDCl_3 ($\delta = 7.27$).

High-resolution mass spectra (FAB) were provided by the California Institute of Technology Mass Spectrometry Facility.

Gel permeation chromatography (GPC) was carried out in THF on two PLgel 10 μm mixed-B LS columns (Polymer Laboratories) connected in series with a DAWN EOS multiangle laser light scattering (MALLS) detector and an Optilab DSP differential refractometer (both from Wyatt Technology). No calibration standards were used, and dn/dc values were obtained for each injection by assuming 100% mass elution from the columns.

Atomic force microscopy (AFM) images were taken using a Nanoscope IV Scanning Probe Microscope Controller (Digital Instruments, Veeco Metrology Group) in tapping mode in air at room temperature using silicon tips (spring constant = 40–50 N/m, resonance frequency = 170–190 kHz, and tip radius of curvature < 10 nm). The samples were prepared by spin-casting dilute solutions (0.01 wt %) in chloroform onto freshly cleaved highly oriented pyrolytic graphite.

***N*-(Hydroxydecanyl)-*cis*-5-norbornene-*exo*-2,3-dicarboximide.** A round-bottom flask was charged with *cis*-5-norbornene-*exo*-2,3-dicarboxylic anhydride (0.95 g, 5.8 mmol) and 10-amino-1-decanol (1.0 g, 5.8 mmol). To the flask was added 20 mL of toluene, followed by triethylamine (80 μL , 0.58 mmol). A homogeneous solution was obtained upon heating. A Dean–Stark trap was attached to the flask, and the reaction mixture was heated at reflux (135 °C) for 4 h. The reaction mixture was then cooled and concentrated in vacuo to yield an off-white solid. This residue was dissolved in 20 mL of CH_2Cl_2 and washed with 0.1 N HCl (10 mL) and brine (10 mL). The organic layer was dried over MgSO_4 and concentrated in vacuo to yield 1.8 g of colorless, viscous oil (97% yield). ^1H NMR (500 MHz, CDCl_3): δ 1.20–1.28 (m, 13H), 1.49–1.56 (m, 5H), 2.65 (d, $J = 1.5$ Hz, 2H), 3.26 (t, $J = 1.5$ Hz, 2H), 3.44 (t, $J = 7.5$ Hz, 2H), 3.62 (t, $J = 6.5$ Hz, 2H), 6.27 (t, $J = 2.0$ Hz, 2H). ^{13}C NMR (125 MHz, CDCl_3): δ 25.9, 27.1, 27.9, 29.3, 29.5, 29.6, 33.0, 39.0, 42.9, 45.4, 48.0, 63.3, 138.1, 178.4. HRMS (FAB⁺) m/z calcd for $\text{C}_{19}\text{H}_{30}\text{O}_3\text{N}$ [$\text{M} + \text{H}$]⁺, 320.2226; found, 320.2238.

***N*-(Pentynyldecanyl)-*cis*-5-norbornene-*exo*-2,3-dicarboximide **4**.** To a round-bottom flask were added *N*-(hydroxydecanyl)-*cis*-5-norbornene-*exo*-2,3-dicarboximide (0.80 g, 2.5 mmol), *N*-(3-dimethylaminopropyl)-*N'*-ethylcarbodiimide hydrochloride (EDC)

(0.58 g, 3.0 mmol), and 4-dimethylaminopyridine (DMAP) (0.10 g, 0.82 mmol), followed by 10 mL of CH_2Cl_2 . Pentynoic acid (0.25 g, 2.5 mmol) was added as a solution in 5 mL of CH_2Cl_2 via syringe. The reaction mixture was allowed to stir under argon at room temperature overnight. The reaction mixture was washed with water (2 \times 20 mL) and brine (20 mL) and dried over MgSO_4 . The solvent was evaporated, and the remaining residual was purified by silica gel chromatography (ethyl acetate/hexanes, 3:7 v/v) to give 0.81 g of **4** as a colorless oil (81% yield). ^1H NMR (500 MHz, CDCl_3): δ 1.22–1.33 (m, 13H), 1.50–1.55 (m, 3H), 1.62 (t, $J = 7.5$ Hz, 2H), 1.98 (t, $J = 2.5$ Hz, 1H), 2.17–2.56 (m, 4H), 2.67 (d, $J = 1.5$ Hz, 2H), 3.27 (t, $J = 1.5$ Hz, 2H), 3.45 (t, $J = 7.5$ Hz, 2H), 4.09 (t, $J = 7$ Hz, 2H), 6.28 (t, $J = 2.0$ Hz, 2H). ^{13}C NMR (125 MHz, CDCl_3): δ 14.6, 26.1, 27.2, 28.0, 28.8, 29.3, 29.4, 29.5, 29.6, 33.6, 39.0, 42.9, 45.4, 48.0, 65.1, 69.2, 82.8, 138.1, 172.1, 178.4. HRMS (FAB⁺) m/z calcd for $\text{C}_{24}\text{H}_{34}\text{O}_4\text{N}$ [$\text{M} + \text{H}$]⁺, 400.2488; found, 400.2505.

General Procedure for Synthesis of Macromonomers via "Click" Coupling of Prepolymer and **4.** In a typical experiment, to a 20 mL scintillation vial were added 1 g of azido-terminated prepolymer, the desired amount of **4** (1 equiv to prepolymer end group), and CuBr (0.1 equiv to **4**), and a stir bar. The vial was then degassed, and 10 mL of degassed anhydrous THF was added via syringe under an argon atmosphere. PMDETA (1 equiv to CuBr) was injected via a microsyringe. The reaction vial was stirred at 50 °C under argon overnight. The reaction mixture was then passed through a short neutral alumina column to remove the catalyst. The resulting macromonomers were isolated by precipitation into MeOH for NB-PS or by removal of the solvent under high vacuum for NB-PrBA.

General Procedure for ROMP of Macromonomers. In a typical experiment, an oven-dried small vial was charged with 100 mg of macromonomer and a stir bar. The vial was then degassed, and the desired amount of degassed, anhydrous THF ($[\text{M}]_0 = 0.05$ – 0.10 M) was added via syringe under an argon atmosphere to dissolve the macromonomer. A stock solution of catalyst **3** in degassed, anhydrous THF was prepared in a separate vial. The desired amount of catalyst was injected into the macromonomer solution to initiate the polymerization. The reaction vial was stirred at room temperature under argon. After the polymerization was complete, the reaction mixture was quenched with one drop of ethyl vinyl ether. A small sample was withdrawn for GPC measurement. The rest of the reaction mixture was then diluted and precipitated into 10 mL of stirring MeOH for PNB-*g*-(PS) and PNB-*g*-(PMA) and MeOH/water (4:1) for PNB-*g*-(PrBA). A trace amount of residual macromonomer can be readily removed via precipitation into MeOH, MeOH/water (4:1), and cyclohexane/heptane (1:2) for PNB-*g*-(PMA), PNB-*g*-(PrBA), and PNB-*g*-(PS) respectively. The resulting brush polymers were dried in vacuo.

Acknowledgment. This work was supported by the Department of Energy (DE-FG02-05ER46218) and the National Science Foundation (CHE-0410425). We gratefully acknowledge Dr. Bradley D. Olsen and Peigen Cao for helpful discussions about the AFM, and Professor James R. Heath for the use of the AFM.

Supporting Information Available: Additional GPC traces of prepolymers, macromonomers, and brush polymers, ^1H NMR spectra of brush polymers, and AFM cross-sectional analysis of brush polymer. This material is available free of charge via the Internet at <http://pubs.acs.org>.

References and Notes

- Percec, V.; Ahn, C. H.; Ungar, G.; Yeardley, D. J. P.; Möller, M.; Sheiko, S. S. *Nature (London)* **1998**, *391*, 161–164.
- Hadjichristidis, N. P., M.; Pispas, S.; Iatrou, H. *Chem. Rev.* **2001**, *101*, 3747.
- Zhang, M.; Müller, A. H. E. *J. Polym. Sci., Part A: Polym. Chem.* **2005**, *43*, 3461–3481.

- (4) Wintermantel, M.; Gerle, M.; Fischer, K.; Schmidt, M.; Wataoka, I.; Urakawa, H.; Kajiura, K.; Tsukahara, Y. *Macromolecules* **1996**, *29*, 978–983.
- (5) Sheiko, S. S.; Möller, M. *Chem. Rev.* **2001**, *101*, 4099–4124.
- (6) Beers, K. L.; Gaynor, S. G.; Matyjaszewski, K.; Sheiko, S. S.; Möller, M. *Macromolecules* **1998**, *31*, 9413–9415.
- (7) Börner, H. G.; Beers, K.; Matyjaszewski, K.; Sheiko, S. S.; Möller, M. *Macromolecules* **2001**, *34*, 4375–4383.
- (8) Cheng, G.; Böker, A.; Zhang, M.; Krausch, G.; Müller, A. H. E. *Macromolecules* **2001**, *34*, 6883.
- (9) Zhang, M.; Breiner, T.; Mori, H.; Müller, A. H. E. *Polymer* **2003**, *44*, 1449–1458.
- (10) Kriegel, R. M.; Rees, W. S.; Weck, M. *Macromolecules* **2004**, *37*, 6644–6649.
- (11) Runge, M. B.; Dutta, S.; Bowden, N. B. *Macromolecules* **2006**, *39*, 498–508.
- (12) Neugebauer, D.; Sumerlin, B. S.; Matyjaszewski, K.; Goodhart, B.; Sheiko, S. S. *Polymer* **2004**, *45*, 8173–8179.
- (13) Sumerlin, B. S.; Neugebauer, D.; Matyjaszewski, K. *Macromolecules* **2005**, *38*, 702–708.
- (14) Deffieux, A.; Schappacher, M. *Macromolecules* **1999**, *32*, 1797–1802.
- (15) Schappacher, M.; Deffieux, A. *Macromolecules* **2005**, *38*, 7209–7213.
- (16) Gao, H.; Matyjaszewski, K. *J. Am. Chem. Soc.* **2007**, *129*, 6633–6639.
- (17) Schappacher, M.; Deffieux, A. *Science* **2008**, *319*, 1512–1515.
- (18) Tsukahara, Y. M.; K.; Segawa, A.; Yamashita, Y. *Macromolecules* **1989**, *22*, 1546–1552.
- (19) Tsukahara, Y. T.; K.; Yamashita, Y.; Shimada, S. *Macromolecules* **1990**, *23*, 5201–5208.
- (20) Dziezok, P.; Sheiko, S. S.; Fischer, K.; Schmidt, M.; Möller, M. *Angew. Chem., Int. Ed. Engl.* **1997**, *36*, 2812–2815.
- (21) Neiser, M. W.; Okuda, J.; Schmidt, M. *Macromolecules* **2003**, *36*, 5437–5439.
- (22) Neiser, M. W.; Muth, S.; Kolb, U.; Harris, J. R.; Okuda, J.; Schmidt, M. *Angew. Chem., Int. Ed.* **2004**, *43*, 3192–3195.
- (23) Yamada, K.; Miyazaki, M.; Ohno, K.; Fukuda, T.; Minoda, M. *Macromolecules* **1999**, *32*, 290–293.
- (24) Pantazis, D.; Chalari, I.; Hadjichristidis, N. *Macromolecules* **2003**, *36*, 3783–3785.
- (25) Heroguez, V.; Breunig, S.; Gnanou, Y.; Fontanille, M. *Macromolecules* **1996**, *29*, 4459–4464.
- (26) Heroguez, V.; Gnanou, Y.; Fontanille, M. *Macromolecules* **1997**, *30*, 4791–4798.
- (27) Heroguez, V.; Amedro, E.; Grande, D.; Fontanille, M.; Gnanou, Y. *Macromolecules* **2000**, *33*, 7241–7248.
- (28) Nomura, K.; Takahashi, S.; Imanishi, Y. *Polymer* **2000**, *41*, 4345–4350.
- (29) Nomura, K.; Takahashi, S.; Imanishi, Y. *Macromolecules* **2001**, *34*, 4712–4723.
- (30) Murphy, J. J.; Nomura, K. *Chem. Commun.* **2005**, 4080–4082.
- (31) Liaw, D.-J.; Huang, C.-C.; Ju, J.-Y. *J. Polym. Sci., Part A: Polym. Chem.* **2006**, *44*, 3382–3392.
- (32) Hilf, S.; Kilbinger, A. F. M. *Macromol. Rapid Commun.* **2007**, *28*, 1225–1230.
- (33) Jha, S.; Dutta, S.; Bowden, N. B. *Macromolecules* **2004**, *37*, 4365–4374.
- (34) Bielawski, C. W.; Grubbs, R. H. *Angew. Chem., Int. Ed.* **2000**, *39*, 2903–2906.
- (35) Choi, T.-L.; Grubbs, R. H. *Angew. Chem., Int. Ed.* **2003**, *42*, 1743–1746.
- (36) Camm, K. D.; MartinezCastro, N.; Liu, Y.; Czechura, P.; Snelgrove, J. L.; Fogg, D. E. *J. Am. Chem. Soc.* **2007**, *129*, 4168–4169.
- (37) Matson, J. B.; Grubbs, R. H. *J. Am. Chem. Soc.* **2008**, *130*, 6731–6733.
- (38) Rajaram, S.; Choi, T.-L.; Rolandi, M.; Fréchet, J. M. J. *J. Am. Chem. Soc.* **2007**, *129*, 9619–9621.
- (39) Hawker, C. J.; Bosman, A. W.; Harth, E. *Chem. Rev.* **2001**, *101*, 3661–3688.
- (40) Matyjaszewski, K.; Xia, J. *Chem. Rev.* **2001**, *101*, 2921–2990.
- (41) Kamigaito, M.; Ando, T.; Sawamoto, M. *Chem. Rev.* **2001**, *101*, 3689–3746.
- (42) Cheng, C.; Khoshdel, E.; Wooley, K. L. *Macromolecules* **2005**, *38*, 9455–9465.
- (43) Patton, D. L.; Advincula, R. C. *Macromolecules* **2006**, *39*, 8674–8683.
- (44) Gao, H.; Louche, G.; Sumerlin, B. S.; Jahed, N.; Golas, P.; Matyjaszewski, K. *Macromolecules* **2005**, *38*, 8979–8982.
- (45) Lutz, J.-F.; Börner, H. G.; Weichenhan, K. *Macromol. Rapid Commun.* **2005**, *26*, 514–518.
- (46) Golas, P. L.; Tsarevsky, N. V.; Sumerlin, B. S.; Matyjaszewski, K. *Macromolecules* **2006**, *39*, 6451–6457.
- (47) Lutz, J.-F.; Börner, H. G.; Weichenhan, K. *Macromolecules* **2006**, *39*, 6376–6383.
- (48) Whittaker, M. R.; Urbani, C. N.; Monteiro, M. J. *J. Am. Chem. Soc.* **2006**, *128*, 11360–11361.
- (49) Vogt, A. P.; Sumerlin, B. S. *Macromolecules* **2006**, *39*, 5286–5292.
- (50) Binder, W. H.; Kluger, C. *Macromolecules* **2004**, *37*, 9321–9330.
- (51) Asrar, J. *Macromolecules* **1992**, *25*, 5150–5156.
- (52) Rule, J. D.; Moore, J. S. *Macromolecules* **2002**, *35*, 7878–7882.
- (53) Pollino, J. M.; Stubbs, L. P.; Weck, M. *Macromolecules* **2003**, *36*, 2230–2234.
- (54) Love, J. A.; Morgan, J. P.; Trnka, T. M.; Grubbs, R. H. *Angew. Chem., Int. Ed.* **2002**, *41*, 4035–4037.

MA900280C