This article was downloaded by: [University of Haifa Library]

On: 08 August 2012, At: 14:16 Publisher: Taylor & Francis

Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered

office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



Molecular Crystals and Liquid Crystals

Publication details, including instructions for authors and subscription information:

http://www.tandfonline.com/loi/gmcl20

Biocides - Stabilizers Against Biodegradation: New Frontiers

G. E. Zaikov ^a , K. Z. Gumargalieva ^b & M. I. Artsis ^a

^a N.M. Emanuel Institute of Biochemical Physics, Russian Academy of Sciences, Moscow, Russia

^b N.N. Semenov Institute of Chemical Physics, Russian Academy of Sciences, Moscow, Russia

Version of record first published: 28 May 2010

To cite this article: G. E. Zaikov, K. Z. Gumargalieva & M. I. Artsis (2010): Biocides - Stabilizers Against Biodegradation: New Frontiers, Molecular Crystals and Liquid Crystals, 522:1, 255/[555]-267/[567]

To link to this article: http://dx.doi.org/10.1080/15421401003725321

PLEASE SCROLL DOWN FOR ARTICLE

Full terms and conditions of use: http://www.tandfonline.com/page/terms-and-conditions

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden.

The publisher does not give any warranty express or implied or make any representation that the contents will be complete or accurate or up to date. The accuracy of any instructions, formulae, and drug doses should be independently verified with primary sources. The publisher shall not be liable for any loss, actions, claims, proceedings, demand, or costs or damages whatsoever or howsoever caused arising directly or indirectly in connection with or arising out of the use of this material.

 $Mol.\ Cryst.\ Liq.\ Cryst.,$ Vol. 522: pp. 255/[555]–267/[567], 2010 Copyright © Taylor & Francis Group, LLC

ISSN: 1542-1406 print/1563-5287 online DOI: 10.1080/15421401003725321



Biocides – Stabilizers Against Biodegradation: New Frontiers

G. E. ZAIKOV, 1 K. Z. GUMARGALIEVA, 2 AND M. I. ARTSIS 1

¹N.M. Emanuel Institute of Biochemical Physics, Russian Academy of Sciences, Moscow, Russia

²N.N. Semenov Institute of Chemical Physics, Russian Academy of Sciences, Moscow, Russia

The contributors are discussing the problems of properties and applications of biocides. Biocide classification, investigation technique, kinetic of biomass growth in a medium containing biocides, kinetic constants are presenting in the article.

Keywords Bacteria; biocides; biodegradation; biomass; kinetics; microscopic fungi; properties; stabilizers; suppression

Introduction

Biofactors are organisms (bacteria, microscopic fungi) and their associates which cause the breakdown of useful materials. The actions of biofactors can be mechanical, chemical or biological. The degradation of an object caused by biological factors is called biodegradation. The chemical compositions which provide protection against biofactor effects are referred to as biocides and (or) fungicides in the case of protection from microscopic fungi effect.

Systematic research concerning the protection from biodegradation was begun in the 1920s and 1930s. At that time the focus was on biocides development for such materials as textiles, leather, paper glues, etc. Development of new materials, increased consumption, short supply of raw materials, and the increased requirements for trouble-free long term performance, coupled with the ecological problems of disposal of polymeric materials prompted, in the late 1980s, the start of a very active research to discover new and more effective biodegradation protectors.

The leading biodegradation protectors are substances-biocides, whose application is characterized by high efficiency in a variety of forms. Biocides can be: introduced directly into the volume of a material, applied to the material surfaces, added to impregnating or lubricating media, etc. Several thousands of such compounds are known and substances containing alcohol and oxidizing groups, heavy metal ions and surfactants belong to biocides.

Address correspondence to G. E. Zaikov, N.M. Emanuel Institute of Biochemical Physics, Russian Academy of Sciences, 4 Kosygin str., Moscow 119334, Russia. Tel.: +7-495-939-7191; Fax: +7-499-137-4101; E-mail: chembio@sky.chph.ras.ru

Table 1 shows properties of some well-known volatile biocides (fumigants). Tables 2 and 3 show examples of supressing microorganism growth (development) by biocides in technical products, obtained by usual estimation technique.

The effectiveness of biocide action is explained by their capability to penetrate into a microorganism cell or on its surface, and interfere with at least one of the vitally important processes or accumulate microorganism. For example, halogenand sulfur-containing biocides cause oppression of microorganism respiration. Iodides and fluorides decrease the activity of some enzymes. Toxicity of metalorganic compounds possessing heavy metal atoms in their composition is stipulated by their influence (effect) on sulfohydryl groups of enzymes.

Modern biocides are required to possess a high activity against destructive functions of biofactors, but their application must be free of all harmful influences on the environment. In addition, the biocides must be stable at elevated temperatures and on exposure to water and air, etc. It is obvious that the application of biocides must not cause any undesirable effects on physico-chemical, mechanical and other properties of materials. They must not accelerate or cause material aging, corrosion, processibility etc.

Beside these general demands there are some special requirements for biocides, connected with certain features of protected material, its production technology and exploitation conditions. For example, biocides designed for protecting polymer and paint should be easily soluble in organic solvents, combine with other components of materials or evenly (uniformly) distribute in them forming stable emulsions or suspensions.

Biocides designed for wood protection should easily penetrate and chemically interact with cellulose and not affect its painting and adhesive characteristics. The toxicological requirements for biocides are:

- 1. Nontoxicity to warm-blooded animals and human beings, and
- No effects associated with carcinogenesis, mutagenity, embrio-toxicity and allergenity.

Biocide Classification

Chemical biodegradation protectors are classified according to their biological action, chemical composition and purposes. The following subdivision is based on their biological action:

- Fungicides, used for protecting materials and articles (appliances) from degradation by fungi;
- 2. Bactericides, used for protecting from putrid (patrefective), acid-forming and other bacteria;
- Algicides, used for protecting ships and technical buildings from algae and mollusks;
- 4. Insecticides-from insects;
- 5. Zoocides-from rodents.

Biocides are also classified into following groups of materials based on their technical purposes and application:

- 1. Wood, paper, cardboard;
- 2. Synthetic polymer materials, compounds, rubbers (caoutchoucs);
- 3. Textile materials;
- 4. Natural (real) leather and articles from it;

 Table 1. Properties of some well-known volatile biocides (fumigants)

Name	Molecular mass	Temperature of boiling, °C	Solubility in water	Inhibiting concentration, mg/l	Penetrability to material	Biocidic activity
 Methylbromide Propylene oxide Formaldehyde Ethylene oxide β-propyolactone 	95 58 30 44 72	4.6 34 -21 10.4 162	Weak Good Good Complete Moderate	3500 $800 \div 2000$ $3 \div 10$ $400 \div 1000$ $2 \div 5$	Excellent Excellent Moderate Does not penetrate, sterilizes from surface	Weak Excellent Excellent Moderate Moderate

 Table 2. Suppression of microorganism growth by influence of different additives, %

Petrol additive	Concentration,	Mixture of fungi	Glagosporium resinae	Pseudomonas pyncyaneum	Mycobacterium lacticolum
Mixture of aliphatic amines Dimethyl aminomethyl-para-chlorophenol Trialkylphenyl ester of cyclohexyl phosphine T-1* petrol with no additives	0.1 0.5 0.5	100 60 40	100 80 40 Plentif	100 100 80 Plentiful growth	100 100 80
				1	

^{*}Russian trade mark.

		Со	ncentration,	ml/l	
Substance	1	10	50	75	150
10-Phenylphenoxarsin	_	_	_	_	_
10-Chlorphenoxarsin	+	+	+	+	_
10-Ethylphenoxarsin	+	+	_	_	_

Table 3. Fungicidity of heterocyclic arsenic derivatives*

- 5. Petroleum products (petrols, oils, lubricants);
- 6. Lubricating fluids,
- 7. Paint and vanish materials and coverings.

Biocides are subdivided as follows according to their chemical structure:

- 1. Inorganic compounds;
- 2. Hydrocarbons, halogen hydrocarbons and nitrocompositions;
- 3. Alcohols, phenols and their derivatives;
- 4. Aldehydes, ketones, organic acids and their derivatives;
- 5. Amines, amine salts and quaternary ammonium compositions;
- 6. Elementorganic compositions;
- 7. Heterocyclic compositions.

Characteristics of most useful biocides are shown in Table 4.

Biocide Investigation Technique

Traditional methods of biocide activity investigations are based on test analysis of the determination of their inhibiting capability of microorganism development at incubation on solid agarized surface. Fungicide activity is determined by the following equation:

$$\mathbf{R} = \frac{(\mathbf{d}_0 - \mathbf{d}_1) \times 100}{\mathbf{d}_0}.$$
 (2)

Here \mathbf{d}_0 is the control diameter of colonies (mm); \mathbf{d}_1 is the diameter of colonies in presence of a fungicide. A similar approach is used to determine the fungicide activity on microorganism biomass in fluid culture medium.

A new approach to estimate the biocide efficiency is based on determination of kinetic parameters characterizing the growth of microorganisms and materials. The set of these kinetic parameters allows us to select the biocides for specific applications with consideration of time dependence of their effectiveness. In this case the estimation of biocide effectiveness is based on the estimation ofbiomass deceleration with the help of rate constants of biomass growth.

Under normal conditions of biomass growth and parallel degradation of materials we must not rule out the effects of biomass metabolites. That is why we must consider the time dependence of biomass growth rate including its degradation supporting and inhibiting effects. To achieve this goal the initial rates of microoganism development must be determined which involves some experimental difficulties.

Table 4. Fungicides protecting nonmetal materials from mold fungi

Class	Purpose	Substance	Solubility in water, %	Toxicity, D_{50}
1. Inorganic compounds	Wood, paper, cotton and flax fibers	Sodium silicofluoride Na ₂ SiF ₆	0.66% at 20°C	High, 50 mg/kg
	Wood anticeptic Wood anticeptic	Sodium fluoride NaF Sodium dichromate	4% at 20°C 200% at 0°C	High, $100 \div 200 \mathrm{mg/kg}$ Very high, $7 \div 8 \mathrm{mg/kg}$
2. Hydrocarbons, halogen hydrocarbons alcohols	Paper	$Na_2Cr_2O_7$ Diphenyl	Insolible	Low, 3000 mg/kg (rats)
and phenols	Natural (real) leather	2-oxydiphenyl	~0.07% at 25°C	Low, 2700 mg/kg
3. Aldehydes, ketones, carbonic and	Cotton thread Paint and vanish coverings, PVC, polymer materials	Phtalan N-(trichlormethyl	Insoluble	Very low, $\sim 10^4 \mathrm{mg/kg}$
carboammonium acids	etc.	thio)phtalimine		
	Film materials (leather, PVC)	Cyclohexilimide of dichlormaleic acid (cimide)	Insoluble	Moderate, 5200 ÷ 7500 mg/kg

High, $780\mathrm{mg/kg}$	4%	High, 44 mg/kg	Moderate, 1000 mg/kg
Insoluble	Cyclohexyla- mine chromate	%00I	Low soluble
Tetramethyl-	CCH ₃) ₂ NCSSCN(CH ₃) ₂ S S High, $16 \div 20 \mathrm{mg/kg}$	Ethylmercurthiosalicilic acid, Na-salt	8-oxyquinoline
Rubber composites	Volatile fungicide for optical appliances protection	Paper, foamy plastics, optical surfaces	Petroleum lubricating materials
	4. Amines, amine salts, quaternary ammonium compositions	5. Elementorganic- compounds	6. Heterocyclic- compositions

Table 5. Initial rates or biomass accumulation	\mathbf{V}_0 and threshold \mathbf{m}_{∞} values on the
surface of different polymer materials	

Support	$\mathbf{m}_{\infty}, \mu \mathrm{g/cm^2}$	V_0 , $\mu g/cm^2 \times day$	$\mathbf{k}_{\mathrm{eff}} \times 10^6, \ \mathrm{s}^{-1}$
Cellulose	10.5 ± 1	0.60 ± 0.05	1.0
Polyethylene terephtalate	2.4 ± 0.15	0.16 ± 0.02	1.2
Polyethylene	1.5 ± 0.20	0.27 ± 0.02	0.9
Polytetrafluorethylene	1.1 ± 0.1	0.04 ± 0.01	0.7

The radioisotopic technique is used for determining the initial mass: polymer materials, charged as suspension in water or in Chapek-Doj culture medium of microscopic fungi possessing 10^6 cell/ml concentration are incubated tritium water vapours. Tritium accumulation in biomass is proportional to microorganism biomass growth, which possess $\sim 85\%$ of water in the composition. Biomass amount is determined by difference in irradiation intensities of charged and control polymer samples and other supports with the help of liquid oscillation counter.

Experimental kinetic curves are exponential, and equilibrium biomass value \mathbf{m}_{∞} , initial biomass growth rate \mathbf{V}_0 and effective rate constant are determined from them. Effective rate constant is determined from logarithmic anamorphose of experimental kinetic curve. These values represent initial characteristics of the material in relation to the existing class of microorganisms. Table 5 shows these parameters for Aspergillus niger microscopic fungus of 10^6 cell/ml concentration, which is specific in relation to polymer materials and some polymer surfaces.

Kinetics of Biomass Growth in a Medium Containing Biocides

Figure 1 shows a typical S-dependence of *Aspergillus niger* biomass growth at cultivation in liquid Chapek-Doj culture medium.

The curve is described by exponential function:

$$\mathbf{m} = \frac{\mathbf{m}_{\infty}}{1 + \mathbf{a} \exp[\mathbf{b}(\mathbf{t} - \mathbf{L})]}$$
 (2)




Figure 1. Asperillus niger biomass dependence on cultivation time in Chapek-Doj medium.




Figure 2. Dependences of the biomass growth at cultivation in liquid culture medium containing different concentrations of biocides: 1 - 0.1 mg/l; 2 - 0.3 mg/l; 3 - 0.5 mg/l of merthiolate (sodium salt of ethylmercursalicilic acid).

here **a** and **b** are kinetic parameters; \mathbf{m}_{∞} is the threshold biomass value; **L** is time of microorganism adaptation to culture medium, the lag-phase.

Parameters **a** and **b** possess certain physical meaning: a characterizes the capability of a spore to form biomass under present conditions, **b** characterizes specific rate of microorganism growth in present culture medium. Values of **a** and **b** are determined graphically (Fig. 1) linearization of Eq. (2) as follows:

$$\ln\left(\frac{\mathbf{m}_{\infty}}{\mathbf{m}} - 1\right) = \ln \mathbf{a} - \mathbf{b}(\mathbf{t} - \mathbf{L}) \tag{3}$$

Injection of water soluble biocide into the culture medium causes no change in kinetic dependence character of biomass growth (Fig. 2).

All kinetic curves are described by Eq. (2). For different biocide concentrations parameters **a**, **b** and **L** change. Consequently, these parameters may be used for estimation of the biocide efficiency.




Figure 3. Concentration dependence of the lag-phase (*Aspergillus niger* fungus development in presence of the fungicide – Nictedin (1,6-diguanidinohexandihydrochloride)).




Figure 4. The dependence of **b** parameter on the biocide concentration (*Aspergillus niger* development in presence of CuSO₄).

Estimation of biocide properties of water insoluble substances is usually performed in agarized culture media, but this method is not suitable for qualitative estimation because of irregular distribution of water in which biocide is insoluble. That is why hydrogel supports, made from hydroxyethylmethacrylate-porous hydrophilic polymer material, should be used for water insoluble biocides, which form the greater part of fungicide family.

Introduction of higher biocide concentration causes the increase of the lag-phase duration L (Fig. 3) and is described by the following equation:






Figure 5. Kinetic constants of the biocide activity of some substances. ABDM is alkylbenzylmethylammonium chloride.

Table 6. Constants of biocide action effectiveness of chemical substances

	Water soluk	Water soluble biocides	Water insolu	Water insoluble biocides		
Biocides	K _L , 1/mg	K _C , mg/1	$\overline{\mathbf{K_L}}$, cm ² /mg	$\mathbf{K}_{\mathbf{C}},\mathrm{mg/cm}^2$	\mathbf{b}_0 , day^{-1}	\mathbf{L}_0 , day
1. Sodium merthiolate	6.7	0.76			0.0015	1.67
(ethylmercursalicilicacid salt)						
2. ABDM (alkylbenzene	0.17	8.9			0.0015	1.67
dimethylammonium chloride)						
3. 1,6-diguanidinohexadi-	0.028	80.5			0.0015	1.67
hydrochloride (nictedine)						
4. Copper(II) sulfate (CuSO ₄)	0.0005	1950			0.0015	1.67
5. Oxydiphenyl (ODP)	250	0.004			0.0015	1.67
6. N-paratolylmonoimide (PTMI)	62.8	0.05			0.0015	1.67
7. Bis(0,0-1-chlor-tri-brom-			1.9	0.7	0.0015	1.67
isopropyl)-3-chlor-2-						
brompropylphosphanate						
(phlamal)						
8. 2,6-ditertbutyl-4-methyl-phenol			0.2	17.5	0.0015	1.67
(ionol)						
9. Pentachlorphenol			125.2	0.012	0.002	2.8
10. Salicilanilide			44.5	3.79	0.0016	2.2
11. Trilan			21.2	0.02	0.001	1.67
12. Biocine	1	1	20700	9.95	0.0025	

Here L_0 is the lag-phase duration in culture medium possessing no biocide; C is biocide concentration; K_L is the kinetic constant, obtained from the graphics (Fig. 3) by linearization of Eq. (4):

$$\ln \frac{\mathbf{L}}{\mathbf{L}_0} = \mathbf{K}_{\mathbf{L}} \mathbf{C}.$$
(4)

Specific growth rate of a microorganism **b** decreases after biocide injection, if all other factors are equal. The inhibited specific growth rate is described by

$$\mathbf{b_i} = \frac{\mathbf{b_0} \mathbf{K_C}}{\mathbf{K_C} + \mathbf{C}}.\tag{5}$$

Here \mathbf{b}_0 is specific growth rate in absence of biocide; \mathbf{C} is biocide concentration in the medium; $\mathbf{K}_{\mathbf{C}}$ is the constant quantitatively equal to biocide concentration at which $\mathbf{b}_i = \mathbf{b}_0/2$. $\mathbf{K}_{\mathbf{C}}$ is determined from experimental data (Fig. 4) by linearization of Eq. (6)

$$\frac{\mathbf{K_C}}{\mathbf{C}} = \frac{\mathbf{b_i}}{\mathbf{b_0} - \mathbf{b_i}}.\tag{6}$$

 $\mathbf{K}_{\mathbf{C}}$ constant of this biocide is practically independent on concentration and may be used for quantitative estimations of the biocide activity. The higher $\mathbf{K}_{\mathbf{C}}$ value is, the lower is the efficiency of the biocide.

Biocide activity constants K_C and K_L are clearly connected with each other and with the biocide effectiveness. For investigated substrates, the values characterizing their effectiveness presented in $\ln 1/K_C - \ln K_L$ coordinates, fit the straight line (Fig. 5).

Such regularity is used for comparative estimation of biocides and preliminary determination of their concentrations in a material required for reliable protection from biodegradation [3–8]. General characteristics of biocides of inhibition of microorganism development based on kinetic estimates are shown in Tables 6 and 7.

Table 7. Kinetic parameters of *Aspergillus niger* biomass growth. The fungicide is copper(II) sulfate (CuSO₄)

			Fung	gicide conc	entration	n, mg/l		
		C	=0			C =	2000	
		Kinetic parameters						
Conditions of fungus growth	$\mathbf{b}, \mathbf{h}^{-1}$	L, h	a	\mathbf{m}_{∞} , $\mu \mathrm{g/cm}^2$	$\mathbf{b}, \mathbf{h}^{-1}$	L, h	a	\mathbf{m}_{∞} , $\mu \mathrm{g/cm}^2$
Liquid Chapek-Doj culture medium	0.037	40	230	8.5	0.019	120	200	7.8
Hydrogel	0.035	40	113	4.0	0.020	120	90	3.5

References

- [1] Plate, N. A. (1983). Actual Questions of Biodegradation, Nauka Publishers: Moscow, USSR.
- [2] Gumargalieva, K. Z. & Zaikov, G. E. (1995). Chemical Physics, 14(10), 29.
- [3] Jimenez, A. & Zaikov, G. E. (2009). Recent Advance in Research on Biodegradable Polymers and Sustainable Compounds, Nova Science Publishers: New York, USA, Vol 1.
- [4] Varfolomeev, S. D., Burlakova, E. B., Popov, A. A., & Zaikov, G. E. (2009). Biochemical Physics Research Trend, Nova Science Publishers: New York, USA.
- [5] Zaikov, G. E. & Krylova, L. P. (2009). Biotechnology, Biodegradation, Water and Foodstuffs, Nova Science Publishers: New York, USA.
- [6] Zaikov, G. E. & Lomova, T. N. (2008). Progress with Participation of Biological and Related Compounds, Brill Academic Publishers: Amsterdam-Leiden, The Netherlands.
- [7] Sukhareva, L. A., Legonkova, O. A., & Yakovlev, V. S. (2008). *Polymers for Packing and Containers Food Industry*, Zaikov, G. E. (Ed.), VSP International Science Publishers: Boston-Leiden, The Netherlands.
- [8] Zaikov, G. E. (2008). Biotechnology: State of the Art and Prospect for Development, Nova Science Publishers: New York, USA.