

This article was downloaded by:

On: 14 January 2011

Access details: *Access Details: Free Access*

Publisher *Taylor & Francis*

Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



Molecular Simulation

Publication details, including instructions for authors and subscription information:

<http://www.informaworld.com/smpp/title~content=t713644482>

Benchmarking DFT surface energies with quantum Monte Carlo

S. J. Binnie^{abc}, E. Sola^{ad}, D. Alfè^d, M. J. Gillan^{abc}

^a Materials Simulation Laboratory, University College London, London, UK ^b Department of Physics and Astronomy, University College London, London, UK ^c London Centre for Nanotechnology, University College London, London, UK ^d Department of Earth Sciences, University College London, London, UK

To cite this Article Binnie, S. J. , Sola, E. , Alfè, D. and Gillan, M. J.(2009) 'Benchmarking DFT surface energies with quantum Monte Carlo', *Molecular Simulation*, 35: 7, 609 – 612

To link to this Article: DOI: 10.1080/08927020802635145

URL: <http://dx.doi.org/10.1080/08927020802635145>

PLEASE SCROLL DOWN FOR ARTICLE

Full terms and conditions of use: <http://www.informaworld.com/terms-and-conditions-of-access.pdf>

This article may be used for research, teaching and private study purposes. Any substantial or systematic reproduction, re-distribution, re-selling, loan or sub-licensing, systematic supply or distribution in any form to anyone is expressly forbidden.

The publisher does not give any warranty express or implied or make any representation that the contents will be complete or accurate or up to date. The accuracy of any instructions, formulae and drug doses should be independently verified with primary sources. The publisher shall not be liable for any loss, actions, claims, proceedings, demand or costs or damages whatsoever or howsoever caused arising directly or indirectly in connection with or arising out of the use of this material.

Benchmarking DFT surface energies with quantum Monte Carlo

S.J. Binnie^{abc*}, E. Sola^{ad}, D. Alfè^{abcd} and M.J. Gillan^{abc}

^aMaterials Simulation Laboratory, University College London, London, UK; ^bDepartment of Physics and Astronomy, University College London, London, UK; ^cLondon Centre for Nanotechnology, University College London, London, UK; ^dDepartment of Earth Sciences, University College London, London, UK

(Received 31 October 2008; final version received 18 November 2008)

Previous work has demonstrated that for many materials, surface energies σ calculated by density functional theory (DFT) methods depend significantly on the exchange-correlation (xc) functional used. This could pose significant problems when using DFT for predicting structures of nanocrystals both in vacuum and on substrates. Here, we present initial results from a systematic study of σ , for a series of ionic materials using the VASP code and its projector augmented wave implementation of DFT. Calculations on LiH and MgO presented here were performed using four of the functionals available in VASP (LDA, PW91, PBE and RPBE) along with the recent Wu–Cohen modification of PBE. The results we present show that there is indeed a significant variation in σ due to differing functionals. Furthermore, we are able to ascertain which functionals gave the most accurate results by performing calculations of σ for LiH using diffusion quantum Monte Carlo methods that are generally accepted to be significantly more accurate, albeit more expensive, in calculating these quantities.

Keywords: DFT; DMC; surface energy; LiH; MgO

1. Introduction

Over the past 20 years, density functional theory (DFT) [7,8] has become the most popular electronic structure method for a variety of applications. This is mainly due to its relative low cost and general accuracy for the systems being studied. The main approximation in DFT is, of course, the form of the exchange-correlation (xc) functional, having developed from the relatively naive local density approximation (LDA) through the various implementations of the generalised gradient approximation (GGA) to the more recent hybrid functionals that include empirical data. Despite DFT's wide use in surface modelling, there is evidence scattered throughout the literature that the results may be strongly affected by the xc used. When one considers the surface formation energy (σ), which is the reversible work done per unit area in creating a surface in a given crystal, the results are particularly worrying. Here, the rather limited work available seems to suggest that this rather important quantity in surface science is consistently *underestimated* by about 30% by the more advance GGA xcs, whereas the more naive LDA approximation seems to reproduce experiment [2,18] (Tables 1 and 2).

In this study, from which we are presenting some preliminary results, we are looking at a variety of ionic solids. We firstly calculate the bulk properties of each solid using DFT and four different xcs, namely: the Perdew–Wang xc (PW91) [13], PBE [14], the revised form of PBE (rPBE) [6] and the recent Wu–Cohen modification

of PBE (WC) [17]. From this, we are able to see the expected dependence on xc of the various bulk properties. We then calculate the surface formation energy using the different functionals. As experimental data are simply unavailable for many systems and for others have error bars comparable with the differences between xcs, we follow the previous work on this subject in using the diffusion Monte Carlo (DMC) [5] method to produce a benchmark by which to measure the DFT functionals. DMC is a theoretically exact method, where the wavefunction for the many-body Schrödinger equation is represented by a number of walkers, whose motion is governed by a drift–diffusion Green's function, whose evolution in imaginary time projects out the groundstate wavefunction. As this method models the same regime as DFT (zero temperature with no zero-point motion) and the only uncontrolled error is the 'fixed-node' error introduced by the fermion-sign problem, this should provide a very good way of benchmarking the accuracy of the DFT values.

2. Methods

In order to reduce what would amount to a bias towards one particular method, it was decided that the lattice parameter used for each xc and for QMC would be the equilibrium lattice parameter for that particular method, breaking from previous work, where the experimental lattice parameter was used throughout. Hence, the first step in the calculations was to obtain the bulk properties of the

*Corresponding author. Email: s.binnie@ucl.ac.uk

Table 1. DFT bulk parameters: lattice constant (a_0) and bulk modulus (B_0).

Functional	LiH		MgO	
	a_0 (Å)	B_0 (GPa)	a_0 (Å)	B_0 (GPa)
LDA	3.9510	40.5 (5)	4.1690	172.26 (5)
PW91	4.0215	36.37 (9)	4.2543	151.3 (2)
PBE	4.0232	36.53 (8)	4.7062	150.4 (2)
rPBE	4.0302	34.8 (1)	4.2954	142.2 (3)
Wu–Cohen	3.9834	37.00 (8)	4.2356	155.9 (1)
DMC	4.006	35.7 (1)	–	–

system for each method. This was done in the usual way by obtaining the total energy of the crystal at several different primitive cell volumes and then fitting this to a Birch–Murnaghan equation of state. When calculating the surface energies, previous studies have shown that the traditional method of just subtracting the appropriate amount of bulk crystal energy from the total energy of a given thickness of slab can lead to inaccurate results. We therefore decided to use a more recent method [4], where the total energy of several different thicknesses of slab are fitted to:

$$E_{\text{slab}} = 2A\sigma + NE_{\text{bulk}} \quad (1)$$

where N is the number of layers, A the surface area of the slab and E_{bulk} the energy of the bulk crystal per layer (obtained here by fitting). This method allows for a significant cancellation of errors and as such seems to give good values for σ .

There is also the question of the geometry of the atoms at the surface of the slab. With DFT it is fairly easy to let these atoms relax whereas with DMC this would be a particularly expensive and time-consuming task (far more expensive in fact than the rest of the calculations). One solution would have been to use the relaxed geometry from a DFT run in the DMC calculations, but this would inherently bias the DMC result. Therefore, it was decided that the DMC calculations would be done just with the bulk-terminated slabs and the DFT calculations done with both bulk-terminated and relaxed slabs. This would allow

us not only to compare the DFT and DMC results directly, but also to see how big an effect the surface relaxation actually is.

2.1 DFT

The DFT work consisted of projector augmented wave calculations done with the VASP [9] code and the pseudo-potentials supplied with the code. The convergence of total energy with respect to k -point sampling was achieved to within 1 meV per formula unit. This required a $7 \times 7 \times 7$ Monkhorst–Pack grid for bulk LiH and $8 \times 8 \times 8$ for bulk MgO. For the slabs, there was also the thickness of the vacuum layer to be taken into account (as the simulation was periodic in the z -direction). Here, convergence of total energy to within 10 meV per layer was achieved with vacuum layers of $2a_0$ for LiH and $(3/2)a_0$ for MgO (with a_0 being the equilibrium lattice parameter). Slabs of thickness between 1 and 15 atomic layers were calculated with finite-size effects causing us to discard layers 1–2. At the end, we achieved convergence for the surface energies of 0.002 J/m².

2.2 QMC

The DMC method allows us to project out the exact groundstate for a given system. However, due to the fermion-sign problem, for fermionic systems, we are required to know *a priori* all the locations, where the wavefunction is zero (the nodal surface). The usual method therefore is to generate a trial wavefunction (in the form of a Slater determinant) using DFT, which fixes the nodal surface. This is then multiplied by a Jastrow factor (containing usually electron–electron, electron–nucleus and electron–electron–nucleus correlation terms) determined by a variational Monte Carlo (VMC) calculation, in order to reduce the cost of the subsequent DMC calculations. This makes the method variational as we are only projecting out the lowest energy state for the given nodal surface; however, this error is usually quite small.

Table 2. DFT surface energies.

Functional	σ (J/m ²)			
	LiH		MgO	
	Bulk terminated	Relaxed	Bulk terminated	Relaxed
LDA	0.4663	0.4586	1.1807	1.1662
PW91	0.3435	0.3342	0.9233	0.9051
PBE	0.3365	0.3273	0.9107	0.8920
RPBE	0.2723	0.2598	0.7807	0.7592
Wu–Cohen	0.4105	0.4024	1.0276	1.0100
DMC	0.36 (1)	–	–	–

Thus, we used the PWscf code from the Quantum Espresso [3] package to generate the trial wavefunction and the Casino [12] code to perform the VMC and DMC calculations. In order to reduce the expense of the calculations, the Dirac–Fock pseudo-potentials by Trail and Needs [15,16] were used. These are quite hard and thus required quite a high plane-wave cut-off (300 Ry) in PWscf. The wavefunction was then re-expanded in b-spline functions (blips) [1] in order to increase the efficiency of the QMC calculations.

DMC is susceptible to two further errors: firstly, the Green's function is only valid in the limit of an infinitely small timestep in the evolution in imaginary time. Convergence of the total energy to less than 10 meV per formula unit was achieved with timesteps of 0.025 a.u. for the bulk and 0.01 a.u. for the slabs. Secondly, DMC suffers from finite-size errors that come about due to the periodic interactions between simulation cells. These decrease as the size of the simulation cell is increased and can be corrected for. In the bulk crystal, we used the recently proposed method of Kwee et al. [10] (implemented in PWscf by Dr Ester Sola), which corrects for both the single- and two-body effects. This involves correcting as follows:

$$E = E_{\text{DMC}}(L) + E_{\text{LDA}}(\infty) - E_{\text{KZK}}(L) \quad (2)$$

where E_{DMC} is the raw DMC energy at cell size $L \times L \times L$, $E_{\text{LDA}}(\infty)$ the converged LDA energy and $E_{\text{KZK}}(L)$ the calculation done with the Kwee et al. xc at a single k -point and E is the corrected total energy.

For the surface, the KZK functional form breaks down due to its dependence on simulation cell volume so the usual single-body LDA correction was used:

$$E = E_{\text{DMC}}(L) + E_{\text{LDA}}(\infty) - E_{\text{LDA}}(L) \quad (3)$$

where $E_{\text{LDA}}(L)$ is the LDA energy at a single k -point.

Slabs of thickness between one and six atomic layers were calculated, with a free boundary condition on the z -axis. Slabs with one and two layers were neglected because of finite-size effects.

3. Results and discussion

As expected, we have quite clearly seen a bias in the bulk parameters for the systems studied with respect to the xc used. Given the nature of the DFT simulations (zero temperature and the lack of zero-point energy corrections) comparison with experiment here is not particularly useful, but the DMC values would suggest that the predictions of PW91 and PBE are good for LiH.

When looking at the surface formation energy, this dependence is even more pronounced with rPBE producing energies of almost half that of the LDA.

Clearly, this is an unacceptably large variation. For LiH, we can see that the PW91 and PBE xcs provide quite good agreement with DMC. However, previous results on both Pb surfaces [18] and MgO [2] have demonstrated good agreement between LDA and DMC, with the GGA functionals in these cases underestimating the DMC value by around 30%. One explanation for this could be that DFT relies on lucky cancellations of errors in order to reproduce accurate surface energies. It is also good to note that the effect of relaxation of the surface structure on σ is indeed small as we assumed, validating our approach of only comparing bulk-terminated surfaces with DMC.

We note that the previous DMC and DFT calculations on MgO [2] were performed with the experimental lattice parameter and as such more work needs to be done on the dependence of σ on the lattice parameter for a fuller comparison to be made.

Calculations are ongoing to extend the number of systems studied and the DFT results seem to support the trends outlined here. An interesting possibility is the use of high-level quantum chemistry, which has already been successfully used to calculate the cohesive energy of LiH [11] and could also be used to calculate surface energies. This would be a great step forward and, of course, would give another independent benchmark with which to compare DFT and indeed DMC.

In summary, we have demonstrated that there is indeed a significant dependence of both bulk properties and surface energies on the DFT xc functional used and demonstrated, in the cases of LiH and MgO, that the relaxation of the surface contributes a relatively small amount to the total surface energy. Finally, we have presented DMC results for LiH showing the xcs that give the best agreement are the PW91 and PBE implementation of the GGA.

References

- [1] D. Alfè and M.J. Gillan, *Efficient localized basis set for quantum Monte Carlo calculations on condensed matter*, Phys. Rev. B 70 (2004), 161101.
- [2] D. Alfè and M.J. Gillan, *The energetics of oxide surfaces by quantum Monte Carlo*, J. Phys.: Condens. Matter 18(35) (2006), pp. L435–L440.
- [3] S. Baroni, A.D. Corso, S. de Gironcoli, P. Giannozzi, C. Cavazzoni, G. Ballabio, S. Scandolo, G. Chiarotti, P. Focher, A. Pasquarello, et al., <<http://www.pwscf.org>>
- [4] V. Fiorentini and M. Methfessel, *Extracting convergent surface energies from slab calculations*, J. Phys. Condens. Matter 8 (1996), pp. 6525–6529.
- [5] W. Foulkes, L. Mitás, R. Needs, and G. Rajagopal, *Quantum Monte Carlo simulations of solids*, Rev. Modern Phys. 73 (2001), pp. 33–83.
- [6] B. Hammer, L.B. Hansen, and J.K. Nørskov, *Improved adsorption energetics within density-functional theory using revised Perdew-Burke-Ernzerhof functionals*, Phys. Rev. B 59 (1999), pp. 7413–7421.
- [7] P. Hohenberg and W. Kohn, *Inhomogeneous electron gas*, Phys. Rev. 136 (1964), pp. B864–B871.
- [8] W. Kohn and L. Sham, *Self-consistent equations including exchange and correlation effects*, Phys. Rev. 140 (1965), pp. A1133–A1138.

- [9] G. Kresse and J. Furthmüller, *Efficient iterative schemes for ab initio total-energy calculations using a plane-wave basis set*, Phys. Rev. B 54 (1996), pp. 11169–11186.
- [10] H. Kwee, S. Zhang, and H. Krakauer, *Finite-size correction in many-body electronic structure calculations*, Phys. Rev. Lett. 100(12) (2008), 126404.
- [11] F.R. Manby, D. Alfè, and M.J. Gillan, *Extension of molecular electronic structure methods to the solid state: computation of the cohesive energy of lithium hydride*, Phys. Chem. Chem. Phys. 8 (2006), pp. 5178–5180.
- [12] R.J. Needs, M.D. Towler, N.D. Drummond, and P. López Ríos, *CASINO version 2.2 User Manual*, University of Cambridge, Cambridge, 2008.
- [13] J.P. Perdew, J.A. Chevary, S.H. Vosko, K.A. Jackson, M.R. Pederson, D.J. Singh, and C. Fiolhais, *Atoms, molecules, solids, and surfaces: applications of the generalized gradient approximation for exchange and correlation*, Phys. Rev. B 46 (1992), pp. 6671–6687.
- [14] J.P. Perdew, K. Burke, and M. Ernzerhof, *Generalized gradient approximation made simple*, Phys. Rev. Lett. 77 (1996), pp. 3865–3868.
- [15] J.R. Trail and R.J. Needs, *Smooth relativistic Hartree–Fock pseudopotentials for H to Ba and Lu to Hg*, J. Chem. Phys. 122(17) (2005a), 174109.
- [16] J.R. Trail and R.J. Needs, *Norm-conserving Hartree–Fock pseudopotentials and their asymptotic behavior*, J. Chem. Phys. 122(1) (2005b), 014112.
- [17] Z. Wu and R.E. Cohen, *More accurate generalized gradient approximation for solids*, Phys. Rev. B 73 (2006), 235116.
- [18] D. Yu and M. Scheffler, *First-principles study of low-index surfaces of lead*, Phys. Rev. B 70 (2004), 155417.