

A-11058-MS

CIC-14 REPORT COLLECTION  
REPRODUCTION  
COPY

Los Alamos National Laboratory is operated by the University of California for the United States Department of Energy under contract W-7405-ENG-36

*Resonance Equation of State*  
Number 7411,  $Al_2O_3$

LOS ALAMOS NATIONAL LABORATORY



3 9338 00319 4353

Los Alamos

Los Alamos National Laboratory  
Los Alamos, New Mexico 87545

**An Affirmative Action/Equal Opportunity Employer**

**DISCLAIMER**

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

LA-11058-MS

UC-34

Issued: August 1987

**Sesame Equation of State  
Number 7411,  $\text{Al}_2\text{O}_3$**

J. F. Barnes  
S. P. Lyon



**Los Alamos**

Los Alamos National Laboratory  
Los Alamos, New Mexico 87545

SESAME EQUATION OF STATE NUMBER 7411,  $\text{Al}_2\text{O}_3$

J. F. Barnes  
and  
S. P. Lyon

ABSTRACT

A new global equation of state for  $\text{Al}_2\text{O}_3$  ("alumina") has been constructed and placed on the SESAME Library as material number 7411.

---

The compound  $\text{Al}_2\text{O}_3$ , "alumina", occurs abundantly in nature as the mineral corundum. A SESAME equation of state (EOS), material number 7410, was created for alumina in 1972. However, some of the physics models used in producing global EOSs for the data library have changed considerably since that time; in particular, J. D. Johnson's improved treatment<sup>1</sup> (CHART JD Model) of the ion thermal (nuclear) contribution to pressure and energy has been incorporated into the GRIZZLY<sup>2</sup> code and is used as the preferred model. Because of the importance of corundum to mixture EOSs for various soils, we considered it advisable to produce a revised global EOS for the material, and it has been placed on the library as EOS number 7411. Although it turned out that there is no apparent large difference between 7410 and 7411, we do recommend usage of the newer EOS.

Alumina exhibits a very high shear strength which has a considerable effect on the experimentally obtained shock Hugoniot. The data are

thoroughly discussed by Graham and Brooks<sup>3</sup>. The shear offset must be corrected for in constructing an equilibrium equation of state; here we accomplish this by simply representing the  $U_s - U_p$  shock data as given in Marsh<sup>4</sup> by a single straight line through the high pressure data with an intercept at the experimentally obtained bulk sound speed. We used the fit  $U_s = 7.93 + 1.298 U_p$  km/s. Shock data were matched to the Thomas-Fermi Dirac calculations at a compression of 1.35.

We used the GRIZZLY code and treated the compound as an average atom with atomic number  $\bar{Z} = 10.0$  and atomic weight  $\bar{A} = 20.392$ . Density at room temperature was taken as  $3.97 \text{ g/cm}^3$ . GRIZZLY constructed the cold curve using the default formulation of the Grüneisen parameter

$$\gamma(\eta) = \gamma_0 \left(\frac{1}{\eta}\right) + \frac{2}{3} \left[1 - \left(\frac{1}{\eta}\right)\right]^2$$

with  $\gamma_0 = 1.595$ , which is both the thermodynamic value and the 2S+1 value from the shock data. The Debye, or characteristic, temperature was calculated to be 1034 K from longitudinal and transverse sound speeds.

The cohesive energy, or energy required to separate  $\text{Al}_2\text{O}_3$  into 5 separate atoms at 0 K, was calculated as 725 kcal/mole, or 145 kcal/mole for the average atom. The form of the cold curve in expansion was then adjusted with the Lennard-Jones (L-J) parameter in an attempt to produce a critical temperature close to our very rough estimate of 1 eV, a figure based on the known boiling point of  $\text{Al}_2\text{O}_3$ . It proved not to be possible to lower the calculated  $T_c$  beneath about 14,600 K without severely disturbing the calculated isotherms. The corresponding value of the L-J parameter is 0.5.

The following graphs were made for EOS 7411 using the SES2D graphics code. Figures 1 and 2 are the pressure and energy isotherms plotted over the entire temperature range of the tables. Figure 3 shows shock speed versus particle speed along the principal Hugoniot, as used in the model.

#### REFERENCES


1. J. D. Johnson, private communication.
2. J. Abdallah, Jr., "User's Manual for GRIZZLY," Los Alamos National Laboratory report LA-10244-M (September, 1984).
3. R. A. Graham and W. P. Brooks, J. Phys. Chem. Solids 32, 2311 (1971).
4. S. P. Marsh, editor, LASL Shock Hugoniot Data, U.C. Press (1980).

7411-IST  
TEMP (K)  
A-0.00+00  
B-2.98+02  
C-1.16+03  
D-5.80+03  
E-1.16+04  
F-2.32+04  
G-3.48+04  
H-5.80+04  
I-1.16+05  
J-2.32+05  
K-3.48+05  
L-5.80+05

changes ?

THURSDAY 14 MAY 87

M-1.16+06  
N-2.90+06  
O-6.96+06  
P-1.74+07  
Q-6.96+07  
R-2.32+08  
S-1.16+09



T4 CRAY SES2D 1R

Figure 1. Selected pressure isotherms for EOS 7411

7411-IST  
 TEMP (K)  
 A-0.00+00  
 B-2.98+02  
 C-1.16+03  
 D-5.80+03  
 E-1.16+04  
 F-2.32+04  
 G-3.48+04  
 H-5.80+04  
 I-1.16+05  
 J-2.32+05  
 K-3.48+05  
 L-5.80+05

changes?

THURSDAY 14 MAY 87





Figure 2. Selected energy isotherms for EOS 7411

T4 CRAY SES2D 1R

7411-HU1  
E0 MJ/KG  
0.00+00

changes ?

THURSDAY 14 MAY 87



T4 CRAY SES2D 1R


Figure 3. Shock velocity versus particle velocity along the principal Hugoniot for EOS 7411

Printed in the United States of America  
Available from  
National Technical Information Service  
US Department of Commerce  
5285 Port Royal Road  
Springfield, VA 22161

Microfiche (A01)

NTIS		NTIS		NTIS		NTIS	
Page Range	Price Code						
001-025	A02	151-175	A08	301-325	A14	451-475	A20
026-050	A03	176-200	A09	326-350	A15	476-500	A21
051-075	A04	201-225	A10	351-375	A16	501-525	A22
076-100	A05	226-250	A11	376-400	A17	526-550	A23
101-125	A06	251-275	A12	401-425	A18	551-575	A24
126-150	A07	276-300	A13	426-450	A19	576-600	A25
						601 up*	A99

\*Contact NTIS for a price quote.



Los Alamos